

BENNETTE

PAINT MFG. CO., INC.
PRODUCT DATA

ATHLETIC FIELD MARKING PAINT 100655

DESCRIPTION: A quality latex coating designed to provide longer lasting marking lines, sideline stripes, and end zone motifs on grass, dirt, synthetic turf, and other playing field surfaces. This paint is formulated to be windproof, non-dusting, non-toxic, and does not harm grass or turf.

SUGGESTED USES: Interior and exterior athletic fields.

COLORS: White. May be tinted to wide range of pastel colors. Custom colors available for orders of 50 gallons or more.

FINISH: Flat

GLOSS: $\leq 2^\circ/85^\circ$

VEHICLE TYPE: Acrylic Copolymer

RECOMMENDED COVERAGE RATES:

Approximately 400 sq. ft. per gallon
(or 1,200 linear feet of 4" line) @:
5.0 mils wet film thickness
1.0 mils dry film thickness

DRY TIME (@ 77°F and 50% rel. humidity):

To Touch: 30 minutes
To Recoat: 2-4 hours

MIN/MAX TEMP @ APPLICATION:

50°F min / 95°F max

WEIGHT PER GALLON: 10.8 lbs.

VISCOSITY: 108 KU (± 2 KU)

SOLIDS CONTENT:

By Weight: 38% (± 1)
By Volume: 21% (± 1)

FLASH POINT: Water-based, Combustible

RECOMMENDED APPLICATION EQUIPMENT:

Brush - Quality synthetic brush, such as Purdy
Nylox-Swan or Wooster Ultra Pro.
Roll - Synthetic such as Kodawool or Pro Doo-Z,
3/4" to 1 1/4" nap
Spray - Graco or Titan Airless - tip size .015 - .017
Or Traffic Striping Machine

THINNING INSTRUCTIONS: Thin with water if necessary.

CLEAN UP: Clean brushes, rollers, and spray equipment immediately after use with warm, soapy water.

FORMULATED WITHOUT LEAD OR MERCURY

102401



All technical advice, recommendations and services are rendered by the Seller gratis. They are based on technical data that the Seller believes to be reliable, and are intended for use by persons having skill and know-how at their own discretion and risk. Seller assumes no responsibility for results obtained or damages incurred from their use by Buyer in whole or in part. Such recommendations, technical advice or services are not to be taken as a license to operate under or intended to suggest infringement of any existing patent.