

BENNETTE

PAINT MFG. CO., INC.
PRODUCT DATA

SIGNATURE
EXTERIOR
ACRYLIC GLOSS
HOUSE PAINT
20 Series

DESCRIPTION: A 100% acrylic system demonstrating superior application and durability characteristics to a variety of exterior surfaces. Properties include excellent leveling, adhesion, hardness, gloss, resistance to mildew, color and gloss retention, flexibility, and blister resistance. This high performance coating is designed to easily obtain professional results.

SUGGESTED USES: On properly primed exterior surfaces including: wood, vinyl, aluminum and asbestos siding; wood trim; windows; masonry; galvanized and ferrous metal.

COLORS: Super White, standard colors, and tint bases to provide a complete range of colors from pastels to deep tones.

FINISH: Gloss

GLOSS: 80°/60°

VEHICLE TYPE: 100% Acrylic

RECOMMENDED COVERAGE RATES:

Approximately 400 sq. ft. per gallon @:
4.6 mils wet film thickness
1.5 mils dry film thickness

DRY TIME (@ 77°F and 50% rel. humidity):

To Touch: 30 minutes to 1 hour
To Recoat: 8 hours

MIN/MAX TEMP @ APPLICATION:

50°F min / 95°F max

WEIGHT PER GALLON: 10.6 lbs.

VISCOSITY: 100-105 KU (±2 KU)

SOLIDS CONTENT:

By Weight: 47% (±1)
By Volume: 33% (±1)

FLASH POINT: Combustible (water-based)

RECOMMENDED APPLICATION EQUIPMENT:

Brush - Synthetic bristle, such as Purdy XL Sprig
Roll - Synthetic, such as Superfab or Pro Doo-Z, 3/8" to 1/2" nap
Spray - Graco or Titan Airless - tip size .017 - .019

THINNING INSTRUCTIONS: Thinning reduces solids and leveling characteristics can be interrupted. If necessary, thin with up to 1/2 pint of water per gallon of paint.

CLEAN UP: Clean all equipment immediately with warm soapy water.

SURFACE PREPARATION: Surface must be free of dirt, chalk, wax or other foreign substances. Glossy surfaces should be sanded and/or scrubbed with a de-glossing solution. Remove mildew with a solution that kills mildew spores. Check adhesion to suspected alkyd or oil paints in an area prior to applying latex coatings. If an adhesion problem is present, use the proper primer as an intermediate coat. New or unpainted surfaces should be primed in accordance with the "Recommended Bennette Primers" section of this sheet.

RECOMMENDED BENNETTE PRIMERS:

<i>Cedar/Redwood</i>	Acrylic Stain Primer	80230
<i>Wood</i>	Exterior Acrylic Latex Primer	70225
	Exterior Acrylic Latex Primer	90225
	Ext. Oil House Paint Primer*	270225
<i>Block, CMU</i>	Acrylic Blockfiller	80250
	Exterior Acrylic Latex Primer	70225
<i>Concrete</i>	Exterior Acrylic Latex Primer	90225
	Exterior Acrylic Latex Primer	70225
	Exterior Acrylic Latex Primer	90225
<i>Brick</i>	Exterior Acrylic Latex Primer	70225
	Exterior Acrylic Latex Primer	90225
<i>Ferrous Metal</i>	Rust Inhib. Metal Primer, Ylw	280237
	Rust Inhib. Metal Primer, Wht	280227
	Acrylic Metal Primer, Red	80228
<i>Galvanized</i>	Acrylic Metal Primer, White	80227
	Acrylic Metal Primer, Red	80228
	Acrylic Metal Primer, White	80227

***NOTE:** This primer must be completely dry prior to applying this paint

FORMULATED WITHOUT LEAD OR MERCURY

041508



All technical advice, recommendations and services are rendered by the Seller gratis. They are based on technical data that the Seller believes to be reliable, and are intended for use by persons having skill and know-how at their own discretion and risk. Seller assumes no responsibility for results obtained or damages incurred from their use by Buyer in whole or in part. Such recommendations, technical advice or services are not to be taken as a license to operate under or intended to suggest infringement of any existing patent.