

BENNETTE

PAINT MFG. CO., INC.
PRODUCT DATA

**EXTERIOR OIL
WOOD FINISH
SEMI-TRANSPARENT
260223**

DESCRIPTION: A blend of resins and solvents designed to preserve and beautify exterior wood surfaces. Penetrates deep into wood fibers to give excellent durability, moisture resistance, and minimum warping and cracking. Dries to a flat, semi-transparent finish that colors the grain, yet allows it to show through, making for an attractive, rustic appearance.

SUGGESTED USES: On exterior new or weathered wood: fences, siding, shingles, shakes, rough-sawn lumber and lawn furniture.

COLORS: Available in tint bases to provide a range of colors from pastels to deep tones.

FINISH: Flat

GLOSS: $\leq 5^{\circ}/60^{\circ}$

VEHICLE TYPE: Long Oil/Alkyd

RECOMMENDED COVERAGE RATES:

Approximately 400 sq. ft. per gallon @:
4.5 mils wet film thickness
1.0 mils dry film thickness

DRY TIME (@ 77°F and 50% rel. humidity):

To Touch: 2 hours
To Recoat: 24 hours

MIN/MAX TEMP @ APPLICATION:

40°F min / 95°F max

WEIGHT PER GALLON: 7.6 lbs.

VISCOSITY: 45 KU (± 2 KU)

SOLIDS CONTENT:

By Weight: 31% (± 1)
By Volume: 21% (± 1)

FLASH POINT: Combustible

RECOMMENDED APPLICATION EQUIPMENT:

Brush - Natural bristle, such as Purdy Sprig or Wooster Friendly

Roll - Lambswool or synthetic, such as Kodawool or Pro Weave

Spray - Graco or Titan Airless - tip size .011 - .013

THINNING INSTRUCTIONS: Thinning not normally required. If necessary, use Bennette Paint Thinner (330010), up to 1/2 pint per gallon.

CLEAN UP: Clean brushes, rollers, and spray equipment immediately after use with Bennette Thinner (330010).

SURFACE PREPARATION: Surface must be free of dirt, chalk, wax or other foreign substances. Glossy surfaces should be sanded and/or scrubbed with a de-glossing solution. Remove mildew with a solution that kills mildew spores.

RECOMMENDED BENNETTE PRIMERS:

Wood Self Prime (two coat system)

APPLICATION INSTRUCTIONS: To prevent lapping, always keep a 'wet edge' when applying this product.

NOTE: Not recommended for cedar, redwood or other staining substrates.

FORMULATED WITHOUT LEAD OR MERCURY

102401



All technical advice, recommendations and services are rendered by the Seller gratis. They are based on technical data that the Seller believes to be reliable, and are intended for use by persons having skill and know-how at their own discretion and risk. Seller assumes no responsibility for results obtained or damages incurred from their use by Buyer in whole or in part. Such recommendations, technical advice or services are not to be taken as a license to operate under or intended to suggest infringement of any existing patent.