

# BENNETTE

PAINT MFG. CO., INC.  
PRODUCT DATA

## QUICK DRYING SANDING SEALER 280203

**DESCRIPTION:** A top-quality, easy to sand sealer that can be used as a prime or finish coat on interior wood surfaces. Brushes easily and dries quickly to a clear, tough, flexible finish.

**SUGGESTED USES:** Interior wood surfaces such as: Paneling, trim, doors, windows, and cabinets.

**COLORS:** Clear

**FINISH:** Low-Lustre

**GLOSS:** 60-70°/60°

**VEHICLE TYPE:** Vinyl Toluene Copolymer

**RECOMMENDED COVERAGE RATES:**

Approximately 500 sq. ft. per gallon @:  
3.2 mils wet film thickness  
1.0 mils dry film thickness

**DRY TIME (@ 77°F and 50% rel. humidity):**

To Touch: 15 minutes  
To Recoat: 4 hours

**MIN/MAX TEMP @ APPLICATION:**

50°F min / 95°F max

**WEIGHT PER GALLON:** 6.9 lbs.

**VISCOSITY:** 50 KU (±2 KU)

**SOLIDS CONTENT:**

By Weight: 39% (±1)  
By Volume: 32% (±1)

**FLASH POINT:** Flammable

**RECOMMENDED APPLICATION EQUIPMENT:**

Brush - Quality natural bristle brush, such as Purdy Sprig or Wooster Friendly  
Roll - Lambswool or synthetic, such as Kodawool or Pro Weave  
Spray - not recommended for spray application

**THINNING INSTRUCTIONS:** Thinning not normally required. If necessary, use Bennette Paint Thinner (330010), up to 1/2 pint per gallon.

**CLEAN UP:** Clean brushes, rollers, and equipment immediately after use with Bennette Thinner (330010).

**SURFACE PREPARATION:**

*Bare Wood:* Must be clean, dry and free of dirt, grease, and other foreign matter. Fill all holes and cracks and sand smooth. Open grained wood should be filled. Apply a coat of Bennette Sanding Sealer (280203) and sand lightly after drying.

*Previously Finished Wood:* Remove all loose, peeling, and flaking finish by sanding or scraping. Where bare wood is exposed, follow procedures for bare wood. Dull glossy surfaces by sanding.

**FORMULATED WITHOUT LEAD OR MERCURY**

102301



All technical advice, recommendations and services are rendered by the Seller gratis. They are based on technical data that the Seller believes to be reliable, and are intended for use by persons having skill and know-how at their own discretion and risk. Seller assumes no responsibility for results obtained or damages incurred from their use by Buyer in whole or in part. Such recommendations, technical advice or services are not to be taken as a license to operate under or intended to suggest infringement of any existing patent.