

# BENNETTE

PAINT MFG. CO., INC.  
PRODUCT DATA

## INTERIOR ALKYD FLAT DRY FOG 280204

**DESCRIPTION:** A high-hiding, quick drying finish designed for spray application on ceilings and walls. Overspray "dust" is dry enough to be swept from the floor after a drop of 8' or more. Ideal for large production painting of warehouse and plant facilities.

**SUGGESTED USES:** Interior of metal roof decks, truss systems, and other ceiling structures where high-hiding and quick cleanup of overspray are important.

**COLORS:** White. Custom colors are available for orders of 50 gallons or more.

**FINISH:** Flat

**GLOSS:**  $\leq 10^{\circ}/85^{\circ}$

**VEHICLE TYPE:** Alkyd

**RECOMMENDED COVERAGE RATES:**

Approximately 400 sq. ft. per gallon @:  
4.0 mils wet film thickness  
1.6 mils dry film thickness

**DRY TIME (@ 77°F and 50% rel. humidity):**

To Touch: 1 hour  
To Recoat: 8 hours

**MIN/MAX TEMP @ APPLICATION:**

40°F min / 95°F max

**WEIGHT PER GALLON:** 11.0 lbs.

**VISCOSITY:** 80 KU ( $\pm 2$  KU)

**SOLIDS CONTENT:**

By Weight: 52% ( $\pm 1$ )  
By Volume: 40% ( $\pm 1$ )

**FLASH POINT:** Flammable

**RECOMMENDED APPLICATION EQUIPMENT:**

Brush - Not recommended  
Roll - Not recommended  
Spray - Graco or Titan Airless - tip size .015 - .019

**THINNING INSTRUCTIONS:** Thinning is not normally required. If necessary, use Bennette VM&P Naphtha (330002), up to 1/2 pint per gallon.

**CLEAN UP:** Clean brushes, rollers, and spray equipment immediately after use with Bennette VM&P Naphtha (330002).

**SURFACE PREPARATION:** Surface must be clean and dry. Remove all dirt, loosely adhering paint, and other foreign matter. Do not apply to damp surfaces.

**FORMULATED WITHOUT LEAD OR MERCURY**

102401



All technical advice, recommendations and services are rendered by the Seller gratis. They are based on technical data that the Seller believes to be reliable, and are intended for use by persons having skill and know-how at their own discretion and risk. Seller assumes no responsibility for results obtained or damages incurred from their use by Buyer in whole or in part. Such recommendations, technical advice or services are not to be taken as a license to operate under or intended to suggest infringement of any existing patent.