

BENNETTE

PAINT MFG. CO., INC.
PRODUCT DATA

WHITE RUST INHIBITING METAL PRIMER 280227

DESCRIPTION: A rust inhibiting primer formulated to give optimum protection to ferrous metal surfaces. Provides excellent corrosion resistance for commercial and industrial steel applications.

SUGGESTED USES: Equipment, tanks, structural steel and any other ferrous metal surface where a white or light color topcoat is required.

COLORS: White

FINISH: Low Sheen

GLOSS: 5°/60°

VEHICLE TYPE: Medium Oil/Alkyd

PIGMENT TYPE: Titanium Dioxide, Zinc Phosphate, and Silicates

RECOMMENDED COVERAGE RATES:

Approximately 400 sq. ft. per gallon @:
4.0 mils wet film thickness
1.8 mils dry film thickness

DRY TIME (@ 77°F and 50% rel. humidity):

To Touch: 3 hours
To Recoat: 24 hours

MIN/MAX TEMP @ APPLICATION:

40°F min / 95°F max

WEIGHT PER GALLON: 10.4 lbs.

VISCOSITY: 75 KU (±2 KU)

SOLIDS CONTENT:

By Weight: 72% (±1)
By Volume: 45% (±1)

FLASH POINT: Combustible

RECOMMENDED APPLICATION EQUIPMENT:

Brush - Natural bristle, such as Purdy Sprig or Wooster Friendly

Roll - Lambswool or synthetic, such as Kodawool or Pro Weave

Spray - Graco or Titan Airless - tip size .013 - .015

THINNING INSTRUCTIONS: Thinning is not normally required. If necessary, use Bennette Paint Thinner (330010), up to 1/2 pint per gallon.

CLEAN UP: Clean brushes, rollers, and spray equipment immediately after use with Bennette Thinner (330010).

SURFACE PREPARATION: Surface must be clean, dry, and free of dirt, grease, oil and grime. Loose rust and mill scale should be removed by scraping, wire brushing and sandblasting.

**RECOMMENDED BENNETTE FINISHES:
INTERIOR/EXTERIOR**

<i>Flat</i>	Flat Black Enamel	280207
<i>Semi-Gloss</i>	Bronzestone Enamel	280846
	Semi-Gloss Black Enamel	280206
	Acrylic 17 Acrylic Enamel	17 series
<i>Gloss</i>	Quick Drying Enamel	29 series

INTERIOR (see NOTE below)

<i>Flat</i>	Signature Interior Latex Flat	1 series
<i>Eggshell</i>	Signature Acrylic Eggshell Enml	4 series
	Interior Alkyd Eggshell Enamel	280806
<i>Satin</i>	Signature Acrylic Satin Enamel	38 series
<i>Semi-Gloss</i>	Signature Acrylic Semi-Gloss	24 series
	Bright Touch Alkyd Semi-Gloss	25 series
	Pro's Choice Alkyd Semi-Gloss	280263

Other finishes may be acceptable. Contact Bennette Paint Mfg. Co., Inc. for more information.

NOTE: Bennette 280233 is recommended as an intermediate coat on interior surfaces.

FORMULATED WITHOUT LEAD OR MERCURY
102301



All technical advice, recommendations and services are rendered by the Seller gratis. They are based on technical data that the Seller believes to be reliable, and are intended for use by persons having skill and know-how at their own discretion and risk. Seller assumes no responsibility for results obtained or damages incurred from their use by Buyer in whole or in part. Such recommendations, technical advice or services are not to be taken as a license to operate under or intended to suggest infringement of any existing patent.