

BENNETTE

PAINT MFG. CO., INC.
PRODUCT DATA

**ALKYD ZONE
MARKING PAINT
BLACK
280252**

DESCRIPTION: A quick drying, durable paint formulated for use on traffic bearing surfaces. The abrasion resistant film is unaffected by water, oil, weather, and chemicals applied to icy streets during winter. Traffic beads can be applied while the film is still wet to provide reflectorized markings.

SUGGESTED USES: Streets, parking lots, and lane marking areas. Interior/exterior cement and asphalt surfaces.

COLORS: Black

FINISH: Flat

GLOSS: 1°/85°

VEHICLE TYPE: Alkyd

RECOMMENDED COVERAGE RATES:

Approximately 400 linear feet per gallon @:
10.0 mils wet film thickness
5.0 mils dry film thickness

DRY TIME (@ 77°F and 50% rel. humidity):

To Touch: 15 minutes
To Recoat: 1 hour

MIN/MAX TEMP @ APPLICATION:

40°F min / 95°F max

WEIGHT PER GALLON: 12.0 lbs.

VISCOSITY: 80 KU (±2 KU)

SOLIDS CONTENT:

By Weight: 71% (±1)
By Volume: 46% (±1)

FLASH POINT: Flammable

RECOMMENDED APPLICATION EQUIPMENT:

Brush - Quality natural bristle, such as Purdy Sprig or Wooster Yachtsman.
Roll - Lambswool or synthetic, such as Kodawool or Pro Weave
Spray - Graco or Titan airless traffic striper

THINNING INSTRUCTIONS: Thinning is not normally required. If necessary, use Bennette VM&P (330002), up to 1/2 pint per gallon.

CLEAN UP: Clean brushes, rollers, and spray equipment immediately after use with Bennette VM&P (330002).

SURFACE PREPARATION: Generally, no surface preparation is required. Heavy grease and oil should be removed to promote adhesion. Broom sweep loose dirt and dust.

NOTE: Not recommended for use on freshly sealcoated asphalt (see 80252).

FORMULATED WITHOUT LEAD OR MERCURY

102401



All technical advice, recommendations and services are rendered by the Seller gratis. They are based on technical data that the Seller believes to be reliable, and are intended for use by persons having skill and know-how at their own discretion and risk. Seller assumes no responsibility for results obtained or damages incurred from their use by Buyer in whole or in part. Such recommendations, technical advice or services are not to be taken as a license to operate under or intended to suggest infringement of any existing patent.