

BENNETTE

PAINT MFG. CO., INC.
PRODUCT DATA

EXTERIOR LATEX, SEMI-GLOSS GLOSS LEVEL 5

32-11
MPI #11

DESCRIPTION: A 100% acrylic coating designed for superior performance on a wide range of surfaces. This high-hiding coating dries fast to a tough, uniform semi-gloss finish and has excellent adhesion, gloss & color retention, durability, and flexibility. Also exhibits excellent resistance to blistering, peeling, mildew, staining, and weathering.

SUGGESTED USES: On properly primed exterior surfaces including: wood, vinyl, aluminum and asbestos siding; wood trim; windows; masonry; galvanized and ferrous metal.

COLORS: Super White, Black, standard colors, and tint bases to provide a complete range of colors from pastels to deep tones.

FINISH: Semi-gloss

GLOSS: 35-70 units @ 60°

VEHICLE TYPE: 100% Acrylic

RECOMMENDED COVERAGE RATES:

Approximately 400 sq. ft. per gallon @:
4.0 mils wet film thickness
1.2 mils dry film thickness

DRY TIME (@ 77°F and 50% rel. humidity):

To Touch: 30 minutes
To Recoat: 8 hours

MIN/MAX TEMP @ APPLICATION:

50°F min / 95°F max

WEIGHT PER GALLON: 10.15 lbs.

VISCOSITY: 90-95 KU (±2 KU)

SOLIDS CONTENT:

By Weight: 42% (±1)
By Volume: 30% (±1)

FLASH POINT: Water-based, Combustible

RECOMMENDED APPLICATION EQUIPMENT:

Brush - Quality synthetic bristle, such as Purdy
Nylox-Swan or Wooster Ultra Pro.
Roll - Synthetic such as Kodawool or Pro Doo-Z
Spray - Graco or Titan Airless - tip size .017 - .019

THINNING INSTRUCTIONS: Thinning not normally required. If necessary, thin with water, no more than 1/2 pint per gallon.

CLEAN UP: Clean brushes, rollers, and spray equipment immediately after use with warm, soapy water.

SURFACE PREPARATION: Surface must be free of dirt, chalk, wax or other foreign substances. Glossy surfaces should be sanded and/or scrubbed with a de-glossing solution. Remove mildew with a solution that kills mildew spores. Check adhesion to suspected alkyd or oil paints in an area prior to applying latex coatings. If an adhesion problem is present, use the proper primer as an intermediate coat. New or unpainted surfaces should be primed in accordance with the "Recommended Bennette Primers" section of this sheet.

RECOMMENDED BENNETTE PRIMERS:

<i>Wood</i>	Exterior Latex Wood Primer	32-6
<i>Block, CMU</i>	Int/Ext Latex Blockfiller	32-4
<i>Concrete</i>	Exterior Latex Wood Primer	32-6
<i>Brick</i>	Exterior Latex Wood Primer	32-6
<i>Ferrous Metal</i>	Anti-Corrosive Metal Primer	32-79
	Surface Tolerant Metal Primer	32-23
	Rust Inhibitive Primer (W. B.)	32-107
<i>Galvanized</i>	Galvanized Primer (W. B.)	32-134
	Rust Inhibitive Primer (W. B.)	32-107
	Galvanized Primer (W. B.)	32-134

Other primers may be acceptable. Contact Bennette Paint Mfg. Co., Inc. for more information.

This product was formulated with no mercury compounds, asbestos, silica sand, lead chromate, or insecticide and not more than 0.06 percent lead.

042105



All technical advice, recommendations and services are rendered by the Seller gratis. They are based on technical data that the Seller believes to be reliable, and are intended for use by persons having skill and know-how at their own discretion and risk. Seller assumes no responsibility for results obtained or damages incurred from their use by Buyer in whole or in part. Such recommendations, technical advice or services are not to be taken as a license to operate under or intended to suggest infringement of any existing patent.