

BENNETTE

PAINT MFG. CO., INC.
PRODUCT DATA

**INTERIOR/
EXTERIOR LATEX
BLOCK FILLER**
32-4
MPI #4

DESCRIPTION: A heavy-bodied, highly pigmented acrylic latex recommended for filling porous surfaces of cement, concrete and masonry block. Suitable for use beneath both interior and exterior coatings, latex or solvent thinned. Sound and moisture transmissions can be reduced with a properly applied blockfiller and topcoat system.

SUGGESTED USES: Interior/exterior concrete block, cinder block, brick, stucco and other porous masonry surfaces as a base for suitable topcoats or as an interior finish.. Drywall ceilings or walls to provide a heavy textured, non-uniform finish.

COLORS: White. May be tinted to provide a wide range of pastel colors.

FINISH: Flat

GLOSS: $\leq 5^{\circ}/60^{\circ}$

VEHICLE TYPE: 100% Acrylic

RECOMMENDED COVERAGE RATES:

Approximately 50-125 sq. ft. per gallon @:

10 - 25 mils wet film thickness

5 - 10 mils dry film thickness

DRY TIME (@ 77°F and 50% rel. humidity):

To Touch: 30 minutes to 1 hour

To Recoat: 4 hours

MIN/MAX TEMP @ APPLICATION:

50°F min / 95°F max

WEIGHT PER GALLON: 13.7 lbs.

VISCOSITY: 115-120 KU (± 2 KU)

SOLIDS CONTENT:

By Weight: 70% (± 1)

By Volume: 52% (± 1)

FLASH POINT: Water-based, Combustible

RECOMMENDED APPLICATION EQUIPMENT:

Brush - Quality synthetic brush, such as Purdy Nylox-Swan or Wooster Ultra Pro.

Roll - Synthetic such as Kodawool or Pro Doo-Z, 3/4" to 1 1/4" nap

Spray - Graco or Titan Airless - tip size .025 - .035

Note: Remove filter to ensure flow.

THINNING INSTRUCTIONS: Thinning is not normally required. If necessary, thin with water, no more than 1/2 pint per gallon.

CLEAN UP: Clean brushes, rollers, and spray equipment immediately after use with warm, soapy water.

SURFACE PREPARATION: Surface must be dry, clean and free of dirt, chalk, wax, or other foreign substances. Glossy and non-weathered areas should be sanded and/or scrubbed with a de-glossing solution. Remove mildew with a solution that kills mildew spores. Do not apply late in the day or when dew, moisture, or condensation is likely to form on the newly painted surface.

NOTE: For spray application, best results are obtained by back-rolling the coating while still wet to work it into the porous surface.

RECOMMENDED BENNETTE FINISHES:

Flat Exterior Latex, Flat 32-10

Satin High Perf. Arch. Latex - GL4 32-140

Semi-Gloss High Perf. Arch. Latex - GL5 32-141

Exterior Latex, Semi-Gloss 32-11

W.B. Light Industrial Coating 32-110-2

Textured Latex Stucco & Masonry Texture 32-42

Other finishes may be acceptable. Contact Bennette Paint Mfg. Co., Inc. for more information.

This product was formulated with no mercury compounds, asbestos, silica sand, lead chromate, or insecticide and not more than 0.06 percent lead.

012203



EMPLOYEE
OWNED
COMPANY

All technical advice, recommendations and services are rendered by the Seller gratis. They are based on technical data that the Seller believes to be reliable, and are intended for use by persons having skill and know-how at their own discretion and risk. Seller assumes no responsibility for results obtained or damages incurred from their use by Buyer in whole or in part. Such recommendations, technical advice or services are not to be taken as a license to operate under or intended to suggest infringement of any existing patent.