

# BENNETTE

PAINT MFG. CO., INC.  
PRODUCT DATA

## STUCCO AND MASONRY COAT COARSE

32-41  
MPI #41

**DESCRIPTION:** A heavy-bodied, 100% acrylic fibered coating that decorates and protects. Combines the aesthetic qualities of a coarse texture finish with the durability of a top quality acrylic system. Exhibits excellent resistance to moisture and mildew, remains flexible, and hides minor surface imperfections.

**SUGGESTED USES:** Exterior (and interior) filled or primed masonry surfaces where a coarse textured finish is desired. Can also be used on properly primed interior drywall and wood.

**COLORS:** White. May be tinted to a wide range of pastel colors. Custom colors are readily available.

**FINISH:** Coarse texture

**GLOSS:**  $\geq 5$  units @ 60°

**VEHICLE TYPE:** Acrylic Polymer

**RECOMMENDED COVERAGE RATES:**

Approximately 60-75 ft. per gallon @:  
10-12 mils wet film thickness  
6-8 mils dry film thickness

**DRY TIME (@ 77°F and 50% rel. humidity):**

To Touch: 2-4 hours  
To Recoat: 48 hours

**MIN/MAX TEMP @ APPLICATION:**

50°F min / 95°F max

**WEIGHT PER GALLON:** 10.4 lbs.

**VISCOSITY:** 125 KU ( $\pm 2$  KU)

**SOLIDS CONTENT:**

By Weight: 63% ( $\pm 1$ )  
By Volume: 59% ( $\pm 1$ )

**FLASH POINT:** Water-based, Combustible

**RECOMMENDED APPLICATION EQUIPMENT:**

Brush - Quality synthetic brush, such as Purdy  
Nylox-Swan or Wooster Ultra Pro.  
Roll - Texture Roller  
Spray - Texture machine & hopper gun or auger-driven texture pump

**THINNING INSTRUCTIONS:** Thinning is not normally required. If necessary, thin with water, no more than 1 pint per gallon.

**CLEAN UP:** Clean brushes, rollers, and spray equipment immediately after use with warm, soapy water.

**SURFACE PREPARATION:** Surface must be free of dirt, chalk, wax or other foreign substances. Glossy surfaces should be sanded and/or scrubbed with a de-glossing solution. Remove mildew with a solution that kills mildew spores. Check adhesion to suspected alkyd or oil paints in an area prior to applying latex coatings. If an adhesion problem is present, use the proper primer as an intermediate coat. New or unpainted surfaces should be primed in accordance with the "Recommended Bennette Primers" section of this sheet.

**RECOMMENDED BENNETTE PRIMERS:**

**INTERIOR**

|                |                              |       |
|----------------|------------------------------|-------|
| <i>Drywall</i> | Interior Vinyl Primer Sealer | 80225 |
| <i>Wood</i>    | Interior Vinyl Primer Sealer | 80225 |

**INTERIOR/EXTERIOR**

|                   |                               |       |
|-------------------|-------------------------------|-------|
| <i>Block, CMU</i> | Acrylic Blockfiller           | 80250 |
| <i>Wood</i>       | Exterior Acrylic Latex Primer | 70225 |
| <i>Concrete</i>   | Exterior Acrylic Latex Primer | 70225 |
| <i>Brick</i>      | Exterior Acrylic Latex Primer | 70225 |

**FORMULATED WITHOUT LEAD OR MERCURY**

030706



All technical advice, recommendations and services are rendered by the Seller gratis. They are based on technical data that the Seller believes to be reliable, and are intended for use by persons having skill and know-how at their own discretion and risk. Seller assumes no responsibility for results obtained or damages incurred from their use by Buyer in whole or in part. Such recommendations, technical advice or services are not to be taken as a license to operate under or intended to suggest infringement of any existing patent.