

BENNETTE

PAINT MFG. CO., INC.
PRODUCT DATA

**INTERIOR/
EXTERIOR ALKYD,
GLOSS
32-48
MPI #48**

DESCRIPTION: A superior quality interior/exterior high gloss alkyd enamel designed for use on a wide variety of surfaces. Dries to a smooth, durable, abrasion resistant finish that is resistant to fading, cracking, and peeling, is non-yellowing and non-chalking, and exhibits excellent gloss and color retention.

SUGGESTED USES: Properly primed interior and exterior structural steel, equipment and tanks, wood trim, doors, cabinets, furniture and masonry surfaces.

COLORS: White, Black, OSHA Safety Colors, standard colors and tint bases to provide a complete range of colors from pastels to deep tones.

FINISH: Gloss

GLOSS: 80° min/60°

VEHICLE TYPE: Medium Oil/Alkyd

RECOMMENDED COVERAGE RATES:

Approximately 400 sq. ft. per gallon @:
4.0 mils wet film thickness
1.6 mils dry film thickness

DRY TIME (@ 77°F and 50% rel. humidity):

To Touch: 4 hours
To Recoat: 12 hours

MIN/MAX TEMP @ APPLICATION:

40°F min / 95°F max

WEIGHT PER GALLON: 9.6 lbs.

VISCOSITY: 80 KU (±2 KU)

SOLIDS CONTENT:

By Weight: 59% (±1)
By Volume: 41% (±1)

FLASH POINT: Combustible

RECOMMENDED APPLICATION EQUIPMENT:

Brush - Quality natural bristle, such as Purdy Sprig or Wooster Yachtsman.

Roll - Synthetic such as Kodawool or Pro Doo-Z, 1/4" nap

Spray - Graco or Titan Airless - tip size .015 - .017

THINNING INSTRUCTIONS: Thinning is not normally required. If necessary, use Bennette Paint Thinner (330010), up to 1/2 pint per gallon. For spray application, thin with Bennette VM&P Naphtha (330002) up to 1/2 pint per gallon.

CLEAN UP: Clean brushes, rollers, and spray equipment immediately after use with Bennette Thinner (330010).

SURFACE PREPARATION: Surface must be free of dirt, chalk, wax or other foreign substances. Glossy surfaces should be sanded and/or scrubbed with a de-glossing solution. Remove mildew with a solution that kills mildew spores. New or unpainted surfaces should be primed in accordance with the "Recommended Bennette Primers" section of this sheet.

RECOMMENDED BENNETTE PRIMERS:

<i>Block, CMU</i>	Int/Ext Latex Blockfiller	32-4
<i>Ferrous Metal</i>	Anti-Corrosive Metal Primer	32-79
	Surface Tolerant Metal Primer	32-23
	Rust Inhibitive Primer (W. B.)	32-107
<i>Galvanized</i>	Galvanized Primer (W. B.)	32-134
	Rust Inhibitive Primer (W. B.)	32-107
	Galvanized Primer (W. B.)	32-134

INTERIOR

<i>Drywall</i>	Interior Enamel Undercoat	32-46
<i>Plaster</i>	Interior Enamel Undercoat	32-46
<i>New Wood</i>	Interior Enamel Undercoat	32-46

EXTERIOR

<i>Wood</i>	Exterior Alkyd Wood Primer	32-5
-------------	----------------------------	------

This product was formulated with no mercury compounds, asbestos, silica sand, lead chromate, or insecticide and not more than 0.06 percent lead.

012203



All technical advice, recommendations and services are rendered by the Seller gratis. They are based on technical data that the Seller believes to be reliable, and are intended for use by persons having skill and know-how at their own discretion and risk. Seller assumes no responsibility for results obtained or damages incurred from their use by Buyer in whole or in part. Such recommendations, technical advice or services are not to be taken as a license to operate under or intended to suggest infringement of any existing patent.