

BENNETTE

PAINT MFG. CO., INC.
PRODUCT DATA

EXTERIOR ALKYD WOOD PRIMER 32-5 MPI #5

DESCRIPTION: A high quality long oil alkyd primer designed to give controlled penetration over new wood and badly weathered surfaces. Seals new wood to ensure a uniform finish. Forms a tough, flexible, mildew resistant film that provides an excellent foundation for any quality Bennette exterior finish.

SUGGESTED USES: Exterior wood siding, trim, windows, and doors. Mildly chalked exterior surfaces.

COLORS: White, may be tinted to pastel colors to approximate color of finish coat.

FINISH: Eggshell

GLOSS: 5-10°/60°

VEHICLE TYPE: Long Oil Alkyd

PIGMENT TYPE: Titanium Dioxide, Silicates

RECOMMENDED COVERAGE RATES:

Approximately 400 sq. ft. per gallon @:
4.0 mils wet film thickness
1.9 mils dry film thickness

DRY TIME (@ 77°F and 50% rel. humidity):

To Touch: 8 hours
To Recoat: 48 hours

MIN/MAX TEMP @ APPLICATION:

50°F min / 95°F max

WEIGHT PER GALLON: 10.5 lbs.

VISCOSITY: 90 KU (±2 KU)

SOLIDS CONTENT:

By Weight: 71% (±1)
By Volume: 48% (±1)

FLASH POINT: Combustible

RECOMMENDED APPLICATION EQUIPMENT:

Brush - Natural bristle, such as Purdy Spring
or Wooster Friendly
Roll - Lambswool or synthetic, such as Kodawool or
Pro Weave
Spray - Graco or Titan Airless - tip size .017 - .019

THINNING INSTRUCTIONS: Thinning is not normally required. If necessary, use Bennette Paint Thinner (330010), up to 1/2 pint per gallon.

CLEAN UP: Clean brushes, rollers, and spray equipment immediately after use with Bennette Thinner (330010).

SURFACE PREPARATION: Surface must be free of dirt, chalk, wax or other foreign substances. Glossy surfaces should be sanded and/or scrubbed with a de-glossing solution. Remove mildew with a solution that kills mildew spores.

**RECOMMENDED BENNETTE FINISH:
EXTERIOR**

<i>Satin</i>	High Perf. Arch. Latex GL4	32-140
<i>Semi-Gloss</i>	High Perf. Arch. Latex GL5	32-141
<i>Gloss</i>	Exterior Alkyd Semi-Gloss	32-94

Other finishes may be acceptable. Contact Bennette Paint Mfg. Co., Inc. for more information.

NOTE: Not recommended for cedar or redwood - use Bennette 80230 instead.

This product was formulated with no mercury compounds, asbestos, silica sand, lead chromate, or insecticide and not more than 0.06 percent lead.

012203



All technical advice, recommendations and services are rendered by the Seller gratis. They are based on technical data that the Seller believes to be reliable, and are intended for use by persons having skill and know-how at their own discretion and risk. Seller assumes no responsibility for results obtained or damages incurred from their use by Buyer in whole or in part. Such recommendations, technical advice or services are not to be taken as a license to operate under or intended to suggest infringement of any existing patent.