

BENNETTE

PAINT MFG. CO., INC.
PRODUCT DATA

**INTERIOR ALKYD -
GLOSS LEVEL 3
32-51
MPI #51**

DESCRIPTION: A quality alkyd enamel that combines the attractive qualities of an eggshell sheen with the durability of an alkyd enamel. It has excellent adhesion and dries to a hard, smooth, velvet finish - the choice of many of today's architects. Alkyd eggshell is attractive on both walls and trim.

SUGGESTED USES: Interior walls, doors, windows, and trim in: Homes, offices, classrooms, hospitals, factories, interior drywall, plaster, CMU, and cement block. Especially suited for kitchens and bathrooms.

COLORS: White tint base provides a wide range of pastel colors. Customer colors are readily available.

FINISH: Eggshell

GLOSS: 10-15°/60°

VEHICLE TYPE: Alkyd

RECOMMENDED COVERAGE RATES:

Approximately 400 sq. ft. per gallon @:
4.0 mils wet film thickness
2.1 mils dry film thickness

DRY TIME (@ 77°F and 50% rel. humidity):

To Touch: 2-4 hours
To Recoat: 24 hours

MIN/MAX TEMP @ APPLICATION:

40°F min / 95°F max

WEIGHT PER GALLON: 11.4 lbs.

VISCOSITY: 90 KU (±2 KU)

SOLIDS CONTENT:

By Weight: 78% (±1)
By Volume: 55% (±1)

FLASH POINT: 104°F

RECOMMENDED APPLICATION EQUIPMENT:

Brush - Quality natural bristle, such as Purdy Sprig or Wooster Yachtsman.

Roll - Synthetic such as Kodawool or Pro Doo-Z, 1/4" to 3/8" nap

Spray - Graco or Titan Airless - tip size .013 - .015

THINNING INSTRUCTIONS: Thinning is not normally required. If necessary, use Bennette Paint Thinner (330010), up to 1/2 pint per gallon for brush and roller, up to 1 pint per gallon for spraying.

CLEAN UP: Clean brushes, rollers, and spray equipment immediately after use with Bennette Thinner (330010).

SURFACE PREPARATION: Surface must be free of dirt, chalk, wax or other foreign substances. Glossy surfaces should be sanded and/or scrubbed with a de-glossing solution. Remove mildew with a solution that kills mildew spores. Previously painted surfaces in good condition may be cleaned and spot-primed with the appropriate primer. Do not apply to any damp or wet surfaces. New or unpainted surfaces should be primed in accordance with the "Recommended Bennette Primers" section of this sheet.

RECOMMENDED BENNETTE PRIMERS:

<i>Block, CMU</i>	Int/Ext Latex Blockfiller	32-4
<i>Concrete</i>	Interior Latex Primer Sealer	32-50
<i>Drywall</i>	Interior Latex Primer Sealer	32-50
<i>Ferrous Metal</i>	Rust Inhibitive Primer (W. B.)	32-107
	Galvanized Primer (W. B.)	32-134
	Anti-Corrosive Metal Primer	32-79
	Surface Tolerant Metal Primer	32-23
<i>Galvanized</i>	Rust Inhibitive Primer (W. B.)	32-107
	Galvanized Primer (W. B.)	32-134
<i>Plaster</i>	Interior Enamel Undercoat	32-46
<i>Wood</i>	Interior Enamel Undercoat	32-46

Other primers may be acceptable. Contact Bennette Paint Mfg. Co., Inc. for more information.

This product was formulated with no mercury compounds, asbestos, silica sand, lead chromate, or insecticide and not more than 0.06 percent lead.

012203



All technical advice, recommendations and services are rendered by the Seller gratis. They are based on technical data that the Seller believes to be reliable, and are intended for use by persons having skill and know-how at their own discretion and risk. Seller assumes no responsibility for results obtained or damages incurred from their use by Buyer in whole or in part. Such recommendations, technical advice or services are not to be taken as a license to operate under or intended to suggest infringement of any existing patent.