

BENNETTE

PAINT MFG. CO., INC.
PRODUCT DATA

**INTERIOR OIL
MODIFIED CLEAR
URETHANE SATIN**
32-57
MPI #57

DESCRIPTION: A premium quality oil modified polyurethane designed for use on interior hardwood floors. Improved dry time allows faster recovery to dwellings than many slower curing satin urethanes. Serves as a very effective sealer on wood when thinned 10% with Bennette Paint Thinner (330010). Not recommended over lacquer sealers, shellac, or fillers containing stearates.

SUGGESTED USES: Interior hardwood floors. Interior plywood, paneling, cabinets, and furniture.

COLOR: Clear

FINISH: Satin

GLOSS: 30-40°/60°

VEHICLE TYPE: Oil Modified Polyurethane

RECOMMENDED COVERAGE RATES:

Depending upon porosity of wood

3.2 mils wet yielding 1.1 mils dry @ 500 sq. ft./gallon
OR

2.5 mils wet yielding 0.9 mils dry @ 650 sq. ft./gallon

DRY TIME (@77°F and 50% rel. humidity):

To Touch: 1-2 hours

To Recoat: 8 hours

MIN/MAX TEMP @ APPLICATION:

50°F min / 90°F max

WEIGHT PER GALLON: 7.3 lbs.

VISCOSITY: 50-60 seconds (#4 FC)

SOLID CONTENT:

By Weight: 41% (±1)

By Volume: 35% (±1)

FLASH POINT: 100°F

RECOMMENDED APPLICATION EQUIPMENT:

Brush - Quality natural bristle brush, such as Purdy
Sprig or Wooster Friendly

Roll - Lambswool pad applicator.

THINNING INSTRUCTIONS: Thinning not normally required. If necessary, use Bennette Paint Thinner (330010), up to 1/2 pint per gallon. Up to 1 pint per gallon for use as a sealer on new floors.

CLEAN UP: Clean brushes, rollers, and spray equipment immediately after use with Bennette Thinner (330010).

SURFACE PREPARATION:

Bare Wood: Must be clean, dry and free of dirt, grease, and other foreign matter. Fill all holes and cracks then sand smooth. Open grained wood should be filled. Use 1 pint of Bennette Paint Thinner (330010) per gallon of material for sealer coat. Additional coats require full strength application.

Previously Finished Wood: Remove all loose, peeling, and flaking finish by sanding or scraping. Where bare wood is exposed, follow procedures for bare wood. Dull glossy surfaces by sanding.

This product was formulated with no mercury compounds, asbestos, silica sand, lead chromate, or insecticide and not more than 0.06 percent lead.

012203



All technical advice, recommendations and services are rendered by the Seller gratis. They are based on technical data that the Seller believes to be reliable, and are intended for use by persons having skill and know-how at their own discretion and risk. Seller assumes no responsibility for results obtained or damages incurred from their use by Buyer in whole or in part. Such recommendations, technical advice or services are not to be taken as a license to operate under or intended to suggest infringement of any existing patent.