

BENNETTE

PAINT MFG. CO., INC.
PRODUCT DATA

EXTERIOR LATEX WOOD PRIMER

32-6
MPI #6

DESCRIPTION: An exterior primer which combines excellent adhesion and sealing properties with fast dry time and easy application. Formulated to develop a "breathing" system when topcoated with any quality Bennette Exterior Latex Finish.

SUGGESTED USES: Properly prepared exterior wood siding, trim, windows, and doors, vinyl and aluminum siding, and non-porous masonry surfaces.

COLORS: White, may be tinted to pastel colors to approximate color of finish coat.

FINISH: Low Sheen

GLOSS: $\leq 5^\circ/60^\circ$

VEHICLE TYPE: 100% Acrylic

PIGMENT TYPE: Titanium Dioxide, Silicates, Zinc, and Mica

RECOMMENDED COVERAGE RATES:

Approximately 400 sq. ft. per gallon @:
4.0 mils wet film thickness
1.4 mils dry film thickness

DRY TIME (@ 77°F and 50% rel. humidity):

To Touch: 30 minutes - 1 hour
To Recoat: 2 - 4 hours

MIN/MAX TEMP @ APPLICATION:

50°F min / 95°F max

WEIGHT PER GALLON: 11.0 lbs.

VISCOSITY: 85-90 KU (± 2 KU)

SOLIDS CONTENT:

By Weight: 52% (± 1)
By Volume: 36% (± 1)

FLASH POINT: Water-based, Combustible

RECOMMENDED APPLICATION EQUIPMENT:

Brush - Quality synthetic brush, such as Purdy Nylox-Swan or Wooster Ultra Pro.
Roll - Synthetic such as Kodawool 1/2" to 3/4" nap
Spray - Graco or Titan Airless - tip size .015 - .017

THINNING INSTRUCTIONS: Thinning is not normally required. If necessary, thin with water, not more than 1/2 pint per gallon.

CLEAN UP: Clean brushes, rollers, and spray equipment immediately after use with warm, soapy water.

SURFACE PREPARATION: Surface must be free of dirt, chalk, wax or other foreign substances. Glossy surfaces should be sanded and/or scrubbed with a de-glossing solution. Remove mildew with a solution that kills mildew spores. Check adhesion to suspected alkyd or oil paints in an area prior to applying latex coatings. If an adhesion problem is present, use the proper primer as an intermediate coat.

RECOMMENDED BENNETTE FINISHES:

<i>Flat</i>	Exterior Latex, Flat	32-10
<i>Satin</i>	High Perf. Arch. Latex - GL4	32-140
<i>Semi-Gloss</i>	High Perf. Arch. Latex - GL5	32-141
	Exterior Latex, Semi-Gloss	32-11
	W.B. Light Industrial Coating	32-110-2
<i>Textured</i>	Latex Stucco & Masonry Texture	32-42

Other finishes may be acceptable. Contact Bennette Paint Mfg. Co., Inc. for more information.

NOTE: Not recommended for cedar or redwood - use Bennette 80230 instead.

This product was formulated with no mercury compounds, asbestos, silica sand, lead chromate, or insecticide and not more than 0.06 percent lead.

012203



All technical advice, recommendations and services are rendered by the Seller gratis. They are based on technical data that the Seller believes to be reliable, and are intended for use by persons having skill and know-how at their own discretion and risk. Seller assumes no responsibility for results obtained or damages incurred from their use by Buyer in whole or in part. Such recommendations, technical advice or services are not to be taken as a license to operate under or intended to suggest infringement of any existing patent.

BENNETTE

PAINT MFG. CO., INC.
PRODUCT DATA

**EXTERIOR LATEX
WOOD PRIMER**
32-6
MPI #6

|| 102202



All technical advice, recommendations and services are rendered by the Seller gratis. They are based on technical data that the Seller believes to be reliable, and are intended for use by persons having skill and know-how at their own discretion and risk. Seller assumes no responsibility for results obtained or damages incurred from their use by Buyer in whole or in part. Such recommendations, technical advice or services are not to be taken as a license to operate under or intended to suggest infringement of any existing patent.