

# BENNETTE

PAINT MFG. CO., INC.  
PRODUCT DATA

**EXTERIOR ALKYD,  
SEMI-GLOSS  
32-94  
MPI #94**

**DESCRIPTION:** A premium quality alkyd finish that resists chalking and fading. Formulated to flow out evenly and dry to a uniform, full gloss finish that weathers extremely well. Provides an unsurpassed level of protection for all exterior wood surfaces.

**SUGGESTED USES:** On properly primed exterior wood siding, wood trim, and metal.

**COLORS:** Super White, standard colors and tint bases to provide a range of colors from pastels to deep tones.

**FINISH:** Semi-Gloss, Gloss Level 5

**GLOSS:** 85-95°/60°

**VEHICLE TYPE:** Long Oil/Alkyd

**RECOMMENDED COVERAGE RATES:**

Approximately 400 sq. ft. per gallon @:  
4.0 mils wet film thickness  
2.4 mils dry film thickness

**DRY TIME (@ 77°F and 50% rel. humidity):**

To Touch: 6 hours  
To Recoat: 24-48 hours

**MIN/MAX TEMP @ APPLICATION:**

50°F min / 95°F max

**WEIGHT PER GALLON:** 11.7 lbs.

**VISCOSITY:** 95 KU (±2 KU)

**SOLIDS CONTENT:**

By Weight: 78% (±1)  
By Volume: 61% (±1)

**FLASH POINT:** Combustible

**RECOMMENDED APPLICATION EQUIPMENT:**

Brush - Natural bristle, such as Purdy Spring  
or Wooster Friendly  
Roll - Lambswool or synthetic, such as Kodawool or  
Pro Weave  
Spray - Graco or Titan Airless - tip size .017 - .019

**THINNING INSTRUCTIONS:** Thinning not normally required. If necessary, use Bennette Paint Thinner (330010), up to 1/2 pint per gallon.

**CLEAN UP:** Clean brushes, rollers, and spray equipment immediately after use with Bennette Thinner (330010).

**SURFACE PREPARATION:** Surface must be free of dirt, chalk, wax or other foreign substances. Glossy surfaces should be sanded and/or scrubbed with a de-glossing solution. Remove mildew with a solution that kills mildew spores. New or unpainted surfaces should be primed in accordance with the "Recommended Bennette Primers" section of this sheet.

**RECOMMENDED BENNETTE PRIMERS:**

<i>Wood</i>	Exterior Alkyd Wood Primer	32-5
<i>Ferrous Metal</i>	Anti-Corrosive Metal Primer	32-79
	Surface Tolerant Metal Primer	32-23
	Rust Inhibitive Primer (W. B.)	32-107
	Galvanized Primer (W. B.)	32-134
<i>Galvanized</i>	Rust Inhibitive Primer (W. B.)	32-107
	Galvanized Primer (W. B.)	32-134

This product was formulated with no mercury compounds, asbestos, silica sand, lead chromate, or insecticide and not more than 0.06 percent lead.

012203



All technical advice, recommendations and services are rendered by the Seller gratis. They are based on technical data that the Seller believes to be reliable, and are intended for use by persons having skill and know-how at their own discretion and risk. Seller assumes no responsibility for results obtained or damages incurred from their use by Buyer in whole or in part. Such recommendations, technical advice or services are not to be taken as a license to operate under or intended to suggest infringement of any existing patent.