

BENNETTE

PAINT MFG. CO., INC.
PRODUCT DATA

WATERBORNE ACRYLIC SANDING SEALER 330080

DESCRIPTION: A clear sealer for interior wood surfaces, offering warmth, clarity, grain character, and sandability. An easily applied, low VOC sealer that provides excellent compatibility with Bennette's Waterborne Polyurethane (330070 or 330071) as the topcoat on interior wood.

SUGGESTED USES: Interior wood surfaces including wood floors, cabinets, or trim.

COLORS: Clear

FINISH: Low-Lustre

GLOSS: 35-45°/60° (depending on porosity)

VEHICLE TYPE: Acrylic

RECOMMENDED COVERAGE RATES:

Approximately 500 sq. ft. per gallon @:
3.2 mils wet film thickness yielding
0.9 mils dry film thickness

DRY TIME (@ 77°F and 50% rel. humidity):

To Touch: 15-30 minutes
To Recoat: 2-4 hours

MIN/MAX TEMP @ APPLICATION:

50°F min / 95°F max

WEIGHT PER GALLON: 8.6 lbs.

VISCOSITY: 80 KU (±2 KU)

SOLIDS CONTENT:

By Weight: 30% (±1)
By Volume: 28% (±1)

VOC: (excluding water)

1.6 lbs/gallon
192 gms/l

FLASH POINT: Combustible

RECOMMENDED APPLICATION EQUIPMENT:

Brush - Quality synthetic bristle brush
Mop - Lambswool pad or Synthetic applicator.
(care should be taken to avoid foam or bubbles)
Other - Padco Floor Coater - Squeegee type

THINNING INSTRUCTIONS: No thinning required. Thinning reduces solids and sealing properties.

CLEAN UP: Clean equipment immediately after use with warm, soapy water.

SURFACE PREPARATION:

Bare Wood: Must be clean, dry and free of dirt, grease, and other foreign matter. Fill all holes and cracks, and sand smooth. Open grained wood should be filled, stained accordingly and allow to thoroughly cure. Sand smooth and profile with light screening. Solvent-based stains should be allowed to totally cure (overnight) prior to applying any waterborne finish.

Previously Finished Wood: All existing varnish or other film forming coatings must be removed by sanding. Follow directions for bare wood.

NOTE: Check adhesion to stain in an inconspicuous area for variances in different stain formulations.

Not recommended for concrete or masonry or in combination with lacquer based or moisture cured coatings.

FORMULATED WITHOUT LEAD OR MERCURY

102301



All technical advice, recommendations and services are rendered by the Seller gratis. They are based on technical data that the Seller believes to be reliable, and are intended for use by persons having skill and know-how at their own discretion and risk. Seller assumes no responsibility for results obtained or damages incurred from their use by Buyer in whole or in part. Such recommendations, technical advice or services are not to be taken as a license to operate under or intended to suggest infringement of any existing patent.