

BENNETTE

PAINT MFG. CO., INC.
PRODUCT DATA

EXTERIOR LATEX FLAT HOUSE PAINT 9 Series

DESCRIPTION: A superior quality vinyl latex paint designed for long term durability on a wide variety of exterior surfaces. This easy to apply, high-hiding coating dries fast to a smooth, velvet sheen and has excellent adhesion, gloss & color retention, durability, and flexibility. Also exhibits excellent resistance to blistering, peeling, mildew, staining, and weathering.

SUGGESTED USES: On properly primed exterior surfaces including: wood, vinyl, aluminum and asbestos siding; wood trim; windows; masonry; galvanized and ferrous metal.

COLORS: Super White, Black, standard colors, and tint bases to provide a complete range of colors from pastels to deep tones.

FINISH: Flat

GLOSS: $\leq 5^\circ/85^\circ$

VEHICLE TYPE: Vinyl Copolymer

RECOMMENDED COVERAGE RATES:

Approximately 400 sq. ft. per gallon @:
4.0 mils wet film thickness
1.3 mils dry film thickness

DRY TIME (@ 77°F and 50% rel. humidity):

To Touch: 30 minutes
To Recoat: 8 hours

MIN/MAX TEMP @ APPLICATION:

50°F min / 95°F max

WEIGHT PER GALLON: 10.8 lbs.

VISCOSITY: 100 KU (± 2 KU)

SOLIDS CONTENT:

By Weight: 50% (± 1)
By Volume: 33% (± 1)

FLASH POINT: Water-based , Combustible

RECOMMENDED APPLICATION EQUIPMENT:

Brush - Quality synthetic bristle, such as Purdy Nylox-Swan or Wooster Ultra Pro.
Roll - Synthetic such as Kodawool or Pro Doo-Z
Spray - Graco or Titan Airless - tip size .017 - .019

THINNING INSTRUCTIONS: Thinning is not normally required. If necessary, thin with water, no more than 1/2 pint per gallon.

CLEAN UP: Clean brushes, rollers, and spray equipment immediately after use with warm, soapy water.

SURFACE PREPARATION: Surface must be free of dirt, chalk, wax or other foreign substances. Glossy surfaces should be sanded and/or scrubbed with a de-glossing solution. Remove mildew with a solution that kills mildew spores. Check adhesion to suspected alkyd or oil paints in an area prior to applying latex coatings. If an adhesion problem is present, use the proper primer as an intermediate coat. New or unpainted surfaces should be primed in accordance with the "Recommended Bennette Primers" section of this sheet.

RECOMMENDED BENNETTE PRIMERS:

<i>Cedar/Redwood</i>	Acrylic Stain Primer	80230
<i>Wood</i>	Exterior Acrylic Latex Primer	70225
	Exterior Acrylic Latex Primer	90225
<i>Block, CMU</i>	Acrylic Blockfiller	80250
<i>Concrete</i>	Exterior Acrylic Latex Primer	70225
	Exterior Acrylic Latex Primer	90225
<i>Brick</i>	Exterior Acrylic Latex Primer	70225
	Exterior Acrylic Latex Primer	90225
<i>Ferrous Metal</i>	Rust Inhib. Metal Primer, Ylw	280237
	Rust Inhib. Metal Primer, Wht	280227
	Acrylic Metal Primer, Red	80228
<i>Galvanized</i>	Acrylic Metal Primer, White	80227
	Acrylic Metal Primer, Red	80228
	Acrylic Metal Primer, White	80227

FORMULATED WITHOUT LEAD OR MERCURY
102401



All technical advice, recommendations and services are rendered by the Seller gratis. They are based on technical data that the Seller believes to be reliable, and are intended for use by persons having skill and know-how at their own discretion and risk. Seller assumes no responsibility for results obtained or damages incurred from their use by Buyer in whole or in part. Such recommendations, technical advice or services are not to be taken as a license to operate under or intended to suggest infringement of any existing patent.