

SECTION 1 - Product and Company Identification				INGREDIENTS	CAS #	VAPOR PRESSURE	EXPOSURE LIMITS
Manufacturer:	E.I. du Pont de Nemours & Co. Du Pont Performance Coatings Wilmington, DE, 19898				7727-43-7	None	A 10.0 mg/m3 Total Dust A 5.0 mg/m3 Respirable Dust O 15.0 mg/m3
Telephone:	Product information:	(800) 441-7515					Total Dust
	Medical emergency:	(800) 441-3637					O 5.0 mg/m3 Respirable Dust
	Transportation emergency:	(800) 424-9300 (CHEMTREC)					D 10.0 mg/m3 Total Dust
Product:	Aerosols			Butyl acetate	123-86-4	10.0	A 200.0 ppm 15 min STEL A 150.0 ppm O 150.0 ppm
DOT Shipping Name:	See DOT addendum.						
Hazardous Materials Information:	See Section 10.			C.i. pigment red 48:4	5280-66-0	None	A None O None
SECTION 2 - Composition/information on ingredients				C.i. pigment yellow	68134-22-5	None	A None O None
INGREDIENTS	CAS #	VAPOR PRESSURE	EXPOSURE LIMITS	INGREDIENTS	CAS #	VAPOR PRESSURE	EXPOSURE LIMITS
1,2,4-trimethyl benzene	95-63-6	7.0@44.4°C	A 25.0 ppm O 25.0 ppm	Calcium carbonate	471-34-1	None	A 10.0 mg/m3 O 15.0 mg/m3 Total Dust O 5.0 mg/m3 Respirable Dust
2,2,4-trimethylpentane	540-84-1	None	A 300.0 ppm O 500.0 ppm	Carbon black	1333-86-4	None	A 3.5 mg/m3 O 3.5 mg/m3 D 0.5 mg/m3 8 & 12 hour TWA
Acetone	67-64-1	247.0@68.0°F	A 750.0 ppm 15 min STEL A 500.0 ppm O 1000.0 ppm D 500.0 ppm 8 & 12 hour TWA	Copper and chromium oxides	NotAvail	None	A None O None
Acrylic polymer	96591-17-2	None	A None O None	Dimethyl glutarate	1119-40-0	0.2	D 10.0 mg/m3 A None O None
Alkyd resin-A	66071-50-9	None	A None O None	Ethylbenzene	100-41-4	7.0	A 125.0 ppm 15 min STEL A 100.0 ppm O 100.0 ppm D 25.0 ppm 8 & 12 hour TWA
Alkyd resin-B	67922-67-2	None	A None O None	Ethylene glycol monobutyl ether acetate	112-07-2	0.3	A 20.0 ppm D 10.0 ppm Skin O None
Alkyd resin-C	150739-98-3	None	A None O None	Hydrous magnesium silicate	14807-96-6	None	A 2.0 mg/m3 Respirable Dust D 0.5 mg/m3 8 & 12 hour TWA Respirable Dust O None
Aluminum	7429-90-5	None	A 10.0 mg/m3 particulate A 5.0 mg/m3 Dust O 15.0 mg/m3 Total Dust O 5.0 mg/m3 Respirable Dust	Isoindolinone pigment	36888-99-0	None	A None O None
Aromatic hydrocarbon-A	64742-94-5	10.0	D 100.0 ppm A None O None	Lead chromate molybdate	12656-85-8	None	A 12.0 ug/m3 Cr A 50.0 ug/m3 Pb A 10.0 mg/m3
Aromatic hydrocarbon-B	64742-95-6	10.0@25.0°C	D 50.0 ppm A None O None				
Azo yellow pigment	31837-42-0	None	A 10.0 mg/m3 O 5.0 mg/m3 Respirable Dust O 15.0 mg/m3				
Barium sulfate							

INGREDIENTS	CAS #	VAPOR PRESSURE	EXPOSURE LIMITS	INGREDIENTS	CAS #	VAPOR PRESSURE	EXPOSURE LIMITS
			inhalable dust Mo A 3.0 mg/m3				D 200.0 ppm 8 & 12 hour TWA
			respirable particulate Mo O 0.1 mg/m3 CEIL CrO3 O 50.0 ug/m3 Pb	Methyl n-propyl ketone 107-87-9		27.8	A 250.0 ppm 15 min STEL A 200.0 ppm O 200.0 ppm
Lead chromate oxide 18454-12-1		None	A 12.0 ug/m3 Cr A 50.0 ug/m3 Pb O 0.1 mg/m3 CEIL CrO3 O 50.0 ug/m3 Cr O 50.0 ug/m3 Pb	Monoazo pigment 12236-62-3		None	A 10.0 mg/m3 inhalable dust particulate O 15.0 mg/m3 Total Dust O 5.0 mg/m3 Respirable Dust
			A 12.0 ug/m3 Cr A 50.0 ug/m3 Pb O 0.1 mg/m3 CEIL CrO3 O 50.0 ug/m3 Cr O 50.0 ug/m3 Pb	N-butyl alcohol 71-36-3		5.6@68.0°F	A 20.0 ppm O 100.0 ppm D 50.0 ppm 15 min TWA D 25.0 ppm
Lead chromates 7758-97-6		None	A 12.0 ug/m3 Cr A 50.0 ug/m3 Pb O 0.1 mg/m3 CEIL CrO3 O 50.0 ug/m3 Pb D 50.0 ug/m3 Cr	Naphthalene 91-20-3		1.0@52.6°C	A 15.0 ppm CEIL Skin A 10.0 ppm Skin O 10.0 ppm D 0.1 ppm 8 & 12 hour TWA
			A 12.0 ug/m3 Cr A 50.0 ug/m3 Pb O 0.1 mg/m3 CEIL CrO3 O 50.0 ug/m3 Pb D 50.0 ug/m3 Cr	Polymer base NotAvail		9.1@68.0°F	A None O None
Lead sulfochromate yellow 1344-37-2		None	A 12.0 ug/m3 Cr A 50.0 ug/m3 Pb O 0.1 mg/m3 Ceiling CrO3 O 50.0 ug/m3 TWA Pb D 50.0 ug/m3 Cr	Propylene glycol monomethyl ether acetate 108-65-6		3.8	D 10.0 ppm 8 & 12 hour TWA A None O None
			A 12.0 ug/m3 Cr A 50.0 ug/m3 Pb O 0.1 mg/m3 Ceiling CrO3 O 50.0 ug/m3 TWA Pb D 50.0 ug/m3 Cr	Quinacridone pigment 1047-16-1		None	A 10.0 mg/m3 inhalable dust A 3.0 mg/m3 O 15.0 mg/m3 Total Dust PNOR O 5.0 mg/m3 Respirable Dust D 10.0 mg/m3 Total Dust
Liquified compressed gas 68476-85-7		999.9	A 1000.0 ppm O 1000.0 ppm	Red iron oxide light 1332-37-2		None	A 10.0 mg/m3 PNOR
Medium mineral spirits 64742-88-7		0.3@68.0°F	D 50.0 ppm 8 & 12 hour TWA A None O None				A 3.0 mg/m3 Respirable Dust A 5.0 mg/m3 Fe O 15.0 mg/m3 Total Dust O 5.0 mg/m3 Respirable Dust
Methyl amyl ketone 110-43-0		3.4	A 50.0 ppm O 100.0 ppm				
Methyl ethyl ketone 78-93-3		89.0 @ 0.0	A 300.0ppm 15 min STEL A 200.0 ppm O 200.0 ppm D 300.0 ppm 15 min TWA	Titanium dioxide 13463-67-7		None	A 10.0 mg/m3 O 15.0 mg/m3 Total Dust D 10.0 mg/m3 Total Dust D 5.0 mg/m3

INGREDIENTS	CAS #	VAPOR PRESSURE	EXPOSURE LIMITS
Toluene	108-88-3	22.0	Respirable Dust A 50.0 ppm Skin O 300.0 ppm CEIL O 500.0 ppm 10 min TWA O 200.0 ppm D 50.0 ppm 8 & 12 hour TWA
Vm&p naphtha	8032-32-4	17.9@68.0°F	A 300.0 ppm D 100.0 ppm O None
Xylene	1330-20-7	8.0@25.0°C	A 150.0 ppm 15 min STEL A 100.0 ppm O 100.0 ppm D 150.0 ppm 15 min STEL D 100.0 ppm 8 & 12 hour TWA
Yellow iron oxide	51274-00-1	None	A 10.0 mg/m3 O 15.0 mg/m3
Zinc oxide	1314-13-2	None	A 10.0 mg/m3 15 min STEL Respirable Dust A 2.0 mg/m3 Respirable Dust O 15.0 mg/m3 Total Dust O 5.0 mg/m3 Respirable Dust

*A=ACGIH, O=OSHA, D=DuPont, S=Suppliers. Limits are 8 hour TWA unless otherwise specified. Vapor pressure @20°C unless otherwise noted.

SECTION 3 - Hazards identification

Potential Health Effects:

Inhalation:

May cause nose and throat irritation. May cause nervous system depression characterized by the following progressive steps: headache, dizziness, nausea, staggering gait, confusion, unconsciousness. Reports have associated repeated and prolonged overexposure to solvents with permanent brain and nervous system damage. INTENTIONAL MISUSE BY DELIBERATELY CONCENTRATING AND INHALING THE CONTENTS MAY BE HARMFUL OR FATAL.

Ingestion:

May result in gastrointestinal distress

Skin or Eye Contact:

May cause irritation or burning of the eyes. Repeated or prolonged liquid contact may cause skin irritation with discomfort and dermatitis.

Other Potential Health Effects in addition to those listed above:

Acetone

The following medical conditions may be aggravated by exposure: lung disease, eye disorders, skin disorders. Overexposure may cause damage to any of the following organs/systems: blood, central nervous system, eyes, kidneys, liver, respiratory system, skin.

Aromatic hydrocarbon-A

Laboratory studies with rats have shown that petroleum distillates can cause kidney damage and kidney or liver tumors. These effects were not seen in similar studies with guinea pigs, dogs, or monkeys. Several studies evaluating petroleum workers have not shown a significant increase of

kidney damage or an increase in kidney or liver tumors.

Aromatic hydrocarbon-B

The following medical conditions may be aggravated by exposure: skin disorders. Laboratory studies with rats have shown that petroleum distillates can cause kidney damage and kidney or liver tumors. These effects were not seen in similar studies with guinea pigs, dogs, or monkeys. Several studies evaluating petroleum workers have not shown a significant increase of kidney damage or an increase in kidney or liver tumors.

Butyl acetate

May cause abnormal liver function. The following medical conditions may be aggravated by exposure: respiratory system. Tests for embryotoxic activity in animals has been inconclusive. Rats exposed to very high airborne levels have exhibited high frequency hearing deficits. The significance of this to man is unknown. Has been toxic to the fetus in laboratory animals at doses that are toxic to the mother.

C.i. pigment yellow

Inhalation may cause any of the following: respiratory tract irritation. Skin or eye contact may cause any of the following: irritation.

Carbon black

Is an IARC, NTP or OSHA carcinogen. Has shown carcinogenic activity in laboratory animals at high doses. Significance to man is unknown. The following medical conditions may be aggravated by exposure: asthma, respiratory disease.

WARNING: This chemical is known to the State of California to cause cancer.

Copper and chromium oxides

The components of this pigment are combined chemically into a uniform substance which does not necessarily reflect the properties of the components metals or oxides.

WARNING: This chemical is known to the State of California to cause cancer.

Ethylbenzene

Is an IARC, NTP or OSHA carcinogen. Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: central nervous system, kidneys, liver, lungs. Recurrent overexposure may result in liver and kidney injury. Studies in laboratory animals have shown reproductive, embryotoxic and developmental effects.

WARNING: This chemical is known to the State of California to cause cancer.

Ethylene glycol monobutyl ether acetate

May destroy red blood cells. May cause abnormal kidney function. May cause temporary upper respiratory and/or lung irritation with cough, difficult breathing, or shortness of breath. The following medical conditions may be aggravated by exposure: central nervous system, gastrointestinal system, kidneys, liver, dermatitis. Can be absorbed through the skin in harmful amounts. Overexposure may cause damage to any of the following organs/systems: blood, kidneys, liver. Ingestion may cause headache, nausea, vomiting, dizziness, and drowsiness.

Lead chromate molybdate

Is an IARC, NTP or OSHA carcinogen. Over exposure to lead may cause adverse effects to the blood forming, nervous, urinary, reproductive systems including embryotoxic effects. Symptoms may include loss of appetite, anemia, disturbance of sleep and fatigue. See OSHA lead standard 29CFR1910.1025. For exposures longer than 8 hours the OSHA exposure limit is reduced by this formula: $\text{limit}(\text{in ug/m}^3) = 400/\text{hours}$ worked in the day.

WARNING: This chemical is known to the State of California to cause cancer and birth defects or other reproductive harm

Lead chromate oxide

Is an IARC, NTP or OSHA carcinogen. Over exposure to lead may cause adverse effects to the blood forming, nervous, urinary, reproductive systems including embryotoxic effects. Symptoms may include loss of appetite, anemia, disturbance of sleep and fatigue. See OSHA lead standard 29CFR1910.1025. For exposures longer than 8 hours the OSHA exposure limit is reduced by this formula: $\text{limit}(\text{in ug/m}^3) = 400/\text{hours}$ worked in the day.

WARNING: This chemical is known to the State of California to cause cancer and birth defects or other reproductive harm

Lead chromates

Is an IARC, NTP or OSHA carcinogen. Over exposure to lead may cause adverse effects to the blood forming, nervous, urinary, reproductive systems including embryotoxic effects. Symptoms may include loss of appetite, anemia, disturbance of sleep and fatigue. See OSHA lead standard 29CFR1910.1025. For exposures longer than 8 hours the OSHA exposure limit is reduced by this formula: $\text{limit(in ug/m}^3\text{)} = 400/\text{hours worked in the day}$.

WARNING: This chemical is known to the State of California to cause cancer and birth defects or other reproductive harm

Lead sulfochromate yellow

Is an IARC, NTP or OSHA carcinogen. Over exposure to lead may cause adverse effects to the blood forming, nervous, urinary, reproductive systems including embryotoxic effects. Symptoms may include loss of appetite, anemia, disturbance of sleep and fatigue. See OSHA lead standard 29CFR1910.1025. For exposures longer than 8 hours the OSHA exposure limit is reduced by this formula: $\text{limit(in ug/m}^3\text{)} = 400/\text{hours worked in the day}$.

WARNING: This chemical is known to the State of California to cause cancer and birth defects or other reproductive harm

Liquified compressed gas

May possibly cause modest initial irritation, followed in hours by severe shortness of breath, requiring prompt medical attention. May cause central nervous system effects such as temporary muscular weakness and loss of coordination. Contact may cause skin burns. Can irritate or burn eyes.

Medium mineral spirits

This substance may cause damage to any of the following organs/systems: blood. Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: central nervous system. This substance may cause damage to any of the following organs/systems: central nervous system, eyes, kidneys. Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: kidneys, liver. This substance may cause damage to any of the following organs/systems: liver, lungs, reproductive system. Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: respiratory system. This substance may cause damage to any of the following organs/systems: skin. Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: skin. Laboratory studies with rats have shown that petroleum distillates can cause kidney damage and kidney or liver tumors. These effects were not seen in similar studies with guinea pigs, dogs, or monkeys. Several studies evaluating petroleum workers have not shown a significant increase of kidney damage or an increase in kidney or liver tumors.

Methyl ethyl ketone

Material is irritating to mucous membranes and upper respiratory tract. Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: central nervous system, eyes, respiratory system, skin. Prolonged or repeated overexposure may cause any of the following: conjunctivitis, dermatitis. High concentrations have caused embryotoxic effects in laboratory animals. Aspiration may occur during swallowing or vomiting, resulting in lung damage. Ingestion may cause headache, nausea, vomiting, dizziness, and drowsiness.

Methyl n-propyl ketone

May cause temporary upper respiratory and/or lung irritation with cough, difficult breathing, or shortness of breath. May cause any of the following central nervous system effects: drowsiness. May cause eye irritation with discomfort, tearing, or blurred vision.

N-butyl alcohol

May cause abnormal blood forming function with anemia. Liquid splashes in the eye may result in chemical burns.

Naphthalene

Is an IARC, NTP or OSHA carcinogen. Tests in some laboratory animals demonstrate carcinogenic activity. Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of

the following: kidneys, liver. Recurrent overexposure may result in liver and kidney injury.

WARNING: This chemical is known to the State of California to cause cancer.

Polymer base

Eye contact may cause any of the following: blurred vision, severe irritation, redness, tearing. Inhalation of high vapor concentrations may cause any of the following: stupor (central nervous system depression). Repeated or prolonged inhalation may cause any of the following: dizziness, headache, nausea, irritation to the nose, lung irritation.

Propylene glycol monomethyl ether acetate

Recurrent overexposure may result in liver and kidney injury.

Red iron oxide light

Long-term respiratory exposure of iron oxide may result in deposition of particles in the lung (benign siderosis).

Titanium dioxide

In a lifetime inhalation test, lung cancers were found in some rats exposed to 250 mg/m³ respirable titanium dust. Analysis of the titanium dioxide concentrations in the rat's lungs showed that the lung clearance mechanism was overwhelmed and that the results at the massive 250 mg/m³ level are not relevant to the workplace.

Toluene

Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: central nervous system, kidneys, liver, respiratory system, skin. Can be absorbed through the skin in harmful amounts. Recurrent overexposure may result in liver and kidney injury. High airborne levels have produced irregular heart beats in animals and occasional palpitations in humans. Rats exposed to very high airborne levels have exhibited high frequency hearing deficits. The significance of this to man is unknown.

WARNING: This chemical is known to the State of California to cause birth defects or other reproductive harm.

Vm&p naphtha

Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: central nervous system, kidneys, liver, lungs, respiratory system, skin. This substance may cause damage to any of the following organs/systems: central nervous system, kidneys, liver, lungs, skin and eyes. Material may be harmful or fatal if swallowed.

Xylene

Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: bone marrow, cardiovascular system, central nervous system, kidneys, liver, lungs. Recurrent overexposure may result in liver and kidney injury. High exposures may produce irregular heart beats. Canada classifies Xylene as a developmental toxin as high exposures to xylenes in some animal studies have been reported to cause health effects on the developing fetus/embryo. These effects were often at levels toxic to the adult animal. The significance of these effects to humans is not known. Repeated or prolonged skin contact may cause any of the following: irritation, dryness, cracking of the skin.

SECTION 4 - First aid measures

First Aid Procedures

Inhalation:

If affected by inhalation of vapor or spray mist, move to fresh air. If not breathing, give artificial respiration, preferably mouth-to-mouth. If breathing difficulty persists, or occurs later, consult a physician.

Ingestion:

In the unlikely event of ingestion, DO NOT INDUCE VOMITING. Call a physician immediately and have names of ingredients available.

Skin or Eye Contact:

In case of eye contact, immediately flush with plenty of water for at least 15

minutes; call a physician. In case of skin contact, wash thoroughly with soap and water. If irritation occurs, contact a physician.

SECTION 5 - Fire-fighting measures

Flash Point (Closed Cup): See Section 11 for exact values

Flammable Limits: LFL 0.5% UFL 13.1%

Extinguishing Media:

Universal aqueous film-forming foam, carbon dioxide, dry chemical.

Fire Fighting Procedures:

Full protective equipment, including self-contained breathing apparatus, is recommended. Water from fog nozzles may be used to prevent pressure build-up.

Fire and Explosion Hazards:

For flammable liquids, vapor/air will ignite when an ignition source is present. In other cases, when heated above the flash point, emits flammable vapors which, when mixed with air, can burn or be explosive. Fine mists or sprays may be flammable at temperatures below the flash point.

SECTION 6 - Accidental release measures

Steps to be taken in case material is released or spilled:

Ventilate area. Remove sources of ignition. Prevent skin and eye contact and breathing of vapor. Wear a properly fitted air-purifying respirator with organic vapor cartridges (NIOSH approved TC-23C), eye protection, gloves and protective clothing. Confine, remove with inert absorbent, and dispose of properly.

SECTION 7 - Handling and storage

Precautions to be taken in handling and storing:

Observe label precautions. If combustible (flashpoint between 100-200 °F), keep away from heat, sparks and flame. If flammable (flashpoint less than 100 °F), also keep away from static discharges and other sources of ignition. If material is extremely flammable (flashpoint less than 20 °F) or flammable, VAPORS MAY IGNITE EXPLOSIVELY OR CAUSE FLASH FIRE, respectively. Vapors may spread long distances. Prevent buildup of vapors. Close container after each use. Ground containers when pouring. Wash thoroughly after handling and before eating or smoking. Do not store above 120 °F. If product is waterbased do not freeze.

CONTENTS UNDER PRESSURE. Clean nozzle and cap container after each use. Do not puncture or incinerate (burn) container. Exposure to heat or prolonged exposure to sun may cause bursting

Other precautions:

If material is a coating: do not sand, flame cut, braze or weld dry coating without a NIOSH approved respirator or appropriate ventilation, and gloves.

SECTION 8 - Exposure controls / personal protection

Engineering controls and work practices:

Ventilation:

Provide sufficient ventilation in volume and pattern to keep contaminants below applicable exposure limits.

Respiratory protection

Do not breathe vapors or mists. Wear a properly fitted air-purifying respirator with organic vapor cartridges (NIOSH approved TC-23C) and particulate filter (NIOSH TC-84A) during application and until all vapors and spray mists are exhausted. In confined spaces, or in situations where continuous spray operations are typical, or if proper air-purifying respirator fit is not possible, wear a positive pressure, supplied-air respirator (NIOSH TC-19C). In all cases, follow respirator manufacturer's directions for

respirator use. Do not permit anyone without protection in the painting area.

Protective equipment

Personal protective equipment should be worn to prevent contact with eyes, skin or clothing.

Skin protection

Neoprene gloves and coveralls are recommended.

Eye protection

Desirable in all industrial situations. Goggles are preferred to prevent eye irritation. If safety glasses are substituted, include splash guard or side shields.

SECTION 9 - Physical and chemical properties

Evaporation rate	Slower than Ether
Solubility in Water	NIL
Vapor Density	Heavier than air
Approx. Boiling Range(°C)	56.1 - 210 °C
Approx. Freezing Range(°C)	-189.7 - -25 °C
Gallon weight (lbs/gal)	6.06 - 7.03
Specific Gravity	0.73 - 0.84
Percent Volatile by Volume	89.22 - 95.93
Percent Volatile by Weight	73.78 - 91.69
Percent Solid by Volume	4.08 - 10.78
Percent Solid by Weight	8.31 - 26.22

SECTION 10 - Stability and reactivity

Stability:

Stable

Incompatibility (materials to avoid):

None reasonably foreseeable

Hazardous Decomposition Products:

CO, CO₂, smoke, and oxides of any heavy metals that are reported in "Composition, Information on Ingredients" section.

Hazardous Polymerization:

Will not occur.

Sensitivity to Static Discharge:

For flammable materials (flashpoint less than 100 deg F) and combustibles (flashpoint between 100-200 deg F) if heated above the flashpoint, solvent vapors in air may explode if static grounding and bonding is not used during transfer of this product.

Sensitivity to Mechanical Impact:

None known

SECTION 11 - Additional Information

Product Code

Ingredients (Product Specific)

900P™ Acetone(24.0%), Acrylic polymer(6.2%), Alkyd resin-B(4.2%), Aromatic hydrocarbon-A(1.2 - 1.2%), Ethylbenzene(0.6 - 1.4%* @), Liquefied compressed gas(27.0%), Methyl ethyl ketone(16.1%), N-butyl alcohol(3.0%*), Titanium dioxide(5.8%), Toluene(3.2 - 3.2%* @), Vm&p naphtha(1.6%), Xylene(4.2 - 5.0%* @)

GAL WT: 6.33 WT PCT SOLIDS: 16.72 VOL PCT SOLIDS: 8.25

SOLVENT DENSITY: 5.75 VOC LE: 4.9 VOC AP: 3.8

FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB

TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

901P™ Acetone(24.0%), Acrylic polymer(7.1%), Alkyd resin-B(4.8%), Aromatic hydrocarbon-A(1.2%), Carbon black(0.4%), Ethylbenzene(0.5 - 1.2%* @), Liquefied compressed gas(27.0%), Methyl ethyl

ketone(16.3%), N-butyl alcohol(3.0%*), Propylene glycol monomethyl ether acetate(1.9%), Toluene(5.8 - 5.9%* @), Xylene(3.6 - 4.3%* @)
GAL WT: 6.12 WT PCT SOLIDS: 12.65 VOL PCT SOLIDS: 8.13
SOLVENT DENSITY: 5.82 VOC LE: 5.0 VOC AP: 3.9
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

902P™ Acetone(24.0%), Acrylic polymer(7.1%), Alkyd resin-B(4.8%), Aromatic hydrocarbon-A(1.2%), Carbon black(0.4%), Ethylbenzene(0.5 - 1.2%* @), Liquefied compressed gas(27.0%), Methyl ethyl ketone(16.3%), N-butyl alcohol(3.0%*), Propylene glycol monomethyl ether acetate(1.9%), Toluene(5.8 - 5.9%* @), Xylene(3.6 - 4.3%* @)
GAL WT: 6.12 WT PCT SOLIDS: 12.64 VOL PCT SOLIDS: 8.12
SOLVENT DENSITY: 5.82 VOC LE: 5.0 VOC AP: 3.9
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

904P™ Acetone(43.3%), Acrylic polymer(5.6%), Alkyd resin-B(3.6%), Butyl acetate(4.1%), Ethylbenzene(0.8 - 1.9%* @), Liquefied compressed gas(25.0%), Methyl ethyl ketone(1.1%), Monoazo pigment(2.3%), Toluene(3.1 - 3.1%* @), Vm&p naphtha(2.0%), Xylene(5.7 - 6.8%* @)
GAL WT: 6.19 WT PCT SOLIDS: 12.08 VOL PCT SOLIDS: 7.59
SOLVENT DENSITY: 5.85 VOC LE: 4.6 VOC AP: 2.7
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

905P™ Acetone(43.3%), Acrylic polymer(6.3%), Alkyd resin-B(4.1%), Butyl acetate(3.4%), Ethylbenzene(0.8 - 2.0%* @), Liquefied compressed gas(25.0%), Methyl ethyl ketone(1.2%), Titanium dioxide(1.1%), Toluene(4.2 - 4.3%* @), Vm&p naphtha(1.9%), Xylene(6.0 - 7.2%* @)
GAL WT: 6.06 WT PCT SOLIDS: 13.04 VOL PCT SOLIDS: 7.19
SOLVENT DENSITY: 5.74 VOC LE: 4.5 VOC AP: 2.7
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

906P™ Acetone(43.3%), Acrylic polymer(6.0%), Alkyd resin-B(3.8%), Butyl acetate(4.6%), C.i. pigment yellow(1.2%), Ethylbenzene(0.8 - 1.9%* @), Liquefied compressed gas(25.0%), Titanium dioxide(1.1%), Toluene(2.2 - 2.3%* @), Vm&p naphtha(2.3%), Xylene(5.8 - 7.0%* @)
GAL WT: 6.21 WT PCT SOLIDS: 13.04 VOL PCT SOLIDS: 7.70
SOLVENT DENSITY: 5.85 VOC LE: 4.6 VOC AP: 2.7
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

907P™ Acetone(43.4%), Acrylic polymer(5.8%), Alkyd resin-B(3.7%), Butyl acetate(4.9%), C.i. pigment yellow(1.7%), Ethylbenzene(0.9 - 2.2%* @), Liquefied compressed gas(25.1%), Toluene(1.6 - 1.7%* @), Vm&p naphtha(1.9%), Xylene(6.6 - 8.0%* @)
GAL WT: 6.19 WT PCT SOLIDS: 12.55 VOL PCT SOLIDS: 7.62
SOLVENT DENSITY: 5.86 VOC LE: 4.6 VOC AP: 2.7
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

908P™ Acetone(43.3%), Acrylic polymer(6.3%), Alkyd resin-B(4.2%), Butyl acetate(3.5%), Ethylbenzene(0.9 - 2.3%* @), Liquefied compressed gas(25.0%), Methyl ethyl ketone(1.1%), Toluene(3.3 - 3.4%* @), Vm&p naphtha(2.0%), Xylene(7.0 - 8.4%* @)
GAL WT: 6.16 WT PCT SOLIDS: 11.58 VOL PCT SOLIDS: 7.20
SOLVENT DENSITY: 5.87 VOC LE: 4.7 VOC AP: 2.8
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

909P™ Acetone(33.4%), Acrylic polymer(6.7%), Alkyd resin-B(4.4%), Butyl acetate(2.9%), C.i. pigment yellow(1.0%), Ethylbenzene(0.9 - 2.3%* @), Liquefied compressed gas(25.0%), Methyl ethyl ketone(10.5%), Toluene(2.3 - 2.4%* @), Vm&p naphtha(2.4%), Xylene(7.1 - 8.5%* @)
GAL WT: 6.18 WT PCT SOLIDS: 12.96 VOL PCT SOLIDS: 8.06
SOLVENT DENSITY: 5.85 VOC LE: 4.8 VOC AP: 3.3
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

910P™ Acetone(29.9%), Acrylic polymer(8.5%), Alkyd resin-B(5.6%),

Butyl acetate(5.9%), Ethylbenzene(0.9 - 2.2%* @), Liquefied compressed gas(29.8%), Methyl ethyl ketone(1.3%), Toluene(3.7 - 3.7%* @), Vm&p naphtha(2.7%), Xylene(6.7 - 8.1%* @), Yellow iron oxide(1.3%)
GAL WT: 6.16 WT PCT SOLIDS: 16.88 VOL PCT SOLIDS: 10.06
SOLVENT DENSITY: 5.69 VOC LE: 4.5 VOC AP: 3.3
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

911P™ 1,2,4-trimethyl benzene(1.6 - 1.6%*), Acetone(30.2%), Acrylic polymer(7.7%), Alkyd resin-B(4.9%), Aromatic hydrocarbon-B(3.2 - 3.2%), Butyl acetate(1.1%), Ethylbenzene(0.8 - 2.0%* @), Liquefied compressed gas(27.0%), Methyl ethyl ketone(1.3%), N-butyl alcohol(2.5%*), Titanium dioxide(2.7%), Toluene(3.9 - 4.0%* @), Vm&p naphtha(3.7%), Xylene(6.2 - 7.4%* @)
GAL WT: 6.25 WT PCT SOLIDS: 16.06 VOL PCT SOLIDS: 9.27
SOLVENT DENSITY: 5.78 VOC LE: 4.7 VOC AP: 3.4
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES

912P™ Acetone(31.7%), Acrylic polymer(8.0%), Alkyd resin-B(5.2%), Butyl acetate(5.8%), Ethylbenzene(0.8 - 2.0%* @), Liquefied compressed gas(26.5%), Methyl ethyl ketone(1.5%), Titanium dioxide(2.8%), Toluene(4.3 - 4.3%* @), Vm&p naphtha(3.8%), Xylene(6.2 - 7.4%* @)
GAL WT: 6.28 WT PCT SOLIDS: 16.65 VOL PCT SOLIDS: 9.67
SOLVENT DENSITY: 5.79 VOC LE: 4.6 VOC AP: 3.2
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

914P™ Acetone(30.4%), Calcium carbonate(6.0%), Ethylbenzene(1.6 - 3.9%* @), Hydrous magnesium silicate(2.8%), Liquefied compressed gas(27.1%), Medium mineral spirits(5.2%), Methyl amyl ketone(3.9%), Methyl n-propyl ketone(1.2%), Polymer base(4.6%), Red iron oxide light(1.7%), Xylene(11.6 - 13.9%* @)
GAL WT: 6.46 WT PCT SOLIDS: 16.11 VOL PCT SOLIDS: 6.19
SOLVENT DENSITY: 5.79 VOC LE: 4.9 VOC AP: 3.5
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES

915P™ Acetone(41.8%), Acrylic polymer(2.9%), Alkyd resin-B(6.6%), Ethylbenzene(1.1 - 2.9%* @), Liquefied compressed gas(25.0%), Propylene glycol monomethyl ether acetate(8.0%), Toluene(1.7 - 1.8%* @), Xylene(8.6 - 10.3%* @)
GAL WT: 6.17 WT PCT SOLIDS: 9.87 VOL PCT SOLIDS: 6.47
SOLVENT DENSITY: 5.95 VOC LE: 4.9 VOC AP: 3.0
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES

916P™ Acetone(30.5%), Alkyd resin-C(4.8%), Copper and chromium oxides(1.1%* @), Hydrous magnesium silicate(2.1%), Liquefied compressed gas(25.0%), Toluene(34.7%* @)
GAL WT: 6.25 WT PCT SOLIDS: 8.31 VOL PCT SOLIDS: 4.34
SOLVENT DENSITY: 5.99 VOC LE: 5.4 VOC AP: 3.8
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES

917P™ Acrylic polymer(6.5%), Alkyd resin-B(2.3%), Aluminum(2.8%*), Ethylbenzene(4.5 - 11.2%* @), Liquefied compressed gas(31.0%), Methyl ethyl ketone(1.2%), Toluene(3.6 - 4.0%* @), Vm&p naphtha(5.3%), Xylene(33.8 - 40.6%* @)
GAL WT: 6.18 WT PCT SOLIDS: 11.95 VOL PCT SOLIDS: 6.97
SOLVENT DENSITY: 5.85 VOC LE: 5.4 VOC AP: 5.4
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES

920P™ Acetone(32.4%), Alkyd resin-A(3.0%), Barium sulfate(5.2%), Butyl acetate(10.6%), Ethylbenzene(0.7 - 1.9%* @), Hydrous magnesium silicate(1.2%), Liquefied compressed gas(24.9%), Methyl ethyl ketone(10.7%), Titanium dioxide(1.9%), Xylene(5.6 - 6.7%* @), Zinc oxide(1.6%*)
GAL WT: 6.51 WT PCT SOLIDS: 13.43 VOL PCT SOLIDS: 4.08
SOLVENT DENSITY: 5.88 VOC LE: 5.2 VOC AP: 3.5
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

922PTM Acetone(43.3%), Acrylic polymer(6.1%), Alkyd resin-B(3.8%), Butyl acetate(3.7%), Ethylbenzene(0.5 - 1.3%*[@]), Liquefied compressed gas(25.0%), Methyl ethyl ketone(1.1%), Titanium dioxide(3.9%), Toluene(3.3 - 3.3%*[@]), Vm&p naphtha(2.8%), Xylene(4.0 - 4.8%*[@])
GAL WT: 6.28 WT PCT SOLIDS: 14.30 VOL PCT SOLIDS: 7.58
SOLVENT DENSITY: 5.82 VOC LE: 4.5 VOC AP: 2.7
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

923PTM Acetone(43.2%), Acrylic polymer(6.1%), Alkyd resin-B(4.1%), Butyl acetate(3.7%), Ethylbenzene(0.6 - 1.6%*[@]), Liquefied compressed gas(25.0%), Methyl ethyl ketone(1.1%), Titanium dioxide(2.9%), Toluene(3.3 - 3.3%*[@]), Vm&p naphtha(2.6%), Xylene(4.8 - 5.8%*[@])
GAL WT: 6.25 WT PCT SOLIDS: 13.65 VOL PCT SOLIDS: 7.57
SOLVENT DENSITY: 5.84 VOC LE: 4.6 VOC AP: 2.7
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

926PTM Acetone(32.3%), Acrylic polymer(5.7%), Alkyd resin-B(3.5%), Butyl acetate(9.9%), Ethylbenzene(0.5 - 1.2%*[@]), Liquefied compressed gas(24.7%), Methyl ethyl ketone(8.1%), Titanium dioxide(3.6%), Toluene(3.1 - 3.1%*[@]), Vm&p naphtha(1.9%), Xylene(3.7 - 4.5%*[@])
GAL WT: 6.30 WT PCT SOLIDS: 13.35 VOL PCT SOLIDS: 7.09
SOLVENT DENSITY: 5.88 VOC LE: 5.0 VOC AP: 3.4
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

928PTM Acetone(36.1%), Acrylic polymer(6.5%), Alkyd resin-B(4.2%), Butyl acetate(5.1%), Ethylbenzene(0.7 - 1.7%*[@]), Liquefied compressed gas(25.1%), Methyl ethyl ketone(5.8%), Titanium dioxide(1.2%), Toluene(5.4 - 5.5%*[@]), Vm&p naphtha(1.9%), Xylene(5.2 - 6.3%*[@])
GAL WT: 6.21 WT PCT SOLIDS: 12.74 VOL PCT SOLIDS: 7.69
SOLVENT DENSITY: 5.87 VOC LE: 4.8 VOC AP: 3.2
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

929PTM 1,2,4-trimethyl benzene(1.5 - 1.5%*), Acetone(22.9%), Acrylic polymer(6.5%), Alkyd resin-B(4.3%), Aromatic hydrocarbon-B(2.7 - 2.7%), Ethylbenzene(0.6 - 1.5%*[@]), Liquefied compressed gas(26.7%), Methyl ethyl ketone(14.3%), N-butyl alcohol(2.9%*), Titanium dioxide(3.6%), Toluene(3.5 - 3.6%*[@]), Vm&p naphtha(2.5%), Xylene(4.6 - 5.5%*[@])
GAL WT: 6.26 WT PCT SOLIDS: 14.88 VOL PCT SOLIDS: 7.99
SOLVENT DENSITY: 5.79 VOC LE: 5.0 VOC AP: 3.9
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES

935PTM Acetone(43.3%), Acrylic polymer(6.8%), Alkyd resin-B(4.6%), Butyl acetate(3.4%), Ethylbenzene(0.8 - 1.9%*[@]), Liquefied compressed gas(25.0%), Methyl ethyl ketone(1.2%), Toluene(3.5 - 3.6%*[@]), Vm&p naphtha(3.0%), Xylene(5.8 - 7.0%*[@])
GAL WT: 6.14 WT PCT SOLIDS: 11.86 VOL PCT SOLIDS: 7.62
SOLVENT DENSITY: 5.86 VOC LE: 4.6 VOC AP: 2.8
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

936PTM Acetone(43.3%), Acrylic polymer(6.6%), Alkyd resin-B(4.4%), Butyl acetate(3.6%), Ethylbenzene(0.8 - 1.9%*[@]), Liquefied compressed gas(25.0%), Methyl ethyl ketone(1.1%), Toluene(3.2 - 3.3%*[@]), Vm&p naphtha(3.1%), Xylene(5.8 - 6.9%*[@])
GAL WT: 6.16 WT PCT SOLIDS: 12.08 VOL PCT SOLIDS: 7.52
SOLVENT DENSITY: 5.86 VOC LE: 4.6 VOC AP: 2.8
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

937PTM Acetone(43.3%), Acrylic polymer(6.6%), Alkyd resin-B(4.4%), Butyl acetate(3.6%), Carbon black(0.1%), Ethylbenzene(0.8 - 2.0%*[@]), Liquefied compressed gas(25.0%), Methyl ethyl ketone(1.2%), Toluene(3.5 - 3.5%*[@]), Vm&p naphtha(2.8%), Xylene(5.9 - 7.1%*[@])
GAL WT: 6.13 WT PCT SOLIDS: 11.47 VOL PCT SOLIDS: 7.40
SOLVENT DENSITY: 5.86 VOC LE: 4.6 VOC AP: 2.8
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

942PTM Acetone(32.4%), Acrylic polymer(4.9%), Alkyd resin-B(3.2%), Butyl acetate(9.5%), Ethylbenzene(0.5 - 1.4%*[@]), Isoindolinone pigment(4.0%), Liquefied compressed gas(25.0%), Methyl ethyl ketone(8.3%), Toluene(2.7 - 2.7%*[@]), Vm&p naphtha(2.3%), Xylene(4.1 - 5.0%*[@])
GAL WT: 6.27 WT PCT SOLIDS: 13.53 VOL PCT SOLIDS: 7.55
SOLVENT DENSITY: 5.86 VOC LE: 4.9 VOC AP: 3.4
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

948PTM Acetone(39.9%), Acrylic polymer(4.2%), Alkyd resin-B(2.7%), Aromatic hydrocarbon-A(1.4 - 1.4%), Butyl acetate(5.1%), Ethylbenzene(0.6 - 1.4%*[@]), Liquefied compressed gas(25.1%), Methyl ethyl ketone(5.3%), Naphthalene(0.0 - 0.2%*[@]), Titanium dioxide(1.9%), Toluene(4.3 - 4.4%*[@]), Vm&p naphtha(3.5%), Xylene(4.3 - 5.2%*[@])
GAL WT: 6.16 WT PCT SOLIDS: 9.32 VOL PCT SOLIDS: 5.07
SOLVENT DENSITY: 5.88 VOC LE: 5.0 VOC AP: 3.1
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

952PTM Acetone(40.0%), Acrylic polymer(4.0%), Alkyd resin-B(2.5%), Aromatic hydrocarbon-A(2.2 - 2.2%), Butyl acetate(5.7%), Ethylbenzene(0.6 - 1.5%*[@]), Liquefied compressed gas(25.0%), Methyl ethyl ketone(5.1%), Naphthalene(0.0 - 0.3%*[@]), Toluene(4.2 - 4.2%*[@]), Vm&p naphtha(2.1%), Xylene(4.6 - 5.5%*[@]), Yellow iron oxide(1.1%)
GAL WT: 6.16 WT PCT SOLIDS: 9.10 VOL PCT SOLIDS: 5.07
SOLVENT DENSITY: 5.90 VOC LE: 5.0 VOC AP: 3.1
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

953PTM Acetone(39.8%), Acrylic polymer(4.4%), Alkyd resin-B(2.9%), Aromatic hydrocarbon-A(2.3 - 2.3%), Butyl acetate(5.7%), Ethylbenzene(0.6 - 1.6%*[@]), Liquefied compressed gas(25.0%), Methyl ethyl ketone(3.7%), Naphthalene(0.0 - 0.3%*[@]), Titanium dioxide(1.1%), Toluene(5.3 - 5.3%*[@]), Vm&p naphtha(3.1%), Xylene(4.7 - 5.7%*[@])
GAL WT: 6.14 WT PCT SOLIDS: 8.79 VOL PCT SOLIDS: 5.15
SOLVENT DENSITY: 5.90 VOC LE: 5.0 VOC AP: 3.2
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

956PTM Acetone(31.8%), Acrylic polymer(6.3%), Alkyd resin-B(4.1%), Butyl acetate(7.7%), Ethylbenzene(0.6 - 1.6%*[@]), Liquefied compressed gas(25.1%), Methyl ethyl ketone(7.8%), Titanium dioxide(2.2%), Toluene(3.0 - 3.0%*[@]), Vm&p naphtha(3.1%), Xylene(4.8 - 5.8%*[@])
GAL WT: 6.28 WT PCT SOLIDS: 13.98 VOL PCT SOLIDS: 7.73
SOLVENT DENSITY: 5.86 VOC LE: 4.9 VOC AP: 3.4
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

958PTM Acetone(43.3%), Acrylic polymer(6.3%), Alkyd resin-B(4.1%), Butyl acetate(4.4%), Ethylbenzene(0.9 - 2.3%*[@]), Liquefied compressed gas(25.0%), Toluene(2.5 - 2.6%*[@]), Vm&p naphtha(2.3%), Xylene(6.9 - 8.2%*[@])
GAL WT: 6.15 WT PCT SOLIDS: 11.42 VOL PCT SOLIDS: 7.24
SOLVENT DENSITY: 5.87 VOC LE: 4.7 VOC AP: 2.8
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

976PTM Acetone(43.3%), Acrylic polymer(6.3%), Alkyd resin-B(4.1%), Butyl acetate(3.6%), Ethylbenzene(0.7 - 1.6%*[@]), Liquefied compressed gas(25.0%), Methyl ethyl ketone(1.2%), Titanium dioxide(2.0%), Toluene(3.3 - 3.4%*[@]), Vm&p naphtha(2.8%), Xylene(4.9 - 5.9%*[@])
GAL WT: 6.21 WT PCT SOLIDS: 12.89 VOL PCT SOLIDS: 7.47
SOLVENT DENSITY: 5.85 VOC LE: 4.6 VOC AP: 2.7
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

978PTM Acetone(43.4%), Acrylic polymer(6.1%), Alkyd resin-B(4.0%), Butyl acetate(4.8%), C.i. pigment yellow(2.0%), Ethylbenzene(0.9 - 2.3%*[@]), Liquefied compressed gas(25.1%), Toluene(1.6 - 1.7%*[@]), Vm&p naphtha(2.0%), Xylene(7.0 - 8.4%*[@])
GAL WT: 6.17 WT PCT SOLIDS: 12.46 VOL PCT SOLIDS: 7.74
SOLVENT DENSITY: 5.85 VOC LE: 4.6 VOC AP: 2.7

FLASH POINT: Below 20°F H: 2 F: 3 R: 0 **OSHA STORAGE:** IB
TSCA STATUS: In Compliance **PHOTO-CHEMICALLY REACTIVE:** NO

980P™ Acetone(43.3%), Acrylic polymer(6.3%), Alkyd resin-B(4.0%), Butyl acetate(3.7%), Ethylbenzene(0.7 - 1.8%* @), Liquefied compressed gas(25.0%), Methyl ethyl ketone(1.1%), Titanium dioxide(1.7%), Toluene(3.1 - 3.2%* @), Vm&p naphtha(2.8%), Xylene(5.4 - 6.5%* @)
GAL WT: 6.20 WT PCT SOLIDS: 12.70 VOL PCT SOLIDS: 7.44
SOLVENT DENSITY: 5.85 VOC LE: 4.6 VOC AP: 2.7
FLASH POINT: Below 20°F H: 2 F: 3 R: 0 **OSHA STORAGE:** IB
TSCA STATUS: In Compliance **PHOTO-CHEMICALLY REACTIVE:** NO

982P™ Acetone(43.3%), Acrylic polymer(5.8%), Alkyd resin-B(3.8%), Butyl acetate(4.7%), C.i. pigment yellow(1.4%), Ethylbenzene(0.9 - 2.2%* @), Liquefied compressed gas(25.0%), Toluene(1.5 - 1.5%* @), Vm&p naphtha(2.1%), Xylene(6.6 - 7.9%* @)
GAL WT: 6.23 WT PCT SOLIDS: 13.18 VOL PCT SOLIDS: 7.54
SOLVENT DENSITY: 5.85 VOC LE: 4.6 VOC AP: 2.7
FLASH POINT: Below 20°F H: 2 F: 3 R: 0 **OSHA STORAGE:** IB
TSCA STATUS: In Compliance **PHOTO-CHEMICALLY REACTIVE:** NO

983P™ Acetone(43.3%), Acrylic polymer(6.3%), Alkyd resin-B(4.2%), Butyl acetate(3.9%), Ethylbenzene(0.7 - 1.8%* @), Liquefied compressed gas(25.0%), Toluene(2.8 - 2.9%* @), Vm&p naphtha(2.9%), Xylene(5.5 - 6.6%* @)
GAL WT: 6.20 WT PCT SOLIDS: 12.83 VOL PCT SOLIDS: 7.58
SOLVENT DENSITY: 5.85 VOC LE: 4.6 VOC AP: 2.7
FLASH POINT: Below 20°F H: 2 F: 3 R: 0 **OSHA STORAGE:** IB
TSCA STATUS: In Compliance **PHOTO-CHEMICALLY REACTIVE:** NO

984P™ Acetone(43.3%), Acrylic polymer(6.4%), Alkyd resin-B(4.1%), Butyl acetate(4.4%), Ethylbenzene(0.9 - 2.2%* @), Liquefied compressed gas(25.0%), Quinacridone pigment(1.0%), Toluene(2.3 - 2.4%* @), Vm&p naphtha(2.3%), Xylene(6.6 - 7.9%* @)
GAL WT: 6.16 WT PCT SOLIDS: 12.27 VOL PCT SOLIDS: 7.70
SOLVENT DENSITY: 5.85 VOC LE: 4.6 VOC AP: 2.7
FLASH POINT: Below 20°F H: 2 F: 3 R: 0 **OSHA STORAGE:** IB
TSCA STATUS: In Compliance **PHOTO-CHEMICALLY REACTIVE:** NO

985P™ Acetone(43.3%), Acrylic polymer(6.2%), Alkyd resin-B(4.0%), Butyl acetate(3.7%), Ethylbenzene(0.6 - 1.6%* @), Liquefied compressed gas(25.0%), Methyl ethyl ketone(1.1%), Titanium dioxide(2.5%), Toluene(3.1 - 3.2%* @), Vm&p naphtha(2.7%), Xylene(4.9 - 5.8%* @)
GAL WT: 6.24 WT PCT SOLIDS: 13.48 VOL PCT SOLIDS: 7.51
SOLVENT DENSITY: 5.84 VOC LE: 4.6 VOC AP: 2.7
FLASH POINT: Below 20°F H: 2 F: 3 R: 0 **OSHA STORAGE:** IB
TSCA STATUS: In Compliance **PHOTO-CHEMICALLY REACTIVE:** NO

987P™ Acetone(43.3%), Acrylic polymer(6.1%), Alkyd resin-B(3.8%), Butyl acetate(3.7%), Ethylbenzene(0.6 - 1.4%* @), Liquefied compressed gas(25.0%), Methyl ethyl ketone(1.1%), Titanium dioxide(3.4%), Toluene(3.2 - 3.2%* @), Vm&p naphtha(2.8%), Xylene(4.2 - 5.0%* @)
GAL WT: 6.27 WT PCT SOLIDS: 14.12 VOL PCT SOLIDS: 7.53
SOLVENT DENSITY: 5.82 VOC LE: 4.5 VOC AP: 2.7
FLASH POINT: Below 20°F H: 2 F: 3 R: 0 **OSHA STORAGE:** IB
TSCA STATUS: In Compliance **PHOTO-CHEMICALLY REACTIVE:** NO

988P™ Acetone(43.3%), Acrylic polymer(6.2%), Alkyd resin-B(4.1%), Butyl acetate(3.9%), Ethylbenzene(0.8 - 2.0%* @), Liquefied compressed gas(25.0%), Toluene(2.8 - 2.9%* @), Vm&p naphtha(2.7%), Xylene(5.9 - 7.1%* @)
GAL WT: 6.18 WT PCT SOLIDS: 12.28 VOL PCT SOLIDS: 7.35
SOLVENT DENSITY: 5.85 VOC LE: 4.6 VOC AP: 2.7
FLASH POINT: Below 20°F H: 2 F: 3 R: 0 **OSHA STORAGE:** IB
TSCA STATUS: In Compliance **PHOTO-CHEMICALLY REACTIVE:** NO

989P™ Acetone(43.3%), Acrylic polymer(6.1%), Alkyd resin-B(3.8%), Butyl acetate(3.7%), Ethylbenzene(0.5 - 1.4%* @), Liquefied compressed gas(25.0%), Methyl ethyl ketone(1.1%), Titanium dioxide(3.6%), Toluene(3.2 - 3.3%* @), Vm&p naphtha(2.8%), Xylene(4.1 - 5.0%* @)
GAL WT: 6.27 WT PCT SOLIDS: 14.19 VOL PCT SOLIDS: 7.58
SOLVENT DENSITY: 5.82 VOC LE: 4.5 VOC AP: 2.7
FLASH POINT: Below 20°F H: 2 F: 3 R: 0 **OSHA STORAGE:** IB

TSCA STATUS: In Compliance **PHOTO-CHEMICALLY REACTIVE:** NO

990P™ Acetone(43.3%), Acrylic polymer(6.3%), Alkyd resin-B(4.0%), Butyl acetate(3.6%), Ethylbenzene(0.6 - 1.6%* @), Liquefied compressed gas(25.0%), Methyl ethyl ketone(1.2%), Titanium dioxide(2.4%), Toluene(3.3 - 3.4%* @), Vm&p naphtha(2.8%), Xylene(4.7 - 5.7%* @)
GAL WT: 6.23 WT PCT SOLIDS: 13.21 VOL PCT SOLIDS: 7.49
SOLVENT DENSITY: 5.85 VOC LE: 4.6 VOC AP: 2.7
FLASH POINT: Below 20°F H: 2 F: 3 R: 0 **OSHA STORAGE:** IB
TSCA STATUS: In Compliance **PHOTO-CHEMICALLY REACTIVE:** NO

991P™ Acetone(43.1%), Acrylic polymer(6.4%), Alkyd resin-B(4.3%), Butyl acetate(3.6%), Ethylbenzene(0.7 - 1.8%* @), Liquefied compressed gas(24.9%), Methyl ethyl ketone(1.2%), Titanium dioxide(1.5%), Toluene(3.4 - 3.5%* @), Vm&p naphtha(2.7%), Xylene(5.4 - 6.5%* @)
GAL WT: 6.20 WT PCT SOLIDS: 12.72 VOL PCT SOLIDS: 7.57
SOLVENT DENSITY: 5.85 VOC LE: 4.6 VOC AP: 2.7
FLASH POINT: Below 20°F H: 2 F: 3 R: 0 **OSHA STORAGE:** IB
TSCA STATUS: In Compliance **PHOTO-CHEMICALLY REACTIVE:** NO

992P™ Acetone(30.0%), Acrylic polymer(7.3%), Alkyd resin-B(4.5%), Azo yellow pigment(2.7%), Butyl acetate(6.7%), Ethylbenzene(0.7 - 1.9%* @), Liquefied compressed gas(29.8%), Methyl ethyl ketone(1.5%), Toluene(3.7 - 3.8%* @), Vm&p naphtha(3.6%), Xylene(5.7 - 6.8%* @), Yellow iron oxide(1.1%)
GAL WT: 6.15 WT PCT SOLIDS: 16.24 VOL PCT SOLIDS: 9.49
SOLVENT DENSITY: 5.69 VOC LE: 4.6 VOC AP: 3.3
FLASH POINT: Below 20°F H: 2 F: 3 R: 0 **OSHA STORAGE:** IB
TSCA STATUS: In Compliance **PHOTO-CHEMICALLY REACTIVE:** NO

1000P™ Acetone(4.4%), Acrylic polymer(6.8%), Alkyd resin-B(4.5%), Butyl acetate(1.8%), Dimethyl glutarate(1.2%), Ethylbenzene(0.9 - 2.3%* @), Ethylene glycol monobutyl ether acetate(5.0%* @), Liquefied compressed gas(25.0%), Medium mineral spirits(4.1%), Propylene glycol monomethyl ether acetate(3.3%), Toluene(6.9 - 7.0%* @), Vm&p naphtha(22.8%), Xylene(6.7 - 8.1%* @)
GAL WT: 6.23 WT PCT SOLIDS: 12.85 VOL PCT SOLIDS: 8.11
SOLVENT DENSITY: 5.91 VOC LE: 5.4 VOC AP: 5.2
FLASH POINT: Below 20°F H: 2 F: 3 R: 0 **OSHA STORAGE:** IB
TSCA STATUS: In Compliance **PHOTO-CHEMICALLY REACTIVE:** NO

1001P™ Acetone(33.6%), Acrylic polymer(6.4%), Alkyd resin-B(4.2%), Butyl acetate(3.2%), C.i. pigment yellow(1.1%), Ethylbenzene(0.9 - 2.2%* @), Liquefied compressed gas(25.1%), Methyl ethyl ketone(10.5%), Toluene(2.0 - 2.1%* @), Vm&p naphtha(2.7%), Xylene(6.7 - 8.1%* @)
GAL WT: 6.19 WT PCT SOLIDS: 12.79 VOL PCT SOLIDS: 7.74
SOLVENT DENSITY: 5.85 VOC LE: 4.8 VOC AP: 3.3
FLASH POINT: Below 20°F H: 2 F: 3 R: 0 **OSHA STORAGE:** IB
TSCA STATUS: In Compliance **PHOTO-CHEMICALLY REACTIVE:** NO

1003P™ Acetone(4.0%), Calcium carbonate(6.8%), Dimethyl glutarate(1.1%), Ethylbenzene(0.1 - 0.3%* @), Ethylene glycol monobutyl ether acetate(4.6%* @), Hydrous magnesium silicate(3.2%), Liquefied compressed gas(23.1%), Medium mineral spirits(3.7%), Methyl amyl ketone(7.2%), Methyl n-propyl ketone(2.0%), Polymer base(7.7%), Propylene glycol monomethyl ether acetate(3.0%), Titanium dioxide(6.6%), Toluene(4.0 - 4.0%* @), Vm&p naphtha(17.9%)
GAL WT: 7.03 WT PCT SOLIDS: 26.22 VOL PCT SOLIDS: 10.78
SOLVENT DENSITY: 5.84 VOC LE: 5.1 VOC AP: 4.9
FLASH POINT: Below 20°F H: 2 F: 3 R: 0 **OSHA STORAGE:** IB
TSCA STATUS: In Compliance **PHOTO-CHEMICALLY REACTIVE:** NO

1004P™ Acetone(4.5%), Acrylic polymer(6.3%), Alkyd resin-B(4.2%), Butyl acetate(1.4%), Dimethyl glutarate(1.3%), Ethylbenzene(0.8 - 2.1%* @), Ethylene glycol monobutyl ether acetate(5.2%* @), Liquefied compressed gas(25.0%), Medium mineral spirits(4.3%), Propylene glycol monomethyl ether acetate(3.4%), Titanium dioxide(2.2%), Toluene(7.3 - 7.4%* @), Vm&p naphtha(22.3%), Xylene(6.0 - 7.4%* @)
GAL WT: 6.30 WT PCT SOLIDS: 13.43 VOL PCT SOLIDS: 7.72
SOLVENT DENSITY: 5.91 VOC LE: 5.4 VOC AP: 5.2
FLASH POINT: Below 20°F H: 2 F: 3 R: 0 **OSHA STORAGE:** IB
TSCA STATUS: In Compliance **PHOTO-CHEMICALLY REACTIVE:** NO

1005PTM Acetone(4.5%), Acrylic polymer(6.4%), Alkyd resin-B(4.3%), Dimethyl glutarate(1.3%), Ethylbenzene(0.7 - 1.7%*), Ethylene glycol monobutyl ether acetate(5.2%*), Liquefied compressed gas(25.0%), Medium mineral spirits(4.4%), Methyl ethyl ketone(1.2%), Propylene glycol monomethyl ether acetate(3.5%), Titanium dioxide(3.1%), Toluene(7.9 - 8.0%*), Vm&p naphtha(22.8%), Xylene(5.0 - 6.1%*)
GAL WT: 6.32 WT PCT SOLIDS: 14.06 VOL PCT SOLIDS: 7.83
SOLVENT DENSITY: 5.89 VOC LE: 5.4 VOC AP: 5.1
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

1006PTM Acetone(4.5%), Acrylic polymer(5.8%), Alkyd resin-B(3.6%), Butyl acetate(1.3%), Dimethyl glutarate(1.3%), Ethylbenzene(0.5 - 1.4%*), Ethylene glycol monobutyl ether acetate(5.2%*), Lead chromate molybdate(2.4%*), Lead chromate oxide(3.4%*), Liquefied compressed gas(25.0%), Medium mineral spirits(4.3%), Methyl ethyl ketone(1.1%), Propylene glycol monomethyl ether acetate(3.4%), Toluene(7.7 - 7.7%*), Vm&p naphtha(22.9%), Xylene(4.1 - 5.0%*)
GAL WT: 6.44 WT PCT SOLIDS: 15.41 VOL PCT SOLIDS: 7.34
SOLVENT DENSITY: 5.88 VOC LE: 5.4 VOC AP: 5.2
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

1007PTM Acetone(4.5%), Acrylic polymer(6.2%), Alkyd resin-B(4.1%), Dimethyl glutarate(1.3%), Ethylbenzene(0.7 - 1.7%*), Ethylene glycol monobutyl ether acetate(5.2%*), Liquefied compressed gas(25.0%), Medium mineral spirits(4.4%), Methyl ethyl ketone(1.1%), Propylene glycol monomethyl ether acetate(3.4%), Titanium dioxide(3.3%), Toluene(7.7 - 7.7%*), Vm&p naphtha(22.8%), Xylene(5.0 - 6.1%*)
GAL WT: 6.35 WT PCT SOLIDS: 14.43 VOL PCT SOLIDS: 7.79
SOLVENT DENSITY: 5.89 VOC LE: 5.4 VOC AP: 5.1
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

1008PTM Acetone(4.5%), Acrylic polymer(6.0%), Alkyd resin-B(4.0%), Butyl acetate(1.1%), Dimethyl glutarate(1.3%), Ethylbenzene(0.7 - 1.9%*), Ethylene glycol monobutyl ether acetate(5.2%*), Liquefied compressed gas(25.0%), Medium mineral spirits(4.3%), Propylene glycol monomethyl ether acetate(3.4%), Titanium dioxide(1.1%), Toluene(7.0 - 7.0%*), Vm&p naphtha(23.4%), Xylene(5.5 - 6.7%*), Yellow iron oxide(2.6%)
GAL WT: 6.34 WT PCT SOLIDS: 13.98 VOL PCT SOLIDS: 7.50
SOLVENT DENSITY: 5.90 VOC LE: 5.4 VOC AP: 5.2
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

1009PTM Acetone(4.5%), Acrylic polymer(6.4%), Alkyd resin-B(4.3%), C.i. pigment red 48:4(1.4%), Dimethyl glutarate(1.3%), Ethylbenzene(0.8 - 2.1%*), Ethylene glycol monobutyl ether acetate(5.2%*), Lead chromate molybdate(0.5%*), Liquefied compressed gas(25.0%), Medium mineral spirits(4.2%), Methyl ethyl ketone(1.2%), Propylene glycol monomethyl ether acetate(3.4%), Toluene(7.9 - 8.0%*), Vm&p naphtha(22.3%), Xylene(6.3 - 7.7%*)
GAL WT: 6.27 WT PCT SOLIDS: 13.29 VOL PCT SOLIDS: 8.04
SOLVENT DENSITY: 5.91 VOC LE: 5.4 VOC AP: 5.2
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

1010PTM Acetone(4.5%), Acrylic polymer(6.2%), Alkyd resin-B(4.2%), Dimethyl glutarate(1.3%), Ethylbenzene(0.8 - 2.0%*), Ethylene glycol monobutyl ether acetate(5.2%*), Lead chromates(0.2%*), Lead sulfochromate yellow(1.2%*), Liquefied compressed gas(25.0%), Medium mineral spirits(4.3%), Methyl ethyl ketone(1.2%), Propylene glycol monomethyl ether acetate(3.4%), Titanium dioxide(1.1%), Toluene(7.9 - 7.9%*), Vm&p naphtha(22.6%), Xylene(5.9 - 7.2%*)
GAL WT: 6.31 WT PCT SOLIDS: 13.43 VOL PCT SOLIDS: 7.50
SOLVENT DENSITY: 5.91 VOC LE: 5.4 VOC AP: 5.2
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

1011PTM Acetone(4.5%), Acrylic polymer(5.9%), Alkyd resin-B(3.9%), Butyl acetate(1.2%), Dimethyl glutarate(1.3%), Ethylbenzene(0.7 - 1.7%*), Ethylene glycol monobutyl ether acetate(5.2%*), Liquefied compressed gas(25.0%), Medium mineral spirits(4.3%), Propylene glycol

monomethyl ether acetate(3.4%), Titanium dioxide(1.9%), Toluene(7.2 - 7.3%*), Vm&p naphtha(23.1%), Xylene(5.0 - 6.1%*), Yellow iron oxide(1.7%)

GAL WT: 6.35 WT PCT SOLIDS: 14.35 VOL PCT SOLIDS: 7.67
SOLVENT DENSITY: 5.89 VOC LE: 5.4 VOC AP: 5.2
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

1012PTM Acetone(4.5%), Acrylic polymer(6.7%), Alkyd resin-B(4.4%), Dimethyl glutarate(1.3%), Ethylbenzene(0.9 - 2.2%*), Ethylene glycol monobutyl ether acetate(5.2%*), Liquefied compressed gas(25.0%), Medium mineral spirits(4.3%), Methyl ethyl ketone(1.1%), Propylene glycol monomethyl ether acetate(3.4%), Toluene(7.6 - 7.7%*), Vm&p naphtha(23.2%), Xylene(6.5 - 8.0%*)
GAL WT: 6.21 WT PCT SOLIDS: 12.13 VOL PCT SOLIDS: 7.70
SOLVENT DENSITY: 5.91 VOC LE: 5.4 VOC AP: 5.2
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

1013PTM Acetone(4.5%), Acrylic polymer(5.8%), Alkyd resin-B(3.7%), Butyl acetate(1.7%), Dimethyl glutarate(1.3%), Ethylbenzene(0.9 - 2.2%*), Ethylene glycol monobutyl ether acetate(5.2%*), Liquefied compressed gas(25.0%), Medium mineral spirits(4.3%), Monoazo pigment(2.1%), Propylene glycol monomethyl ether acetate(3.4%), Toluene(7.0 - 7.0%*), Vm&p naphtha(22.3%), Xylene(6.5 - 7.9%*)
GAL WT: 6.26 WT PCT SOLIDS: 12.71 VOL PCT SOLIDS: 7.66
SOLVENT DENSITY: 5.92 VOC LE: 5.4 VOC AP: 5.2
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

1014PTM Acetone(4.5%), Acrylic polymer(6.2%), Alkyd resin-B(4.0%), Butyl acetate(1.2%), Dimethyl glutarate(1.3%), Ethylbenzene(0.6 - 1.5%*), Ethylene glycol monobutyl ether acetate(5.2%*), Liquefied compressed gas(25.0%), Medium mineral spirits(4.4%), Methyl ethyl ketone(1.3%), Propylene glycol monomethyl ether acetate(3.4%), Titanium dioxide(2.8%), Toluene(7.9 - 7.9%*), Vm&p naphtha(22.8%), Xylene(4.5 - 5.5%*)
GAL WT: 6.33 WT PCT SOLIDS: 14.45 VOL PCT SOLIDS: 8.03
SOLVENT DENSITY: 5.89 VOC LE: 5.4 VOC AP: 5.1
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

1015PTM Acetone(4.5%), Acrylic polymer(6.0%), Alkyd resin-B(4.0%), Butyl acetate(1.1%), Dimethyl glutarate(1.3%), Ethylbenzene(0.7 - 1.8%*), Ethylene glycol monobutyl ether acetate(5.2%*), Liquefied compressed gas(25.0%), Medium mineral spirits(4.3%), Propylene glycol monomethyl ether acetate(3.4%), Titanium dioxide(1.7%), Toluene(7.1 - 7.2%*), Vm&p naphtha(23.3%), Xylene(5.2 - 6.4%*), Yellow iron oxide(2.3%)
GAL WT: 6.35 WT PCT SOLIDS: 14.23 VOL PCT SOLIDS: 7.58
SOLVENT DENSITY: 5.89 VOC LE: 5.4 VOC AP: 5.2
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

1016PTM Acetone(4.5%), Acrylic polymer(6.0%), Alkyd resin-B(3.8%), Azo yellow pigment(1.5%), Butyl acetate(1.9%), Dimethyl glutarate(1.3%), Ethylbenzene(0.6 - 1.6%*), Ethylene glycol monobutyl ether acetate(5.2%*), Isoindolinone pigment(1.3%), Liquefied compressed gas(25.0%), Medium mineral spirits(4.3%), Methyl ethyl ketone(1.3%), Propylene glycol monomethyl ether acetate(3.4%), Toluene(7.7 - 7.7%*), Vm&p naphtha(22.8%), Xylene(4.7 - 5.8%*)
GAL WT: 6.28 WT PCT SOLIDS: 13.61 VOL PCT SOLIDS: 8.04
SOLVENT DENSITY: 5.90 VOC LE: 5.4 VOC AP: 5.1
FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

1017PTM Acetone(4.5%), Acrylic polymer(6.0%), Alkyd resin-B(4.0%), Butyl acetate(2.1%), C.i. pigment yellow(1.6%), Dimethyl glutarate(1.3%), Ethylbenzene(0.9 - 2.3%*), Ethylene glycol monobutyl ether acetate(5.2%*), Liquefied compressed gas(25.0%), Medium mineral spirits(4.2%), Propylene glycol monomethyl ether acetate(3.4%), Toluene(6.2 - 6.3%*), Vm&p naphtha(22.5%), Xylene(6.7 - 8.2%*)
GAL WT: 6.28 WT PCT SOLIDS: 13.25 VOL PCT SOLIDS: 7.88
SOLVENT DENSITY: 5.91 VOC LE: 5.4 VOC AP: 5.2

FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

1018P™ Acetone(4.5%), Acrylic polymer(6.0%), Alkyd resin-B(3.9%), Butyl acetate(1.1%), Dimethyl glutarate(1.3%), Ethylbenzene(0.7 - 1.8%* @), Ethylene glycol monobutyl ether acetate(5.2%* @), Liquefied compressed gas(25.0%), Medium mineral spirits(4.3%), Propylene glycol monomethyl ether acetate(3.4%), Titanium dioxide(1.5%), Toluene(7.1 - 7.2%* @), Vm&p naphtha(23.3%), Xylene(5.2 - 6.4%* @), Yellow iron oxide(2.2%)

GAL WT: 6.34 WT PCT SOLIDS: 14.15 VOL PCT SOLIDS: 7.60
SOLVENT DENSITY: 5.89 VOC LE: 5.4 VOC AP: 5.2

FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

1019P™ Acetone(4.5%), Acrylic polymer(6.7%), Alkyd resin-B(4.5%), Carbon black(0.1%), Dimethyl glutarate(1.3%), Ethylbenzene(0.8 - 2.0%* @), Ethylene glycol monobutyl ether acetate(5.2%* @), Liquefied compressed gas(25.0%), Medium mineral spirits(4.3%), Methyl ethyl ketone(1.2%), Propylene glycol monomethyl ether acetate(3.9%), Toluene(8.1 - 8.2%* @), Vm&p naphtha(23.0%), Xylene(5.9 - 7.2%* @)

GAL WT: 6.22 WT PCT SOLIDS: 12.19 VOL PCT SOLIDS: 7.66
SOLVENT DENSITY: 5.91 VOC LE: 5.4 VOC AP: 5.2

FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

1020P™ Acetone(4.5%), Acrylic polymer(6.2%), Alkyd resin-B(4.1%), Dimethyl glutarate(1.3%), Ethylbenzene(0.6 - 1.6%* @), Ethylene glycol monobutyl ether acetate(5.2%* @), Liquefied compressed gas(25.0%), Medium mineral spirits(4.4%), Methyl ethyl ketone(1.1%), Propylene glycol monomethyl ether acetate(3.4%), Titanium dioxide(4.0%), Toluene(7.8 - 7.9%* @), Vm&p naphtha(22.7%), Xylene(4.6 - 5.6%* @)

GAL WT: 6.37 WT PCT SOLIDS: 14.88 VOL PCT SOLIDS: 7.90
SOLVENT DENSITY: 5.89 VOC LE: 5.4 VOC AP: 5.1

FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

1021P™ Acetone(4.5%), Acrylic polymer(6.6%), Alkyd resin-B(4.4%), Dimethyl glutarate(1.3%), Ethylbenzene(0.8 - 1.9%* @), Ethylene glycol monobutyl ether acetate(5.2%* @), Liquefied compressed gas(25.0%), Medium mineral spirits(4.3%), Methyl ethyl ketone(1.2%), Propylene glycol monomethyl ether acetate(3.4%), Titanium dioxide(1.0%), Toluene(9.6 - 9.7%* @), Vm&p naphtha(22.0%), Xylene(5.7 - 6.9%* @)

GAL WT: 6.25 WT PCT SOLIDS: 12.62 VOL PCT SOLIDS: 7.72
SOLVENT DENSITY: 5.92 VOC LE: 5.4 VOC AP: 5.2

FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

1022P™ Acetone(4.5%), Acrylic polymer(6.2%), Alkyd resin-B(4.1%), Dimethyl glutarate(1.3%), Ethylbenzene(0.6 - 1.6%* @), Ethylene glycol monobutyl ether acetate(5.2%* @), Liquefied compressed gas(25.0%), Medium mineral spirits(4.4%), Methyl ethyl ketone(1.2%), Propylene glycol monomethyl ether acetate(3.4%), Titanium dioxide(4.0%), Toluene(8.0 - 8.0%* @), Vm&p naphtha(22.6%), Xylene(4.6 - 5.6%* @)

GAL WT: 6.37 WT PCT SOLIDS: 14.83 VOL PCT SOLIDS: 7.90
SOLVENT DENSITY: 5.89 VOC LE: 5.4 VOC AP: 5.1

FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

1023P™ Acetone(4.5%), Acrylic polymer(6.1%), Alkyd resin-B(4.1%), Dimethyl glutarate(1.3%), Ethylbenzene(0.6 - 1.5%* @), Ethylene glycol monobutyl ether acetate(5.2%* @), Liquefied compressed gas(25.1%), Medium mineral spirits(4.4%), Methyl ethyl ketone(1.1%), Propylene glycol monomethyl ether acetate(3.4%), Titanium dioxide(4.0%), Toluene(7.8 - 7.9%* @), Vm&p naphtha(22.8%), Xylene(4.5 - 5.6%* @)

GAL WT: 6.36 WT PCT SOLIDS: 14.69 VOL PCT SOLIDS: 7.81
SOLVENT DENSITY: 5.89 VOC LE: 5.4 VOC AP: 5.1

FLASH POINT: Below 20° F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

Footnotes:

TSCA: in compliance = In compliance with TSCA Inventory requirements for commercial purposes.

ACGIH = American Conference of Government Industrial Hygienists.

IARC = International agency for Research on Cancer.

NTP = National Toxicology Program.

OSHA = Occupational Safety and Health Administration.

PNOR = Particles Not Otherwise Regulated.

PNOC = Particles Not Otherwise Classified.

STEL = Short Term Exposure Limit.

TWA = Time Weighted Average.

TM = Is a Trademark of E.I. du Pont de Nemours & Co.

* = Section 313 Supplier Notification: These chemicals are subject to the reporting requirements of Section 313 of the Emergency planning and Right-to-Know act of 1986 and of 40 CFR 372.

@ = Clean Air Act Hazardous Air Pollutant.

= EPCRA Section 302 - Extremely Hazardous Substance.

NOTICE:

The information on this Material Safety Data Sheet relates only to the specific material designated herein and does not relate to use in combination with any other material or in any process.

Product Manager - Refinish Sales

Prepared by: HazCom Coordinator