

SECTION 1 - Product and Company Identification

Manufacturer: E.I. du Pont de Nemours & Co.
Du Pont Performance Coatings
Wilmington, DE, 19898

Telephone: Product information: (800) 441-7515
Medical emergency: (800) 441-3637
Transportation emergency: (800) 424-9300
(CHEMTREC)

Product: **Imron® 2.1-HG,2.8-HG,3.5-HG Solid Enamels;**
Imron® 2.8FT-C,3.4 HG-C, 3.5HG-C Clears;
Imron® 2.8-PR Primers

DOT Shipping Name: See DOT addendum.

Hazardous Materials Information: See Section 10.

INGREDIENTS	CAS #	VAPOR PRESSURE	EXPOSURE LIMITS
Acrylic polymer-E	170475-04-4	None	A None O None
Aluminum	7429-90-5	None	A 10.0 mg/m3 particulate A 5.0 mg/m3 Dust O 15.0 mg/m3 Total Dust O 5.0 mg/m3 Respirable Dust
Aluminum hydrate	21645-51-2	None	A None O None
Amorphous silica	7631-86-9	None	A 10.0 mg/m3 Total Dust O 20.0 mppcf D 3.0 mg/m3
Amorphous silica - silica base	63231-67-4	None	A 10.0 mg/m3 D 1.0 mg/m3 Respirable Dust O None
Amorphous silica-fumed	68611-44-9	None	A 2.0 mg/m3 Respirable Dust D 1.0 mg/m3 Respirable Dust O None
Aromatic hydrocarbon	64742-95-6	10.0@25.0°C	D 50.0 ppm A None O None
Azo yellow pigment	31837-42-0	None	A 10.0 mg/m3 O 5.0 mg/m3 Respirable Dust O 15.0 mg/m3
Barium sulfate	7727-43-7	None	A 10.0 mg/m3 Total Dust A 5.0 mg/m3 Respirable Dust O 15.0 mg/m3 Total Dust O 5.0 mg/m3 Respirable Dust D 10.0 mg/m3 Total Dust
Butanedioic acid, dimethyl ester	106-65-0	None	D 10.0 mg/m3 A None O None
Butyl acetate	123-86-4	10.0	A 200.0 ppm 15 min STEL A 150.0 ppm O 150.0 ppm
C.i. pigment red 254	84632-65-5	None	A None O None
Calcium carbonate	471-34-1	None	A 10.0 mg/m3 O 15.0 mg/m3 Total Dust

SECTION 2 - Composition/information on ingredients

INGREDIENTS	CAS #	VAPOR PRESSURE	EXPOSURE LIMITS
1,2,4-trimethyl benzene	95-63-6	7.0@44.4°C	A 25.0 ppm O 25.0 ppm
1,3,5-trimethyl benzene	108-67-8	None	A 25.0 ppm O None
2,4-pentanedione	123-54-6	9.0	D 5.0 ppm 8 & 12 hour TWA A None O None
2-(2h-benzotriazol-2-yl)-4,6-bis(1-methyl-1-phenylethyl)phenol	70321-86-7	None	S 2.0 mg/m3 A None O None
2-ethylhexyl acetate	103-09-3	0.5	A None O None
2-methyl butyl acetate	624-41-9	None	A 100.0 ppm 15 min STEL A 50.0 ppm O None
4-chlorobenzotrifluoride	98-56-6	7.6@25.0°C	D 20.0 ppm 8 & 12 hour TWA A None O None
Acetone	67-64-1	247.0@68.0°F	A 750.0 ppm 15 min STEL A 500.0 ppm O 1000.0 ppm D 500.0 ppm 8 & 12 hour TWA
Acrylic polymer-A	Not Avail	None	A None O None
Acrylic polymer-B	42767-92-0	None	A None O None
Acrylic polymer-C	70942-12-0	None	A None O None
Acrylic polymer-D	104032-39-5	None	A None O None

INGREDIENTS	CAS #	VAPOR PRESSURE	EXPOSURE LIMITS	INGREDIENTS	CAS #	VAPOR PRESSURE	EXPOSURE LIMITS
Carbon black	1333-86-4	None	O 5.0 mg/m3 Respirable Dust A 3.5 mg/m3 O 3.5 mg/m3 D 0.5 mg/m3 8 & 12 hour TWA	Methyl ethyl ketone	78-93-3	89.0 @ 0.0	A 300.0ppm 15 min STEL A 200.0 ppm O 200.0 ppm D 300.0 ppm 15 min TWA D 200.0 ppm 8 & 12 hour TWA
Cristobalite siO2	14464-46-1	None	A 50.0 ug/m3 D 0.1 mg/m3 Respirable Dust O None	Monoazo pigment	12236-62-3	None	A 10.0 mg/m3 inhalable dust particulate O 15.0 mg/m3 Total Dust O 5.0 mg/m3 Respirable Dust
Diatomaceous earth	68855-54-9	None	A None O None	Organoclay	68911-87-5	None	A None O None
Dimethyl glutarate	1119-40-0	0.2	D 10.0 mg/m3 A None O None	Phthalocyanine blue pigment	147-14-8	None	A 10.0 mg/m3 inhalable dust PNOC A 3.0 mg/m3 respirable particulate PNOC O 15.0 mg/m3 Total Dust PNOR O 5.0 mg/m3 TWA Respirable Dust PNOR
Ethyl acetate	141-78-6	93.2@25.0°C	A 400.0 ppm O 400.0 ppm	Phthalocyanine green pigment	14302-13-7	None	A None O None
Ethylbenzene	100-41-4	7.0	A 125.0 ppm 15 min STEL A 100.0 ppm O 100.0 ppm D 25.0 ppm 8 & 12 hour TWA	Polyester resin	71010-58-7	None	A None O None
Ethylene glycol monobutyl ether acetate	112-07-2	0.3	A 20.0 ppm D 10.0 ppm Skin O None	Primary amyl acetate	628-63-7	4.2	A 100.0 ppm 15 min STEL A 50.0 ppm O 100.0 ppm
Hydrous magnesium silicate	14807-96-6	None	A 2.0 mg/m3 Respirable Dust D 0.5 mg/m3 8 & 12 hour TWA Respirable Dust O None	Propylene glycol monomethyl ether acetate	108-65-6	3.8	D 10.0 ppm 8 & 12 hour TWA A None O None
Isoindolinone pigment	36888-99-0	None	A None O None	Quartz-crystalline silica	14808-60-7	None	A 50.0 ug/m3 Respirable Dust O 0.1 mg/m3 Respirable Dust D 0.1 mg/m3 Respirable Dust
Isopropyl alcohol	67-63-0	48.0	O 400.0 ppm D 200.0 ppm 8 & 12 hour TWA A 500.0 ppm 15 min STEL A 400.0 ppm	Quinacridone pigment	1047-16-1	None	A 10.0 mg/m3 inhalable dust A 3.0 mg/m3 O 15.0 mg/m3 Total Dust PNOR O 5.0 mg/m3 Respirable Dust D 10.0 mg/m3
Kaolin	1332-58-7	None	A 2.0 mg/m3 Respirable Dust O 15.0 mg/m3 TWA Total Dust O 5.0 mg/m3 TWA Respirable Dust	Medium mineral spirits	64742-88-7	0.3@68.0°F	D 50.0 ppm 8 & 12 hour TWA A None O None
Methyl amyl ketone	110-43-0	3.4	A 50.0 ppm O 100.0 ppm				

INGREDIENTS	CAS #	VAPOR PRESSURE	EXPOSURE LIMITS	Potential Health Effects:
Red iron oxide light	1332-37-2	None	Total Dust A 10.0 mg/m3 PNOR A 3.0 mg/m3 Respirable Dust A 5.0 mg/m3 Fe O 15.0 mg/m3 Total Dust O 5.0 mg/m3 Respirable Dust	Inhalation: May cause nose and throat irritation. May cause nervous system depression, characterized by the following progressive steps: headache, dizziness, nausea, staggering gait, confusion, unconsciousness. Reports have associated repeated and prolonged overexposure to solvents with permanent brain and nervous system damage. If this product contains or is mixed with an isocyanate activator/hardener, the following health effects may apply: Exposure to isocyanates may cause respiratory sensitization. This effect may be permanent. Symptoms include an asthma-like reaction with shortness of breath, wheezing, cough or permanent lung sensitization. This effect may be delayed for several hours after exposure. Repeated overexposure to isocyanates may cause a decrease in lung function, which may be permanent. Individuals with lung or breathing problems or prior reactions to isocyanates must not be exposed to vapors or spray mist of this product.
Stoddard solvent	8052-41-3	None	A 100.0 ppm O 500.0 ppm TWA D 50.0 ppm 8 & 12 hour TWA	Ingestion: May result in gastrointestinal distress
Substituted benzotriazole	127519-17-9	0.1	S 4.0 mg/m3 A None O None	Skin or Eye Contact: May cause irritation or burning of the eyes. Repeated or prolonged liquid contact may cause skin irritation with discomfort and dermatitis.
Substituted benzotriazole	25973-55-1	None	A None O None	
Titanium dioxide	13463-67-7	None	A 10.0 mg/m3 O 15.0 mg/m3 Total Dust D 10.0 mg/m3 Total Dust D 5.0 mg/m3 Respirable Dust	Other Potential Health Effects in addition to those listed above: 2,4-pentanedione 2,4-pentanedione, a component of this product, is regulated by the U.S. EPA, under a significant new use rule. It is a violation of federal law to sell or use this product in consumer applications, including to private individuals, schools, and vocational schools. Can be absorbed through the skin in harmful amounts. Repeated exposures to high concentrations has caused adverse health effects in laboratory animals. These effects involved the central nervous system, immune system, and the red blood cell forming system. No effect was seen at 100 ppm. The odor is disagreeable at a few ppm. Repeated or prolonged skin contact may cause any of the following: skin sensitization. Skin or eye contact may cause any of the following: irritation. Overexposure of this substance may cause effects on any of the following organs/systems: central nervous system, lungs, upper respiratory system, thymus.
Toluene	108-88-3	22.0	A 50.0 ppm Skin O 300.0 ppm CEIL O 500.0 ppm 10 min TWA O 200.0 ppm D 50.0 ppm 8 & 12 hour TWA	4-chlorobenzotrifluoride Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: skin. Prolonged or repeated exposure may cause damage to any of the following organs/systems: kidneys, liver, thyroid. Potential skin sensitizer that may cause allergic reactions and contact dermatitis resulting in severe irritation, dryness, and cracking of the skin. Ingestion may cause any of the following: gastrointestinal irritation. Eye contact may cause any of the following: permanent eye injury. Inhalation may cause any of the following: stupor (central nervous system depression), respiratory tract irritation.
Xylene	1330-20-7	8.0@25.0°C	A 150.0 ppm 15 min STEL A 100.0 ppm O 100.0 ppm D 150.0 ppm 15 min STEL D 100.0 ppm 8 & 12 hour TWA	Acetone The following medical conditions may be aggravated by exposure: lung disease, eye disorders, skin disorders. Overexposure may cause damage to any of the following organs/systems: blood, central nervous system, eyes, kidneys, liver, respiratory system, skin.
Yellow iron oxide	51274-00-1	None	A 10.0 mg/m3 O 15.0 mg/m3	Acrylic polymer-A Contact may cause skin irritation with discomfort or rash. May cause eye irritation with discomfort, tearing, or blurred vision.
Zinc oxide	1314-13-2	None	A 10.0 mg/m3 15 min STEL Respirable Dust A 2.0 mg/m3 Respirable Dust O 15.0 mg/m3 Total Dust O 5.0 mg/m3 Respirable Dust	Acrylic polymer-B Skin contact may cause any of the following: mild irritation.

*A=ACGIH, O=OSHA, D=DuPont, S=Suppliers. Limits are 8 hour TWA unless otherwise specified. Vapor pressure @20°C unless otherwise noted.

SECTION 3 - Hazards identification

Butyl acetate

Aromatic hydrocarbon
The following medical conditions may be aggravated by exposure: skin disorders. Laboratory studies with rats have shown that petroleum distillates can cause kidney damage and kidney or liver tumors. These effects were not seen in similar studies with guinea pigs, dogs, or monkeys. Several studies evaluating petroleum workers have not shown a significant increase of kidney damage or an increase in kidney or liver tumors.

May cause abnormal liver function. The following medical conditions may be aggravated by exposure: respiratory system. Tests for embryotoxic activity in animals has been inconclusive. Rats exposed to very high airborne levels have exhibited high frequency hearing deficits. The significance of this to man is unknown. Has been toxic to the fetus in laboratory animals at doses that are toxic to the mother.

Carbon black

Is an IARC, NTP or OSHA carcinogen. Has shown carcinogenic activity in laboratory animals at high doses. Significance to man is unknown. The following medical conditions may be aggravated by exposure: asthma, respiratory disease.

WARNING: This chemical is known to the State of California to cause cancer.

Cristobalite siO₂

Is an IARC, NTP or OSHA carcinogen. Repeated overexposure to crystalline silica may lead to x-ray changes and chronic lung disease.

WARNING: This chemical is known to the State of California to cause cancer.

Ethyl acetate

Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: eyes, respiratory system, skin. Tests in laboratory animals have shown effects on any of the following organs/systems: blood, kidneys, liver.

Ethylbenzene

Is an IARC, NTP or OSHA carcinogen. Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: central nervous system, kidneys, liver, lungs.

Recurrent overexposure may result in liver and kidney injury. Studies in laboratory animals have shown reproductive, embryotoxic and developmental effects.

WARNING: This chemical is known to the State of California to cause cancer.

Ethylene glycol monobutyl ether acetate

May destroy red blood cells. May cause abnormal kidney function. May cause temporary upper respiratory and/or lung irritation with cough, difficult breathing, or shortness of breath. The following medical conditions may be aggravated by exposure: central nervous system, gastrointestinal system, kidneys, liver, dermatitis. Can be absorbed through the skin in harmful amounts. Overexposure may cause damage to any of the following organs/systems: blood, kidneys, liver. Ingestion may cause headache, nausea, vomiting, dizziness, and drowsiness.

Isopropyl alcohol

The following medical conditions may be aggravated by exposure: dermatitis, respiratory disease. Developmental toxicity was seen in rat's offspring at doses that were maternally toxic. Contact will cause moderate to severe redness and swelling, itching, tingling sensation, painful burning. May cause injury to the cornea of the eyes. Prolonged or repeated exposure may cause damage to any of the following organs/systems: liver. Ingestion studies on laboratory animals showed that very high oral doses caused increased liver and kidney weights.

Kaolin

The following medical conditions may be aggravated by exposure: asthma, dermatitis. Repeated or prolonged inhalation may cause any of the following: lung injury.

Medium mineral spirits

This substance may cause damage to any of the following organs/systems: blood. Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: central nervous system. This substance may cause damage to any of the following organs/systems: central nervous system, eyes, kidneys. Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: kidneys, liver. This substance may cause damage to any of the following organs/systems: liver, lungs, reproductive system. Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: respiratory system. This substance may cause damage to any of the following organs/systems: skin. Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of

the following: skin. Laboratory studies with rats have shown that petroleum distillates can cause kidney damage and kidney or liver tumors. These effects were not seen in similar studies with guinea pigs, dogs, or monkeys. Several studies evaluating petroleum workers have not shown a significant increase of kidney damage or an increase in kidney or liver tumors.

Methyl ethyl ketone

Material is irritating to mucous membranes and upper respiratory tract. Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: central nervous system, eyes, respiratory system, skin. Prolonged or repeated overexposure may cause any of the following: conjunctivitis, dermatitis. High concentrations have caused embryotoxic effects in laboratory animals. Aspiration may occur during swallowing or vomiting, resulting in lung damage. Ingestion may cause headache, nausea, vomiting, dizziness, and drowsiness.

Propylene glycol monomethyl ether acetate

Recurrent overexposure may result in liver and kidney injury.

Quartz-crystalline silica

Is an IARC, NTP or OSHA carcinogen. Repeated overexposure to crystalline silica may lead to x-ray changes and chronic lung disease. Inhalation of high dust concentrations may cause: breathing difficulties, lung injury.

WARNING: This chemical is known to the State of California to cause cancer.

Red iron oxide light

Long-term respiratory exposure of iron oxide may result in deposition of particles in the lung (benign siderosis).

Stoddard solvent

The following medical conditions may be aggravated by exposure: asthma, skin disorders. Laboratory studies with rats have shown that petroleum distillates can cause kidney damage and kidney or liver tumors. These effects were not seen in similar studies with guinea pigs, dogs, or monkeys. Several studies evaluating petroleum workers have not shown a significant increase of kidney damage or an increase in kidney or liver tumors.

Substituted benzotriazole

Tests in laboratory animals have shown effects on any of the following organs/systems: blood, kidneys, liver, thyroid, upper respiratory system. The following medical conditions may be aggravated by exposure: jaundice, liver disease.

Substituted benzotriazole

The following medical conditions may be aggravated by exposure: jaundice, liver disease. Repeated or prolonged ingestion may cause any of the following: changes in the blood, liver effects.

Titanium dioxide

In a lifetime inhalation test, lung cancers were found in some rats exposed to 250 mg/m³ respirable titanium dust. Analysis of the titanium dioxide concentrations in the rat's lungs showed that the lung clearance mechanism was overwhelmed and that the results at the massive 250 mg/m³ level are not relevant to the workplace.

Toluene

Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: central nervous system, kidneys, liver, respiratory system, skin. Can be absorbed through the skin in harmful amounts. Recurrent overexposure may result in liver and kidney injury. High airborne levels have produced irregular heart beats in animals and occasional palpitations in humans. Rats exposed to very high airborne levels have exhibited high frequency hearing deficits. The significance of this to man is unknown.

WARNING: This chemical is known to the State of California to cause birth defects or other reproductive harm.

Xylene

Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: bone marrow, cardiovascular system, central nervous system, kidneys, liver, lungs. Recurrent overexposure may result in liver and kidney injury. High exposures may produce irregular heart beats. Canada classifies Xylene as

a developmental toxin as high exposures to xylenes in some animal studies have been reported to cause health effects on the developing fetus/embryo. These effects were often at levels toxic to the adult animal. The significance of these effects to humans is not known. Repeated or prolonged skin contact may cause any of the following: irritation, dryness, cracking of the skin.

SECTION 4 - First aid measures

First Aid Procedures

Inhalation:

If affected by inhalation of vapor or spray mist, move to fresh air. If not breathing, give artificial respiration, preferably mouth-to-mouth. If breathing difficulty persists, or occurs later, consult a physician.

Ingestion:

In the unlikely event of ingestion, DO NOT INDUCE VOMITING. Call a physician immediately and have names of ingredients available.

Skin or Eye Contact:

In case of eye contact, immediately flush with plenty of water for at least 15 minutes; call a physician. In case of skin contact, wash thoroughly with soap and water. If irritation occurs, contact a physician.

SECTION 5 - Fire-fighting measures

Flash Point (Closed Cup): See Section 11 for exact values

Flammable Limits: LFL 0.5% UFL 13.1%

Extinguishing Media:

Universal aqueous film-forming foam, carbon dioxide, dry chemical.

Fire Fighting Procedures:

Full protective equipment, including self-contained breathing apparatus, is recommended. Water from fog nozzles may be used to prevent pressure build-up.

Fire and Explosion Hazards:

For flammable liquids, vapor/air will ignite when an ignition source is present. In other cases, when heated above the flash point, emits flammable vapors which, when mixed with air, can burn or be explosive. Fine mists or sprays may be flammable at temperatures below the flash point.

SECTION 6 - Accidental release measures

Steps to be taken in case material is released or spilled:

Ventilate area. Remove sources of ignition. Prevent skin and eye contact and breathing of vapor. If the material contains, or is mixed with an isocyanate activator/hardener: Wear a positive-pressure, supplied-air respirator (NIOSH approved TC-19C), eye protection, gloves and protective clothing. Pour liquid decontamination solution over the spill and allow to sit at least 10 minutes. Typical decontamination solutions for isocyanate containing materials are: 20% Surfactant (Tergitol TMN10) and 80% Water OR 0 -10% Ammonia, 2-5% Detergent and Water (balance) Pressure can be generated. Do not seal waste containers for 48 hours to allow CO2 to vent. After 48 hours, material may be sealed and disposed of properly. If material does not contain or is not mixed with an isocyanate activator/hardener: Wear a properly fitted air-purifying respirator with organic vapor cartridges (NIOSH approved TC-23C), eye protection, gloves and protective clothing. Confine, remove with inert absorbent, and dispose of properly.

SECTION 7 - Handling and storage

Precautions to be taken in handling and storing:

Observe label precautions. If combustible (flashpoint between 100-200 .F),

keep away from heat, sparks and flame. If flammable (flashpoint less than 100. F), also keep away from static discharges and other sources of ignition. If material is extremely flammable (flashpoint less than 20. F) or flammable, VAPORS MAY IGNITE EXPLOSIVELY OR CAUSE FLASH FIRE, respectively. Vapors may spread long distances. Prevent buildup of vapors. Close container after each use. Ground containers when pouring. Wash thoroughly after handling and before eating or smoking. Do not store above 120 .F. If product is waterbased do not freeze.

Other precautions:

If material is a coating: do not sand, flame cut, braze or weld dry coating without a NIOSH approved respirator or appropriate ventilation, and gloves.

SECTION 8 - Exposure controls / personal protection

Engineering controls and work practices:

Ventilation:

Provide sufficient ventilation in volume and pattern to keep contaminants below applicable exposure limits.

Respiratory protection

Do not breathe vapors or mists. If this product contains isocyanates or is used with an isocyanate activator/hardener, wear a positive-pressure, supplied-air respirator (NIOSH approved TC-19C) while mixing activator/hardener with paint, during application and until all vapors and spray mist are exhausted. If product does not contain or is not mixed with an isocyanate activator/hardener, a properly fitted air-purifying respirator with organic vapor cartridges (NIOSH TC-23C) and particulate filter (NIOSH TC-84A) may be used. Follow respirator manufacturer's directions for respirator use. Do not permit anyone without protection in the painting area. Individuals with history of lung or breathing problems or prior reaction to isocyanates should not use or be exposed to vapor or spray mist if product contains or is mixed with isocyanate activators/hardeners.

Protective equipment

Personal protective equipment should be worn to prevent contact with eyes, skin or clothing.

Skin protection

Neoprene gloves and coveralls are recommended.

Eye protection

Desirable in all industrial situations. Goggles are preferred to prevent eye irritation. If safety glasses are substituted, include splash guard or side shields.

SECTION 9 - Physical and chemical properties

Evaporation rate	Slower than Ether
Solubility in Water	NIL
Vapor Density	Heavier than air
Approx. Boiling Range(°C)	56.1 - 225 °C
Approx. Freezing Range(°C)	-93 - -73 °C
Gallon weight (lbs/gal)	7.97 - 11.85
Specific Gravity	0.96 - 1.42
Percent Volatile by Volume	35.78 - 56.06
Percent Volatile by Weight	26.06 - 48.73
Percent Solid by Volume	43.94 - 64.22
Percent Solid by Weight	51.27 - 73.94

SECTION 10 - Stability and reactivity

Stability:

Stable

Incompatibility (materials to avoid):

None reasonably foreseeable

Hazardous Decomposition Products:

CO, CO₂, smoke, and oxides of any heavy metals that are reported in "Composition, Information on Ingredients" section.

Hazardous Polymerization:

Will not occur.

Sensitivity to Static Discharge:

For flammable materials (flashpoint less than 100 deg F) and combustibles (flashpoint between 100-200 deg F) if heated above the flashpoint, solvent vapors in air may explode if static grounding and bonding is not used during transfer of this product.

Sensitivity to Mechanical Impact:

None known

SECTION 11 - Additional Information**Product Code****Ingredients (Product Specific)**

62-1632™ 2-ethylhexyl acetate(6.0%), Acetone(12.9%), Acrylic polymer-C(23.1%), Calcium carbonate(6.7%), Cristobalite siO₂(4.3%), Diatomaceous earth(1.7%), Ethyl acetate(4.1%), Ethylbenzene(0.3 - 0.8%* @), Hydrous magnesium silicate(7.3%), Kaolin(7.6%), Methyl amyl ketone(6.1%), Quartz-crystalline silica(0.2%), Titanium dioxide(11.3%), Xylene(2.3 - 2.7%* @), Zinc oxide(2.4%*)
GAL WT: 10.99 WT PCT SOLIDS: 66.23 VOL PCT SOLIDS: 46.34
SOLVENT DENSITY: 6.90 VOC LE: 2.9 VOC AP: 2.3
FLASH POINT: 20°F to below 73°F H: 3 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

62-711™ 2-ethylhexyl acetate(6.0%), Acetone(12.9%), Acrylic polymer-C(23.1%), Calcium carbonate(6.6%), Carbon black(0.2%), Cristobalite siO₂(4.3%), Diatomaceous earth(1.7%), Ethyl acetate(4.1%), Ethylbenzene(0.3 - 0.7%* @), Hydrous magnesium silicate(7.2%), Kaolin(7.5%), Methyl amyl ketone(6.1%), Quartz-crystalline silica(0.2%), Red iron oxide light(11.8%), Xylene(2.2 - 2.7%* @), Zinc oxide(2.4%*)
GAL WT: 11.07 WT PCT SOLIDS: 66.30 VOL PCT SOLIDS: 46.08
SOLVENT DENSITY: 6.90 VOC LE: 2.9 VOC AP: 2.3
FLASH POINT: 20°F to below 73°F H: 3 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

62-1640™ 2-ethylhexyl acetate(6.0%), Acetone(12.9%), Acrylic polymer-C(23.0%), Calcium carbonate(8.3%), Carbon black(4.0%), Cristobalite siO₂(5.6%), Diatomaceous earth(2.2%), Ethyl acetate(4.2%), Ethylbenzene(0.3 - 0.7%* @), Hydrous magnesium silicate(9.2%), Kaolin(9.4%), Methyl amyl ketone(6.1%), Quartz-crystalline silica(0.3%), Xylene(2.2 - 2.7%* @), Zinc oxide(2.7%*)
GAL WT: 10.68 WT PCT SOLIDS: 66.21 VOL PCT SOLIDS: 47.87
SOLVENT DENSITY: 6.90 VOC LE: 2.8 VOC AP: 2.2
FLASH POINT: 20°F to below 73°F H: 3 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

62-1060™ 2-ethylhexyl acetate(5.9%), Acetone(12.9%), Acrylic polymer-C(23.2%), Calcium carbonate(6.6%), Cristobalite siO₂(4.2%), Diatomaceous earth(1.7%), Ethyl acetate(4.1%), Ethylbenzene(0.3 - 0.8%* @), Hydrous magnesium silicate(7.2%), Kaolin(7.5%), Methyl amyl ketone(6.1%), Quartz-crystalline silica(0.2%), Titanium dioxide(11.2%), Xylene(2.3 - 2.8%* @), Zinc oxide(2.4%*)
GAL WT: 10.97 WT PCT SOLIDS: 66.11 VOL PCT SOLIDS: 46.28
SOLVENT DENSITY: 6.90 VOC LE: 2.9 VOC AP: 2.3
FLASH POINT: 20°F to below 73°F H: 3 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

62-1072™ 2-ethylhexyl acetate(5.9%), Acetone(12.7%), Acrylic polymer-C(23.3%), Calcium carbonate(6.5%), Carbon black(0.1%), Cristobalite siO₂(4.2%), Diatomaceous earth(1.7%), Ethyl acetate(4.0%), Ethylbenzene(0.3 - 0.8%* @), Hydrous magnesium silicate(7.1%), Kaolin(7.4%), Methyl amyl ketone(6.1%), Quartz-crystalline silica(0.2%), Titanium dioxide(11.1%), Xylene(2.3 - 2.8%* @), Zinc oxide(2.3%*)
GAL WT: 10.94 WT PCT SOLIDS: 65.94 VOL PCT SOLIDS: 46.18
SOLVENT DENSITY: 6.91 VOC LE: 3.0 VOC AP: 2.3
FLASH POINT: 20°F to below 73°F H: 3 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

62-705™ 2-ethylhexyl acetate(6.0%), Acetone(12.9%), Acrylic polymer-C(23.1%), Calcium carbonate(6.6%), Cristobalite siO₂(4.3%), Diatomaceous earth(1.7%), Ethyl acetate(4.1%), Ethylbenzene(0.3 - 0.8%* @), Hydrous magnesium silicate(7.2%), Kaolin(7.5%), Methyl amyl ketone(6.1%), Quartz-crystalline silica(0.2%), Xylene(2.3 - 2.7%* @), Yellow iron oxide(11.8%), Zinc oxide(2.5%*)
GAL WT: 11.00 WT PCT SOLIDS: 66.30 VOL PCT SOLIDS: 46.39
SOLVENT DENSITY: 6.90 VOC LE: 2.9 VOC AP: 2.3
FLASH POINT: 20°F to below 73°F H: 3 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

333-29007™ Acetone(1.4%), Acrylic polymer-C(18.5%), Butyl acetate(1.5%), Ethyl acetate(2.7%), Ethylbenzene(0.2 - 0.4%* @), Ethylene glycol monobutyl ether acetate(4.3%* @), Isoindolinone pigment(1.2%), Methyl amyl ketone(6.6%), Polyester resin(19.1%), Propylene glycol monomethyl ether acetate(12.0%), Red iron oxide light(1.3%), Titanium dioxide(11.0%), Toluene(1.7 - 1.7%* @), Xylene(1.3 - 1.5%* @), Yellow iron oxide(14.7%)
GAL WT: 10.87 WT PCT SOLIDS: 67.95 VOL PCT SOLIDS: 53.44
SOLVENT DENSITY: 7.46 VOC LE: 3.4 VOC AP: 3.3
FLASH POINT: 20°F to below 73°F H: 1 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

333-30693™ Acetone(2.2%), Acrylic polymer-B(18.2%), Aromatic hydrocarbon(1.5%), C.i. pigment red 254(3.4%), Ethyl acetate(4.3%), Ethylbenzene(0.3 - 0.7%* @), Ethylene glycol monobutyl ether acetate(3.1%* @), Methyl amyl ketone(6.5%), Monoazo pigment(8.9%), Polyester resin(31.3%), Propylene glycol monomethyl ether acetate(12.4%), Titanium dioxide(1.3%), Xylene(2.2 - 2.7%* @)
GAL WT: 9.12 WT PCT SOLIDS: 64.28 VOL PCT SOLIDS: 56.29
SOLVENT DENSITY: 7.44 VOC LE: 3.2 VOC AP: 3.1
FLASH POINT: 20°F to below 73°F H: 1 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES

333-67632™ Acetone(1.2%), Acrylic polymer-B(15.0%), Aluminum hydrate(1.2%), Amorphous silica(2.0%), Ethyl acetate(2.8%), Ethylbenzene(0.2 - 0.5%* @), Ethylene glycol monobutyl ether acetate(6.4%* @), Methyl amyl ketone(6.6%), Polyester resin(20.0%), Propylene glycol monomethyl ether acetate(8.9%), Titanium dioxide(31.9%), Toluene(1.1 - 1.1%* @), Xylene(1.4 - 1.7%* @)
GAL WT: 11.54 WT PCT SOLIDS: 70.98 VOL PCT SOLIDS: 55.14
SOLVENT DENSITY: 7.44 VOC LE: 3.3 VOC AP: 3.2
FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

333-67633™ Acrylic polymer-C(15.4%), Aluminum hydrate(1.0%), Amorphous silica(1.6%), Carbon black(0.1%), Ethyl acetate(3.3%), Ethylbenzene(0.2 - 0.5%* @), Ethylene glycol monobutyl ether acetate(7.0%* @), Methyl amyl ketone(14.6%), Polyester resin(23.8%), Titanium dioxide(26.3%), Toluene(2.5 - 2.5%* @), Xylene(1.5 - 1.8%* @)
GAL WT: 10.87 WT PCT SOLIDS: 70.61 VOL PCT SOLIDS: 55.31
SOLVENT DENSITY: 7.13 VOC LE: 3.2 VOC AP: 3.2
FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

333-67635™ Acrylic polymer-C(13.8%), Aluminum hydrate(1.3%), Amorphous silica(2.1%), Ethyl acetate(2.4%), Ethylbenzene(0.2 - 0.4%* @), Ethylene glycol monobutyl ether acetate(7.5%* @), Methyl amyl ketone(5.4%), Polyester resin(17.5%), Propylene glycol monomethyl ether acetate(9.7%), Titanium dioxide(34.5%), Toluene(2.9 - 2.9%* @), Xylene(1.2 - 1.5%* @)
GAL WT: 11.85 WT PCT SOLIDS: 70.31 VOL PCT SOLIDS: 53.46
SOLVENT DENSITY: 7.53 VOC LE: 3.5 VOC AP: 3.5
FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

333-67637™ Acetone(1.3%), Acrylic polymer-B(14.9%), Aluminum hydrate(1.2%), Amorphous silica(2.0%), Ethyl acetate(2.8%), Ethylbenzene(0.2 - 0.5%* @), Ethylene glycol monobutyl ether acetate(5.3%* @), Methyl amyl ketone(7.3%), Polyester resin(20.1%), Propylene glycol monomethyl ether acetate(8.9%), Titanium dioxide(32.0%), Toluene(1.1 - 1.1%* @), Xylene(1.4 - 1.7%* @)
GAL WT: 11.54 WT PCT SOLIDS: 71.18 VOL PCT SOLIDS: 55.26
SOLVENT DENSITY: 7.41 VOC LE: 3.3 VOC AP: 3.2

FLASH POINT: 20°F to below 73°F **H: 2 F: 3 R: 0** **OSHA STORAGE:** IB
TSCA STATUS: In Compliance **PHOTO-CHEMICALLY REACTIVE:** NO

333-67640™ Acetone(1.8%), Acrylic polymer-C(20.1%), Carbon black(2.0%), Ethyl acetate(5.1%), Ethylbenzene(0.3 - 0.7%* @), Ethylene glycol monobutyl ether acetate(6.0%* @), Methyl amyl ketone(22.1%), Polyester resin(37.4%), Toluene(1.6 - 1.7%* @), Xylene(2.2 - 2.6%* @)
GAL WT: 8.49 WT PCT SOLIDS: 60.36 VOL PCT SOLIDS: 52.24
SOLVENT DENSITY: 7.04 VOC LE: 3.3 VOC AP: 3.2
FLASH POINT: 20°F to below 73°F **H: 2 F: 3 R: 0** **OSHA STORAGE:** IB
TSCA STATUS: In Compliance **PHOTO-CHEMICALLY REACTIVE:** NO

333M24861™ 2-ethylhexyl acetate(1.3%), Acrylic polymer-B(16.0%), Aluminum hydrate(1.2%), Amorphous silica(1.8%), Ethyl acetate(10.6%), Ethylbenzene(0.1 - 0.2%* @), Ethylene glycol monobutyl ether acetate(9.6%* @), Methyl amyl ketone(11.2%), Methyl ethyl ketone(1.4%), Organoclay(1.2%), Polyester resin(14.5%), Titanium dioxide(29.9%)
GAL WT: 10.99 WT PCT SOLIDS: 65.23 VOL PCT SOLIDS: 47.57
SOLVENT DENSITY: 7.26 VOC LE: 3.8 VOC AP: 3.8
FLASH POINT: 20°F to below 73°F **H: 2 F: 3 R: 0** **OSHA STORAGE:** IB
TSCA STATUS: In Compliance **PHOTO-CHEMICALLY REACTIVE:** NO

333M24926™ Acetone(2.1%), Acrylic polymer-A(8.9%), Amorphous silica-fumed(2.9%), Butyl acetate(10.1%), Carbon black(2.0%), Ethyl acetate(14.6%), Ethylbenzene(0.6 - 1.4%* @), Ethylene glycol monobutyl ether acetate(11.8%* @), Methyl ethyl ketone(1.5%), Polyester resin(38.8%), Xylene(4.2 - 5.0%* @)
GAL WT: 8.66 WT PCT SOLIDS: 53.33 VOL PCT SOLIDS: 45.64
SOLVENT DENSITY: 7.40 VOC LE: 4.0 VOC AP: 3.9
FLASH POINT: 20°F to below 73°F **H: 2 F: 3 R: 0** **OSHA STORAGE:** IB
TSCA STATUS: In Compliance **PHOTO-CHEMICALLY REACTIVE:** YES

333M27263™ Acrylic polymer-B(23.1%), Aromatic hydrocarbon(1.3%), Butyl acetate(13.0%), C.i. pigment red 254(7.5%), Ethyl acetate(7.7%), Ethylbenzene(0.1 - 0.2%* @), Ethylene glycol monobutyl ether acetate(2.3%* @), Methyl amyl ketone(6.7%), Organoclay(1.7%), Polyester resin(21.9%), Propylene glycol monomethyl ether acetate(10.5%), Titanium dioxide(1.1%)
GAL WT: 8.79 WT PCT SOLIDS: 56.36 VOL PCT SOLIDS: 48.50
SOLVENT DENSITY: 7.44 VOC LE: 3.8 VOC AP: 3.8
FLASH POINT: 20°F to below 73°F **H: 2 F: 3 R: 0** **OSHA STORAGE:** IB
TSCA STATUS: In Compliance **PHOTO-CHEMICALLY REACTIVE:** NO

333M28042™ Acrylic polymer-B(26.8%), Aromatic hydrocarbon(1.2%), Butyl acetate(13.1%), Ethyl acetate(2.3%), Ethylbenzene(0.1 - 0.2%* @), Methyl amyl ketone(7.3%), Organoclay(1.7%), Phthalocyanine blue pigment(3.7%), Polyester resin(13.3%), Propylene glycol monomethyl ether acetate(14.4%), Titanium dioxide(10.4%)
GAL WT: 9.39 WT PCT SOLIDS: 58.77 VOL PCT SOLIDS: 48.09
SOLVENT DENSITY: 7.68 VOC LE: 3.9 VOC AP: 3.9
FLASH POINT: 20°F to below 73°F **H: 2 F: 3 R: 0** **OSHA STORAGE:** IB
TSCA STATUS: In Compliance **PHOTO-CHEMICALLY REACTIVE:** NO

333M30469™ 2-ethylhexyl acetate(1.3%), Acrylic polymer-B(16.1%), Aluminum hydrate(1.2%), Amorphous silica(1.8%), Ethyl acetate(10.5%), Ethylbenzene(0.1 - 0.2%* @), Ethylene glycol monobutyl ether acetate(9.6%* @), Methyl amyl ketone(11.2%), Methyl ethyl ketone(1.4%), Organoclay(1.2%), Polyester resin(14.5%), Titanium dioxide(29.9%)
GAL WT: 10.99 WT PCT SOLIDS: 65.20 VOL PCT SOLIDS: 47.56
SOLVENT DENSITY: 7.26 VOC LE: 3.8 VOC AP: 3.8
FLASH POINT: 20°F to below 73°F **H: 2 F: 3 R: 0** **OSHA STORAGE:** IB
TSCA STATUS: In Compliance **PHOTO-CHEMICALLY REACTIVE:** NO

333M30470™ Acrylic polymer-B(24.0%), Azo yellow pigment(4.6%), Butyl acetate(8.7%), Carbon black(0.2%), Ethyl acetate(4.9%), Ethylbenzene(0.1 - 0.3%* @), Ethylene glycol monobutyl ether acetate(1.5%* @), Methyl amyl ketone(18.3%), Phthalocyanine green pigment(3.7%), Polyester resin(20.6%), Propylene glycol monomethyl ether acetate(7.1%), Titanium dioxide(1.3%)
GAL WT: 8.71 WT PCT SOLIDS: 56.15 VOL PCT SOLIDS: 47.05
SOLVENT DENSITY: 7.23 VOC LE: 3.8 VOC AP: 3.8

FLASH POINT: 20°F to below 73°F **H: 2 F: 3 R: 0** **OSHA STORAGE:** IB
TSCA STATUS: In Compliance **PHOTO-CHEMICALLY REACTIVE:** NO

333M67633™ 2-ethylhexyl acetate(1.2%), Acrylic polymer-B(17.3%), Aluminum hydrate(1.1%), Amorphous silica(1.7%), Butyl acetate(1.7%), Carbon black(0.4%), Ethyl acetate(9.8%), Ethylbenzene(0.1 - 0.3%* @), Ethylene glycol monobutyl ether acetate(8.7%* @), Methyl amyl ketone(11.0%), Methyl ethyl ketone(1.3%), Organoclay(1.1%), Polyester resin(14.7%), Titanium dioxide(27.5%)
GAL WT: 10.77 WT PCT SOLIDS: 64.72 VOL PCT SOLIDS: 47.83
SOLVENT DENSITY: 7.26 VOC LE: 3.8 VOC AP: 3.8
FLASH POINT: 20°F to below 73°F **H: 2 F: 3 R: 0** **OSHA STORAGE:** IB
TSCA STATUS: In Compliance **PHOTO-CHEMICALLY REACTIVE:** NO

333M67641™ 2-ethylhexyl acetate(1.3%), Acrylic polymer-B(16.3%), Aluminum hydrate(1.1%), Amorphous silica(1.8%), Ethyl acetate(10.0%), Ethylbenzene(0.1 - 0.2%* @), Ethylene glycol monobutyl ether acetate(9.5%* @), Methyl amyl ketone(11.2%), Methyl ethyl ketone(1.4%), Organoclay(1.1%), Polyester resin(14.4%), Titanium dioxide(29.6%)
GAL WT: 11.02 WT PCT SOLIDS: 65.47 VOL PCT SOLIDS: 47.83
SOLVENT DENSITY: 7.26 VOC LE: 3.8 VOC AP: 3.8
FLASH POINT: 20°F to below 73°F **H: 2 F: 3 R: 0** **OSHA STORAGE:** IB
TSCA STATUS: In Compliance **PHOTO-CHEMICALLY REACTIVE:** NO

333M68288™ Acrylic polymer-B(22.0%), Aromatic hydrocarbon(1.1 - 1.1%), Butyl acetate(13.8%), Carbon black(0.3%), Ethyl acetate(6.3%), Ethylbenzene(0.1 - 0.3%* @), Ethylene glycol monobutyl ether acetate(1.6%* @), Methyl amyl ketone(5.7%), Organoclay(1.4%), Polyester resin(15.6%), Propylene glycol monomethyl ether acetate(6.1%), Red iron oxide light(1.3%), Titanium dioxide(16.0%), Yellow iron oxide(3.1%)
GAL WT: 10.07 WT PCT SOLIDS: 62.21 VOL PCT SOLIDS: 48.42
SOLVENT DENSITY: 7.37 VOC LE: 3.8 VOC AP: 3.8
FLASH POINT: 20°F to below 73°F **H: 2 F: 3 R: 0** **OSHA STORAGE:** IB
TSCA STATUS: In Compliance **PHOTO-CHEMICALLY REACTIVE:** NO

333MAG009™ 1,2,4-trimethyl benzene(1.3%*), Acrylic polymer-C(17.4%), Aluminum(8.8%*), Aromatic hydrocarbon(1.6%), Butyl acetate(6.7%), Ethyl acetate(5.1%), Ethylbenzene(0.3 - 0.7%* @), Ethylene glycol monobutyl ether acetate(5.9%* @), Methyl amyl ketone(6.2%), Polyester resin(37.4%), Stoddard solvent(1.8%), Toluene(2.6 - 2.7%* @), Xylene(2.3 - 2.8%* @)
GAL WT: 9.10 WT PCT SOLIDS: 65.43 VOL PCT SOLIDS: 57.29
SOLVENT DENSITY: 7.34 VOC LE: 3.1 VOC AP: 3.1
FLASH POINT: 20°F to below 73°F **H: 2 F: 3 R: 1** **OSHA STORAGE:** IB
TSCA STATUS: In Compliance **PHOTO-CHEMICALLY REACTIVE:** YES

333P24861™ 2,4-pentanedione(1.8%), 2-ethylhexyl acetate(1.3%), Acrylic polymer-B(16.0%), Aluminum hydrate(1.2%), Amorphous silica(1.8%), Ethyl acetate(9.7%), Ethylbenzene(0.1 - 0.2%* @), Ethylene glycol monobutyl ether acetate(8.8%* @), Methyl amyl ketone(11.2%), Methyl ethyl ketone(1.1%), Organoclay(1.2%), Polyester resin(14.5%), Titanium dioxide(29.9%)
GAL WT: 11.02 WT PCT SOLIDS: 65.31 VOL PCT SOLIDS: 47.76
SOLVENT DENSITY: 7.29 VOC LE: 3.8 VOC AP: 3.8
FLASH POINT: 20°F to below 73°F **H: 2 F: 3 R: 0** **OSHA STORAGE:** IB
TSCA STATUS: In Compliance **PHOTO-CHEMICALLY REACTIVE:** NO

333P24926™ 2,4-pentanedione(3.7%), Acetone(2.1%), Acrylic polymer-A(8.9%), Amorphous silica-fumed(2.9%), Butyl acetate(10.1%), Carbon black(2.0%), Ethyl acetate(12.1%), Ethylbenzene(0.5 - 1.3%* @), Ethylene glycol monobutyl ether acetate(11.4%* @), Polyester resin(38.9%), Xylene(3.8 - 4.6%* @)
GAL WT: 8.70 WT PCT SOLIDS: 53.51 VOL PCT SOLIDS: 46.01
SOLVENT DENSITY: 7.45 VOC LE: 4.0 VOC AP: 3.9
FLASH POINT: 20°F to below 73°F **H: 2 F: 3 R: 0** **OSHA STORAGE:** IB
TSCA STATUS: In Compliance **PHOTO-CHEMICALLY REACTIVE:** YES

333-23662™ Acrylic polymer-C(18.3%), Ethyl acetate(4.3%), Ethylbenzene(0.3 - 0.7%* @), Ethylene glycol monobutyl ether acetate(9.2%* @), Isoindolinone pigment(5.0%), Methyl amyl ketone(6.9%), Monoazo pigment(5.3%), Polyester resin(31.0%), Propylene glycol monomethyl ether acetate(12.5%), Titanium dioxide(2.0%), Xylene(2.0 - 2.4%* @)

GAL WT: 9.26 WT PCT SOLIDS: 63.72 VOL PCT SOLIDS: 55.71
SOLVENT DENSITY: 7.55 VOC LE: 3.4 VOC AP: 3.4
FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 1 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

333-23663™ Acetone(1.8%), Acrylic polymer-C(18.0%), Azo yellow pigment(7.6%), Ethyl acetate(4.2%), Ethylbenzene(0.3 - 0.6%* @), Ethylene glycol monobutyl ether acetate(6.8%* @), Methyl amyl ketone(6.6%), Polyester resin(30.0%), Propylene glycol monomethyl ether acetate(13.1%), Titanium dioxide(5.9%), Xylene(1.9 - 2.3%* @), Yellow iron oxide(1.1%)
GAL WT: 9.40 WT PCT SOLIDS: 63.99 VOL PCT SOLIDS: 55.04
SOLVENT DENSITY: 7.50 VOC LE: 3.3 VOC AP: 3.2
FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

333-23664™ Acetone(2.2%), Acrylic polymer-B(18.1%), Ethyl acetate(4.1%), Ethylbenzene(0.3 - 0.6%* @), Ethylene glycol monobutyl ether acetate(6.3%* @), Methyl amyl ketone(6.3%), Monoazo pigment(7.9%), Polyester resin(29.2%), Propylene glycol monomethyl ether acetate(14.0%), Quinacridone pigment(5.5%), Xylene(2.0 - 2.3%* @)
GAL WT: 9.08 WT PCT SOLIDS: 62.62 VOL PCT SOLIDS: 54.89
SOLVENT DENSITY: 7.50 VOC LE: 3.3 VOC AP: 3.2
FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

333-23665™ Acrylic polymer-C(20.7%), Butyl acetate(1.8%), Ethyl acetate(4.2%), Ethylbenzene(0.3 - 0.6%* @), Ethylene glycol monobutyl ether acetate(8.7%* @), Methyl amyl ketone(7.3%), Phthalocyanine blue pigment(1.2%), Polyester resin(30.1%), Propylene glycol monomethyl ether acetate(6.6%), Titanium dioxide(11.2%), Toluene(2.9 - 2.9%* @), Xylene(1.9 - 2.3%* @)
GAL WT: 9.55 WT PCT SOLIDS: 65.41 VOL PCT SOLIDS: 55.67
SOLVENT DENSITY: 7.42 VOC LE: 3.3 VOC AP: 3.3
FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

333-23666™ Acrylic polymer-C(17.6%), Ethyl acetate(4.0%), Ethylbenzene(0.3 - 0.6%* @), Ethylene glycol monobutyl ether acetate(9.3%* @), Methyl amyl ketone(9.0%), Polyester resin(28.6%), Propylene glycol monomethyl ether acetate(7.9%), Titanium dioxide(14.9%), Xylene(1.9 - 2.3%* @), Yellow iron oxide(1.7%)
GAL WT: 9.99 WT PCT SOLIDS: 66.23 VOL PCT SOLIDS: 54.81
SOLVENT DENSITY: 7.43 VOC LE: 3.4 VOC AP: 3.4
FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

333-27263™ Acrylic polymer-B(18.4%), C.i. pigment red 254(8.6%), Ethyl acetate(4.8%), Ethylbenzene(0.3 - 0.7%* @), Ethylene glycol monobutyl ether acetate(8.6%* @), Methyl amyl ketone(7.0%), Polyester resin(34.7%), Propylene glycol monomethyl ether acetate(12.1%), Titanium dioxide(1.3%), Xylene(2.2 - 2.6%* @)
GAL WT: 9.08 WT PCT SOLIDS: 64.14 VOL PCT SOLIDS: 56.95
SOLVENT DENSITY: 7.53 VOC LE: 3.3 VOC AP: 3.3
FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

333-27468™ Acetone(1.6%), Acrylic polymer-C(11.0%), Aluminum hydrate(1.3%), Amorphous silica(2.1%), Ethyl acetate(2.8%), Ethylbenzene(0.2 - 0.5%* @), Ethylene glycol monobutyl ether acetate(7.9%* @), Methyl amyl ketone(5.6%), Polyester resin(20.1%), Propylene glycol monomethyl ether acetate(9.4%), Titanium dioxide(33.8%), Toluene(1.5 - 1.5%* @), Xylene(1.4 - 1.7%* @)
GAL WT: 11.72 WT PCT SOLIDS: 69.27 VOL PCT SOLIDS: 52.02
SOLVENT DENSITY: 7.47 VOC LE: 3.5 VOC AP: 3.4
FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

333-28981™ Acetone(3.5%), Acrylic polymer-B(18.3%), C.i. pigment red 254(3.7%), Ethyl acetate(4.5%), Ethylbenzene(0.3 - 0.7%* @), Ethylene glycol monobutyl ether acetate(5.4%* @), Methyl amyl ketone(6.4%), Polyester resin(32.2%), Propylene glycol monomethyl ether acetate(13.6%), Quinacridone pigment(6.4%), Xylene(2.3 - 2.7%* @)

GAL WT: 8.88 WT PCT SOLIDS: 61.78 VOL PCT SOLIDS: 54.49
SOLVENT DENSITY: 7.44 VOC LE: 3.2 VOC AP: 3.1
FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

333-28982™ Acetone(1.2%), Acrylic polymer-C(19.8%), Butyl acetate(1.9%), Ethyl acetate(2.6%), Ethylbenzene(0.2 - 0.4%* @), Ethylene glycol monobutyl ether acetate(3.3%* @), Methyl amyl ketone(6.7%), Polyester resin(18.9%), Propylene glycol monomethyl ether acetate(11.6%), Titanium dioxide(8.5%), Toluene(1.7 - 1.8%* @), Xylene(1.3 - 1.5%* @), Yellow iron oxide(19.6%)
GAL WT: 10.89 WT PCT SOLIDS: 68.56 VOL PCT SOLIDS: 54.14
SOLVENT DENSITY: 7.45 VOC LE: 3.4 VOC AP: 3.3
FLASH POINT: 20°F to below 73°F H: 1 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

333-28984™ Acetone(1.6%), Acrylic polymer-B(19.3%), Azo yellow pigment(4.1%), Butyl acetate(1.2%), Ethyl acetate(3.9%), Ethylbenzene(0.2 - 0.6%* @), Ethylene glycol monobutyl ether acetate(3.4%* @), Methyl amyl ketone(12.2%), Phthalocyanine green pigment(1.9%), Polyester resin(28.3%), Propylene glycol monomethyl ether acetate(10.0%), Titanium dioxide(1.1%), Toluene(1.0 - 1.0%* @), Xylene(1.8 - 2.1%* @), Yellow iron oxide(7.9%)
GAL WT: 9.37 WT PCT SOLIDS: 63.60 VOL PCT SOLIDS: 53.42
SOLVENT DENSITY: 7.32 VOC LE: 3.3 VOC AP: 3.3
FLASH POINT: 20°F to below 73°F H: 1 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

333-28985™ Acrylic polymer-B(23.1%), Butyl acetate(3.5%), Ethyl acetate(4.3%), Ethylbenzene(0.3 - 0.7%* @), Ethylene glycol monobutyl ether acetate(3.2%* @), Methyl amyl ketone(10.7%), Phthalocyanine blue pigment(2.8%), Polyester resin(31.3%), Propylene glycol monomethyl ether acetate(10.5%), Titanium dioxide(2.7%), Xylene(2.0 - 2.4%* @)
GAL WT: 8.91 WT PCT SOLIDS: 62.70 VOL PCT SOLIDS: 54.90
SOLVENT DENSITY: 7.37 VOC LE: 3.3 VOC AP: 3.3
FLASH POINT: 20°F to below 73°F H: 1 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES

333-28993™ Acetone(1.5%), Acrylic polymer-C(17.2%), Amorphous silica(1.2%), Butyl acetate(1.6%), Carbon black(0.1%), Ethyl acetate(3.8%), Ethylbenzene(0.3 - 0.7%* @), Ethylene glycol monobutyl ether acetate(8.9%* @), Methyl amyl ketone(6.7%), Polyester resin(27.3%), Propylene glycol monomethyl ether acetate(6.1%), Titanium dioxide(18.7%), Toluene(1.7 - 1.7%* @), Xylene(2.0 - 2.4%* @)
GAL WT: 10.15 WT PCT SOLIDS: 66.87 VOL PCT SOLIDS: 54.71
SOLVENT DENSITY: 7.39 VOC LE: 3.3 VOC AP: 3.2
FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

333-29001™ Acetone(2.2%), Acrylic polymer-B(15.2%), Ethyl acetate(3.1%), Ethylbenzene(0.2 - 0.5%* @), Ethylene glycol monobutyl ether acetate(5.4%* @), Methyl amyl ketone(5.4%), Polyester resin(22.3%), Propylene glycol monomethyl ether acetate(11.5%), Titanium dioxide(12.1%), Xylene(1.5 - 1.7%* @), Yellow iron oxide(16.8%)
GAL WT: 11.05 WT PCT SOLIDS: 68.90 VOL PCT SOLIDS: 54.17
SOLVENT DENSITY: 7.47 VOC LE: 3.3 VOC AP: 3.2
FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

333-29002™ Acetone(1.0%), Acrylic polymer-C(20.9%), Ethyl acetate(4.3%), Ethylbenzene(0.3 - 0.7%* @), Ethylene glycol monobutyl ether acetate(7.1%* @), Methyl amyl ketone(8.6%), Phthalocyanine blue pigment(2.3%), Polyester resin(31.3%), Propylene glycol monomethyl ether acetate(8.9%), Titanium dioxide(7.0%), Toluene(2.6 - 2.6%* @), Xylene(2.0 - 2.4%* @)
GAL WT: 9.25 WT PCT SOLIDS: 63.99 VOL PCT SOLIDS: 55.12
SOLVENT DENSITY: 7.40 VOC LE: 3.3 VOC AP: 3.2
FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

333-29006™ Acetone(1.8%), Acrylic polymer-B(19.2%), Butyl acetate(1.7%), Ethyl acetate(3.0%), Ethylbenzene(0.2 - 0.5%* @), Ethylene glycol monobutyl ether acetate(4.1%* @), Isoindolinone pigment(2.7%),

Methyl amyl ketone(6.4%), Polyester resin(21.6%), Propylene glycol monomethyl ether acetate(12.1%), Titanium dioxide(11.9%), Xylene(1.4 - 1.7%* @), Yellow iron oxide(10.0%)

GAL WT: 10.54 WT PCT SOLIDS: 67.99 VOL PCT SOLIDS: 54.87

SOLVENT DENSITY: 7.46 VOC LE: 3.3 VOC AP: 3.2

**FLASH POINT: 20°F to below 73°F H: 1 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

334M67640™ 2-ethylhexyl acetate(1.2%), Acetone(7.2%), Acrylic polymer-D(28.4%), Amorphous silica(11.3%), Amorphous silica - silica base(4.5%), Butyl acetate(11.4%), Carbon black(1.2%), Ethyl acetate(4.8%), Ethylbenzene(0.3 - 0.7%* @), Methyl amyl ketone(12.1%), Polyester resin(9.9%), Toluene(1.6 - 1.7%* @), Xylene(2.2 - 2.7%* @)

GAL WT: 8.83 WT PCT SOLIDS: 57.32 VOL PCT SOLIDS: 46.44

SOLVENT DENSITY: 7.04 VOC LE: 3.5 VOC AP: 3.1

**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

334M27264™ Acetone(6.0%), Acrylic polymer-D(24.2%), Amorphous silica(8.1%), Amorphous silica - silica base(1.6%), Azo yellow pigment(3.0%), Butyl acetate(3.9%), Carbon black(0.1%), Ethyl acetate(1.0%), Ethylbenzene(0.1 - 0.2%* @), Methyl amyl ketone(10.3%), Polyester resin(4.0%), Propylene glycol monomethyl ether acetate(10.2%), Red iron oxide light(1.2%), Titanium dioxide(20.3%), Toluene(1.6 - 1.6%* @)

GAL WT: 10.55 WT PCT SOLIDS: 64.62 VOL PCT SOLIDS: 48.22

SOLVENT DENSITY: 7.20 VOC LE: 3.4 VOC AP: 3.1

**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

334M12134™ Acetone(7.6%), Acrylic polymer-D(29.9%), Amorphous silica(9.3%), Amorphous silica - silica base(2.0%), Butyl acetate(8.3%), Carbon black(1.5%), Ethyl acetate(1.2%), Ethylbenzene(0.3 - 0.8%* @), Methyl amyl ketone(11.1%), Polyester resin(4.4%), Propylene glycol monomethyl ether acetate(3.6%), Titanium dioxide(9.5%), Toluene(2.6 - 2.7%* @), Xylene(2.4 - 2.9%* @), Yellow iron oxide(1.8%)

GAL WT: 9.54 WT PCT SOLIDS: 60.82 VOL PCT SOLIDS: 47.10

SOLVENT DENSITY: 7.06 VOC LE: 3.4 VOC AP: 3.0

**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

334M27260™ Acetone(5.6%), Acrylic polymer-D(22.1%), Aluminum hydrate(1.1%), Amorphous silica(8.2%), Amorphous silica - silica base(1.5%), Butyl acetate(2.6%), Ethyl acetate(1.2%), Ethylbenzene(0.1 - 0.2%* @), Methyl amyl ketone(9.7%), Polyester resin(4.5%), Propylene glycol monomethyl ether acetate(8.7%), Titanium dioxide(28.1%), Toluene(1.6 - 1.6%* @), Yellow iron oxide(1.9%)

GAL WT: 11.40 WT PCT SOLIDS: 68.82 VOL PCT SOLIDS: 50.45

SOLVENT DENSITY: 7.17 VOC LE: 3.2 VOC AP: 2.9

**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

610P™ 1,2,4-trimethyl benzene(4.6 - 4.6%*), 1,3,5-trimethyl benzene(1.0 - 1.0%),

2-(2h-benzotriazol-2-yl)-4,6-bis(1-methyl-1-phenylethyl)phenol(1.2%), Acrylic polymer-D(50.1%), Aromatic hydrocarbon(7.3 - 7.3%), Butyl acetate(7.3%), Ethylbenzene(0.6 - 1.6%* @), Ethylene glycol monobutyl ether acetate(4.6%* @), Methyl ethyl ketone(13.9%), Xylene(4.9 - 5.8%* @)

GAL WT: 8.09 WT PCT SOLIDS: 52.85 VOL PCT SOLIDS: 46.64

SOLVENT DENSITY: 7.11 VOC LE: 3.8 VOC AP: 3.8

**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES**

611P™ Acrylic polymer-D(50.2%), Butanedioic acid, dimethyl ester(1.1%), Butyl acetate(4.3%), Dimethyl glutarate(3.3%), Ethylbenzene(0.2 - 0.4%* @), Ethylene glycol monobutyl ether acetate(2.5%* @), Methyl amyl ketone(24.2%), Methyl ethyl ketone(2.9%), Substituted benzotriazole(1.3%), Toluene(4.8 - 4.8%* @), Xylene(1.2 - 1.4%* @)

GAL WT: 8.13 WT PCT SOLIDS: 53.04 VOL PCT SOLIDS: 46.58

SOLVENT DENSITY: 7.15 VOC LE: 3.8 VOC AP: 3.8

**FLASH POINT: 20°F to below 73°F H: 1 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

613P™ Acetone(14.3%), Acrylic polymer-D(35.5%), Amorphous silica(16.3%), Amorphous silica - silica base(4.0%), Butyl acetate(3.0%), Ethylbenzene(0.1 - 0.3%* @), Methyl amyl ketone(17.8%), Toluene(3.7 - 3.7%* @)

GAL WT: 8.78 WT PCT SOLIDS: 57.92 VOL PCT SOLIDS: 45.82

SOLVENT DENSITY: 6.81 VOC LE: 3.0 VOC AP: 2.4

**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO**

633-87001™ Acrylic polymer-E(17.3%), Aluminum hydrate(1.1%), Amorphous silica(1.7%), Aromatic hydrocarbon(1.6%), Butyl acetate(15.9%), Ethyl acetate(2.3%), Ethylbenzene(0.1 - 0.2%* @), Ethylene glycol monobutyl ether acetate(2.5%* @), Methyl amyl ketone(4.0%), Organoclay(2.1%), Polyester resin(12.7%), Propylene glycol monomethyl ether acetate(7.7%), Titanium dioxide(27.6%)

GAL WT: 10.83 WT PCT SOLIDS: 63.65 VOL PCT SOLIDS: 47.10

SOLVENT DENSITY: 7.43 VOC LE: 3.9 VOC AP: 3.9

**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES**

633-67640™ 1,2,4-trimethyl benzene(1.0%*), 2,4-pentanedione(1.6%), Acrylic polymer-B(28.1%), Aromatic hydrocarbon(1.6%), Butyl acetate(16.7%), Carbon black(1.0%), Ethyl acetate(4.1%), Ethylbenzene(0.1 - 0.3%* @), Ethylene glycol monobutyl ether acetate(2.9%* @), Methyl amyl ketone(14.3%), Organoclay(2.2%), Polyester resin(22.6%)

GAL WT: 8.42 WT PCT SOLIDS: 55.05 VOL PCT SOLIDS: 47.44

SOLVENT DENSITY: 7.20 VOC LE: 3.8 VOC AP: 3.8

**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES**

633-67637™ 1,2,4-trimethyl benzene(1.0%*), 2,4-pentanedione(1.6%), Acrylic polymer-E(17.2%), Aluminum hydrate(1.0%), Amorphous silica(1.6%), Aromatic hydrocarbon(1.6%), Butyl acetate(16.4%), Ethyl acetate(2.8%), Ethylbenzene(0.1 - 0.2%* @), Ethylene glycol monobutyl ether acetate(1.1%* @), Methyl amyl ketone(3.7%), Organoclay(2.2%), Polyester resin(12.9%), Propylene glycol monomethyl ether acetate(7.5%), Titanium dioxide(26.8%)

GAL WT: 10.74 WT PCT SOLIDS: 62.89 VOL PCT SOLIDS: 46.52

SOLVENT DENSITY: 7.45 VOC LE: 4.0 VOC AP: 4.0

**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES**

633-67635™ 1,2,4-trimethyl benzene(1.0%*), 2,4-pentanedione(1.6%), Acrylic polymer-E(17.3%), Aluminum hydrate(1.0%), Amorphous silica(1.6%), Aromatic hydrocarbon(1.6%), Butyl acetate(16.2%), Ethyl acetate(1.9%), Ethylbenzene(0.1 - 0.2%* @), Ethylene glycol monobutyl ether acetate(1.6%* @), Methyl amyl ketone(3.8%), Organoclay(2.2%), Polyester resin(12.7%), Propylene glycol monomethyl ether acetate(7.8%), Titanium dioxide(26.6%)

GAL WT: 10.81 WT PCT SOLIDS: 63.24 VOL PCT SOLIDS: 46.79

SOLVENT DENSITY: 7.45 VOC LE: 4.0 VOC AP: 4.0

**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES**

633-67633™ 2,4-pentanedione(1.6%), Acrylic polymer-E(18.5%), Amorphous silica(1.4%), Aromatic hydrocarbon(1.5%), Butyl acetate(16.9%), Carbon black(0.2%), Ethyl acetate(3.0%), Ethylbenzene(0.1 - 0.3%* @), Ethylene glycol monobutyl ether acetate(1.5%* @), Methyl amyl ketone(4.3%), Organoclay(2.1%), Polyester resin(14.5%), Propylene glycol monomethyl ether acetate(6.5%), Titanium dioxide(22.9%)

GAL WT: 10.35 WT PCT SOLIDS: 61.83 VOL PCT SOLIDS: 46.85

SOLVENT DENSITY: 7.42 VOC LE: 4.0 VOC AP: 3.9

**FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES**

633-67632™ 2,4-pentanedione(1.6%), 2-ethylhexyl acetate(1.2%), Acrylic polymer-B(18.6%), Aluminum hydrate(1.1%), Amorphous silica(1.7%), Butyl acetate(10.1%), Ethyl acetate(6.4%), Ethylbenzene(0.1 - 0.2%* @), Methyl amyl ketone(5.3%), Organoclay(1.4%), Polyester resin(13.4%), Propylene glycol monomethyl ether acetate(7.7%), Titanium dioxide(27.6%)

GAL WT: 10.86 WT PCT SOLIDS: 64.92 VOL PCT SOLIDS: 48.77

SOLVENT DENSITY: 7.44 VOC LE: 3.8 VOC AP: 3.8
FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

633-28066™ Acrylic polymer-B(26.5%), Barium sulfate(2.8%), Butyl acetate(19.2%), Carbon black(2.8%), Ethyl acetate(3.2%), Ethylbenzene(0.4 - 0.9%* @), Ethylene glycol monobutyl ether acetate(7.7%* @), Methyl amyl ketone(5.3%), Organoclay(1.3%), Polyester resin(21.7%), Xylene(2.9 - 3.4%* @)

GAL WT: 8.78 WT PCT SOLIDS: 57.19 VOL PCT SOLIDS: 48.87
SOLVENT DENSITY: 7.33 VOC LE: 3.8 VOC AP: 3.8
FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES

633-23667™ 2,4-pentanedione(1.7%), 2-methyl butyl acetate(3.3%), Acrylic polymer-B(23.5%), Aromatic hydrocarbon(1.4%), Butyl acetate(14.4%), Ethyl acetate(2.4%), Ethylbenzene(0.1 - 0.2%* @), Methyl amyl ketone(6.2%), Organoclay(1.9%), Polyester resin(16.9%), Primary amyl acetate(6.2%), Propylene glycol monomethyl ether acetate(3.7%), Quinacridone pigment(4.0%), Titanium dioxide(9.0%)

GAL WT: 9.21 WT PCT SOLIDS: 58.04 VOL PCT SOLIDS: 47.31
SOLVENT DENSITY: 7.33 VOC LE: 3.9 VOC AP: 3.9
FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

633-23666™ 2,4-pentanedione(1.6%), Acrylic polymer-B(20.3%), Amorphous silica(1.1%), Aromatic hydrocarbon(1.4%), Azo yellow pigment(1.3%), Butyl acetate(15.0%), Carbon black(0.1%), Ethyl acetate(2.2%), Ethylbenzene(0.1 - 0.2%* @), Ethylene glycol monobutyl ether acetate(1.9%* @), Methyl amyl ketone(7.7%), Organoclay(1.9%), Polyester resin(15.3%), Propylene glycol monomethyl ether acetate(6.9%), Titanium dioxide(17.9%)

GAL WT: 9.93 WT PCT SOLIDS: 60.61 VOL PCT SOLIDS: 46.98
SOLVENT DENSITY: 7.38 VOC LE: 3.9 VOC AP: 3.9
FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES

633-23665™ 2,4-pentanedione(1.6%), Acrylic polymer-B(22.7%), Amorphous silica(1.1%), Aromatic hydrocarbon(1.3%), Butyl acetate(13.8%), Ethyl acetate(1.9%), Ethylbenzene(0.1 - 0.2%* @), Methyl amyl ketone(5.9%), Organoclay(1.8%), Phthalocyanine blue pigment(2.2%), Polyester resin(13.0%), Propylene glycol monomethyl ether acetate(11.6%), Titanium dioxide(17.7%)

GAL WT: 9.97 WT PCT SOLIDS: 60.74 VOL PCT SOLIDS: 47.60
SOLVENT DENSITY: 7.47 VOC LE: 3.9 VOC AP: 3.9
FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

633-23664™ 1,2,4-trimethyl benzene(1.3%*), 2,4-pentanedione(1.6%), Acrylic polymer-B(28.6%), Aromatic hydrocarbon(2.0%), Butyl acetate(20.1%), Ethyl acetate(2.6%), Ethylbenzene(0.1 - 0.2%* @), Isoindolinone pigment(1.1%), Methyl amyl ketone(6.8%), Organoclay(2.7%), Polyester resin(17.7%), Propylene glycol monomethyl ether acetate(7.5%), Quinacridone pigment(4.4%)

GAL WT: 8.65 WT PCT SOLIDS: 56.04 VOL PCT SOLIDS: 48.46
SOLVENT DENSITY: 7.59 VOC LE: 3.8 VOC AP: 3.8
FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES

633-23663™ 2,4-pentanedione(1.6%), Acrylic polymer-B(24.2%), Aromatic hydrocarbon(1.2%), Azo yellow pigment(8.5%), Butyl acetate(12.1%), Ethyl acetate(2.2%), Ethylbenzene(0.1 - 0.2%* @), Methyl amyl ketone(6.8%), Organoclay(1.6%), Polyester resin(15.2%), Propylene glycol monomethyl ether acetate(14.9%), Titanium dioxide(6.1%), Yellow iron oxide(1.7%)

GAL WT: 9.32 WT PCT SOLIDS: 58.75 VOL PCT SOLIDS: 48.78
SOLVENT DENSITY: 7.51 VOC LE: 3.8 VOC AP: 3.8
FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

633-23662™ 2,4-pentanedione(1.6%), Acrylic polymer-B(23.7%), Aromatic hydrocarbon(1.3%), Barium sulfate(1.1%), Butyl acetate(13.0%), Ethyl acetate(2.3%), Ethylbenzene(0.1 - 0.2%* @), Isoindolinone

pigment(6.3%), Methyl amyl ketone(6.6%), Monoazo pigment(5.3%), Organoclay(1.7%), Polyester resin(16.1%), Propylene glycol monomethyl ether acetate(14.6%), Titanium dioxide(2.8%)

GAL WT: 9.18 WT PCT SOLIDS: 58.21 VOL PCT SOLIDS: 48.88
SOLVENT DENSITY: 7.50 VOC LE: 3.8 VOC AP: 3.8
FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 1 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

633-100™ 2,4-pentanedione(1.6%), Acrylic polymer-B(21.0%), Aromatic hydrocarbon(1.2%), Azo yellow pigment(6.2%), Butyl acetate(12.6%), Ethyl acetate(2.5%), Ethylbenzene(0.1 - 0.2%* @), Methyl amyl ketone(5.4%), Organoclay(1.6%), Polyester resin(17.9%), Propylene glycol monomethyl ether acetate(13.8%), Titanium dioxide(7.4%), Yellow iron oxide(3.9%)

GAL WT: 9.59 WT PCT SOLIDS: 60.26 VOL PCT SOLIDS: 49.27
SOLVENT DENSITY: 7.52 VOC LE: 3.8 VOC AP: 3.8
FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

1333-67640™ 2,4-pentanedione(1.1%), 2-ethylhexyl acetate(1.5%), 4-chlorobenzotrifluoride(4.6%), Acetone(4.3%), Acrylic polymer-A(8.2%), Butyl acetate(8.0%), Carbon black(1.8%), Ethyl acetate(4.6%), Ethylbenzene(0.7 - 1.6%* @), Polyester resin(54.3%), Propylene glycol monomethyl ether acetate(1.4%), Substituted benzotriazole(1.0%), Xylene(4.9 - 5.8%* @)

GAL WT: 8.82 WT PCT SOLIDS: 67.12 VOL PCT SOLIDS: 62.06
SOLVENT DENSITY: 7.62 VOC LE: 2.3 VOC AP: 2.1
FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES

1333-67637™ 4-chlorobenzotrifluoride(4.8%), Acetone(4.0%), Acrylic polymer-B(4.8%), Aluminum hydrate(1.1%), Amorphous silica(1.8%), Ethyl acetate(2.8%), Ethylbenzene(0.2 - 0.5%* @), Methyl amyl ketone(1.5%), Polyester resin(35.2%), Propylene glycol monomethyl ether acetate(8.9%), Titanium dioxide(28.7%), Xylene(1.6 - 2.0%* @)

GAL WT: 11.47 WT PCT SOLIDS: 73.74 VOL PCT SOLIDS: 61.95
SOLVENT DENSITY: 7.91 VOC LE: 2.3 VOC AP: 2.0
FLASH POINT: 20°F to below 73°F H: 1 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

1333-67635™ 4-chlorobenzotrifluoride(4.6%), Acetone(4.3%), Acrylic polymer-B(4.6%), Aluminum hydrate(1.1%), Amorphous silica(1.8%), Ethyl acetate(3.0%), Ethylbenzene(0.2 - 0.5%* @), Methyl amyl ketone(1.5%), Polyester resin(35.3%), Propylene glycol monomethyl ether acetate(9.0%), Titanium dioxide(28.8%), Xylene(1.6 - 2.0%* @)

GAL WT: 11.46 WT PCT SOLIDS: 73.55 VOL PCT SOLIDS: 61.59
SOLVENT DENSITY: 7.88 VOC LE: 2.3 VOC AP: 2.0
FLASH POINT: 20°F to below 73°F H: 1 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

1333-67633™ 2-ethylhexyl acetate(1.1%), 4-chlorobenzotrifluoride(5.0%), Acetone(4.6%), Acrylic polymer-B(5.2%), Amorphous silica(1.5%), Butyl acetate(1.2%), Carbon black(0.3%), Ethyl acetate(3.2%), Ethylbenzene(0.3 - 0.7%* @), Methyl amyl ketone(1.6%), Polyester resin(37.8%), Propylene glycol monomethyl ether acetate(7.7%), Titanium dioxide(23.8%), Xylene(2.1 - 2.5%* @)

GAL WT: 10.90 WT PCT SOLIDS: 71.86 VOL PCT SOLIDS: 60.88
SOLVENT DENSITY: 7.83 VOC LE: 2.3 VOC AP: 2.0
FLASH POINT: 20°F to below 73°F H: 1 F: 3 R: 1 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES

1333-67632™ 4-chlorobenzotrifluoride(4.8%), Acetone(4.0%), Acrylic polymer-B(4.7%), Aluminum hydrate(1.1%), Amorphous silica(1.8%), Ethyl acetate(2.8%), Ethylbenzene(0.2 - 0.5%* @), Methyl amyl ketone(1.6%), Polyester resin(34.5%), Propylene glycol monomethyl ether acetate(9.2%), Titanium dioxide(29.8%), Xylene(1.5 - 1.8%* @)

GAL WT: 11.59 WT PCT SOLIDS: 73.94 VOL PCT SOLIDS: 61.91
SOLVENT DENSITY: 7.92 VOC LE: 2.3 VOC AP: 2.0
FLASH POINT: 20°F to below 73°F H: 1 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

1333-23666™ 2-ethylhexyl acetate(1.2%), 4-chlorobenzotrifluoride(5.7%), Acetone(5.3%), Acrylic polymer-B(5.3%), Ethyl acetate(3.6%), Ethylbenzene(0.3 - 0.7%* @), Methyl amyl ketone(3.7%), Polyester

resin(43.4%), Propylene glycol monomethyl ether acetate(6.3%), Titanium dioxide(14.4%), Xylene(2.1 - 2.5%* @), Yellow iron oxide(1.6%)

GAL WT: 10.10 WT PCT SOLIDS: 69.35 VOL PCT SOLIDS: 60.15
SOLVENT DENSITY: 7.76 VOC LE: 2.3 VOC AP: 2.0
FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 1 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES

1333-23665™ 2-ethylhexyl acetate(1.3%), 4-chlorobenzotrifluoride(5.1%), Acetone(4.5%), Acrylic polymer-B(5.4%), Ethyl acetate(4.5%), Ethylbenzene(0.3 - 0.8%* @), Methyl amyl ketone(1.7%), Phthalocyanine blue pigment(1.0%), Polyester resin(51.0%), Propylene glycol monomethyl ether acetate(7.2%), Titanium dioxide(10.1%), Xylene(2.4 - 2.8%* @)

GAL WT: 9.72 WT PCT SOLIDS: 71.13 VOL PCT SOLIDS: 64.22
SOLVENT DENSITY: 7.83 VOC LE: 2.1 VOC AP: 1.9
FLASH POINT: 20°F to below 73°F H: 1 F: 3 R: 1 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: YES

1333-23664™ 2-ethylhexyl acetate(1.4%), 4-chlorobenzotrifluoride(4.1%), Acetone(3.8%), Acrylic polymer-B(8.7%), Ethyl acetate(3.4%), Ethylbenzene(0.3 - 0.7%* @), Methyl amyl ketone(2.5%), Monoazo pigment(6.8%), Polyester resin(43.4%), Propylene glycol monomethyl ether acetate(13.3%), Quinacridone pigment(4.6%), Xylene(2.1 - 2.5%* @)

GAL WT: 9.15 WT PCT SOLIDS: 66.49 VOL PCT SOLIDS: 60.78
SOLVENT DENSITY: 7.81 VOC LE: 2.6 VOC AP: 2.3
FLASH POINT: 20°F to below 73°F H: 1 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

1333-23663™ 2-ethylhexyl acetate(1.3%), 4-chlorobenzotrifluoride(3.8%), Acetone(3.6%), Acrylic polymer-B(6.7%), Azo yellow pigment(6.9%), Ethyl acetate(3.8%), Ethylbenzene(0.3 - 0.7%* @), Methyl amyl ketone(2.1%), Polyester resin(45.0%), Propylene glycol monomethyl ether acetate(13.2%), Titanium dioxide(5.4%), Xylene(2.1 - 2.5%* @), Yellow iron oxide(1.0%)

GAL WT: 9.49 WT PCT SOLIDS: 67.76 VOL PCT SOLIDS: 60.93
SOLVENT DENSITY: 7.83 VOC LE: 2.6 VOC AP: 2.4
FLASH POINT: 20°F to below 73°F H: 1 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

1333-23662™ 2-ethylhexyl acetate(1.3%), 4-chlorobenzotrifluoride(4.0%), Acetone(3.7%), Acrylic polymer-B(7.5%), Ethyl acetate(3.9%), Ethylbenzene(0.3 - 0.7%* @), Isoindolinone pigment(4.4%), Methyl amyl ketone(2.4%), Monoazo pigment(4.7%), Polyester resin(46.6%), Propylene glycol monomethyl ether acetate(12.2%), Titanium dioxide(1.8%), Xylene(2.2 - 2.6%* @)

GAL WT: 9.32 WT PCT SOLIDS: 68.18 VOL PCT SOLIDS: 62.09
SOLVENT DENSITY: 7.81 VOC LE: 2.5 VOC AP: 2.2
FLASH POINT: 20°F to below 73°F H: 1 F: 3 R: 1 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

RK 31251™ 2-ethylhexyl acetate(5.4%), Acetone(3.3%), Acrylic polymer-D(50.6%), Dimethyl glutarate(2.3%), Isopropyl alcohol(1.4%), Medium mineral spirits(1.5%), Methyl amyl ketone(30.5%)

GAL WT: 7.97 WT PCT SOLIDS: 51.27 VOL PCT SOLIDS: 43.94
SOLVENT DENSITY: 6.93 VOC LE: 3.8 VOC AP: 3.6
FLASH POINT: 20°F to below 73°F H: 2 F: 3 R: 0 OSHA STORAGE: IB
TSCA STATUS: In Compliance PHOTO-CHEMICALLY REACTIVE: NO

Footnotes:

TSCA: in compliance = In compliance with TSCA Inventory requirements for commercial purposes.

ACGIH = American Conference of Government Industrial Hygienists.

IARC = International agency for Research on Cancer.

NTP = National Toxicology Program.

OSHA = Occupational Safety and Health Administration.

PNOR = Particles Not Otherwise Regulated.

PNOC = Particles Not Otherwise Classified.

STEL = Short Term Exposure Limit.

TWA = Time Weighted Average.

TM = Is a Trademark of E.I. du Pont de Nemours & Co.

* = Section 313 Supplier Notification: These chemicals are subject to the reporting requirements of Section 313 of the Emergency planning and Right-to-Know act of 1986 and of 40 CFR 372.

@ = Clean Air Act Hazardous Air Pollutant.

= EPCRA Section 302 - Extremely Hazardous Substance.

NOTICE:

The information on this Material Safety Data Sheet relates only to the specific material designated herein and does not relate to use in combination with any other material or in any process.

Product Manager - Refinish Sales
Prepared by: HazCom Coordinator